

RG 104, Sequence 25

8NN-104-86-025, Register of Assays on
Bullion Deposits, 1916 - 1972.

FORM 123

**REGISTER OF ASSAYS
GOLD AND SILVER DEPOSITS**





8NN-104-86-025

Vol 16 of 16

16/38/3'2

J.Y. 1967 Continued

Form 123
TREASURY DEPARTMENT
MINT SERVICE

REGISTER OF ASSAYS,

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
11/23/66		3:30	391	393	Bars	S. Nakata	157544
			392	394	"	" "	289487
			393	395	PI Scrap	" Ind	54449
			394	396	"	"	11552
			395	397	Port	Balo - Adams	2362
			396	398	Scrap	Ind	45471
			397	399	Port	Calif.	1418
			398	400	Scrap	Jewelry Ind	251
			399	401	Wet Sweeps	Ind	41567
			400	402	Scrap	"	119641
			401	403	Gr Nags	Alaska	139
			402	404	This receipt changed to #14-416 - 417		
			403	405	Scrap	Ind	2978
			404	406	Bars	S. Nakata	590614
			405	407	Barin	Montebalest Barin	26721
	J.M. better		C-39	C-39	Gold Coin	1-50 Peso	133
	11/18/66		C-40	C-40	Gold Coin	3-Spanish	079
			406	408	Wet Sweeps	Ind	53160
11/30	9am.		407	409	Bars	S. Nakata	325876
12/1	1:35pm.		408	410	"	" "	280157
			409	411	Scrap	Ind	3073
			410	412	"	Plental "	617
			411	413	"	"	970
			412	414	"	"	65556
			413	415	"	"	64872
			414	416	Magnetic	Ind	71981
			"	417	Contacts	Steel Wire Removed	40623
			415	418	Scrap	Ind	72924
			416	419	"	"	119623
			417	420	Wet Sweeps	"	46106

PART

Shipment 1392.85
132.83 " 7.183.83
Steel Wire Removed 1259.02

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
996 $\frac{3}{4}$			0			\$	\$	\$	\$
998 $\frac{3}{4}$			0				"		
992 $^{\circ}$	1 $^{\circ}$	207 $^{\circ}$	16				Motorola		
998 $^{\circ}$			0				"		
906 $^{\circ}$	90 $^{\circ}$	4 $^{\circ}$	12				Jenckling & Plummer		
409 $^{\circ}$	13 $^{\circ}$	460 $^{\circ}$	18				Joster		
828 $^{\circ}$	164 $^{\circ}$	8 $^{\circ}$	12				Carl Ricci; West Sacramento, Calif		
563 $^{\circ}$	102 $^{\circ}$	335 $^{\circ}$	18				Monovan & Christman; Exira, Ia		
412 $^{\circ}$	113 $^{\circ}$	474 $\frac{1}{2}$	18			7 $\frac{55}{100}$ M.	Joster		
407 $\frac{1}{2}$	119 $^{\circ}$	473 $\frac{1}{2}$	18				"		
717 $^{\circ}$	280 $^{\circ}$	3 $^{\circ}$	12				Henry M. Mason; Portland, Oregon		
524 $\frac{1}{2}$	119 $^{\circ}$	356 $\frac{1}{2}$	21				Jackson Jewelry Co; Omaha, Nebr.		
997 $^{\circ}$			0				Hammett		
0 $^{\circ}$	877 $^{\circ}$	123 $^{\circ}$	0				Lupit		
900 $^{\circ}$	0 $^{\circ}$	100 $^{\circ}$	0				Miss Glenda Jones; Houston, Tex		
900 $^{\circ}$	0 $^{\circ}$	100 $^{\circ}$	0				Miss Eva Johnson; Austin, Tex		
416 $^{\circ}$	130 $^{\circ}$	454 $^{\circ}$	18			9 $\frac{05}{100}$ M.	Joster		
996 $\frac{3}{4}$			0				Hammett		
997 $\frac{3}{4}$			0				"		
507 $^{\circ}$	116 $^{\circ}$	377 $^{\circ}$	21				McNitt Jewelry Co; Dallas		
769 $^{\circ}$	107 $^{\circ}$	124 $^{\circ}$	13				Dr. Harry E. Stuart; Los Angeles		
446 $\frac{1}{2}$	60 $^{\circ}$	493 $\frac{1}{2}$	18				LeMaster Jewelry; Amarillo, Tex		
354 $^{\circ}$	186 $^{\circ}$	490 $^{\circ}$	18				Joster		
360 $\frac{1}{2}$	115 $^{\circ}$	524 $\frac{1}{2}$	18				"		
235 $^{\circ}$	9 $^{\circ}$	756 $^{\circ}$	23				Texas Bank Bury, Dallas		
288 $\frac{1}{2}$	15 $^{\circ}$	696 $\frac{1}{2}$	23				" " " "		
406 $^{\circ}$	76 $^{\circ}$	578 $^{\circ}$	18				Joster		
418 $\frac{1}{2}$	125 $^{\circ}$	456 $\frac{1}{2}$	18				"		
421 $\frac{1}{2}$	124 $^{\circ}$	454 $\frac{1}{2}$	18			8 $\frac{30}{100}$ M.	"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
12/1	P.M. 3		418	421	Scrap	Ind	1152.01
			419	422	Bars	S. Lakota	3500.02
			420	423	Scrap	Ind	427.44
			421	424	7-Scrap	"	188.48
			422	425	"	"	1470.05
12/6	4M 9:30		423	426	King Scrap	Colo - Kiggins	3.00
			424	427	Spec. S.	Ind	13.43
			425	428	Scrap	"	52.76
			426	429	Wet Sweeps	"	1194.26
			427	430	Scrap Wet	Jewelry	1410.46
			428	431	Sweeps	"	466.36
			429	432	Retort	Colo - Jeff	27.17
			430	433	"	" - Adams	25.65
			431	434	"	" - Jeff	29.90
			432	435	"	" - Adams	25.37
12/7	P.M. 3:30		433	436	Bars	S. Lakota	2867.96
			434	437	-	-	3132.59
			435	438	Scrap	Ind	184.25
			436	439	-	-	59.37
			437	440	Retort	Idaho - Boise	21.47
			438	441	Scrap	Jewelry Ind	592.36
			439	442	-	-	912.77
			440	443	-	-	15.23
		J.M. Better 11/29/66	441	444	5-Gold Dental strips	Forfeited Gold Ind	0.95
			442	445	Scrap	Dental	1.87
12/12	A.B. S.B.		5	5	Grains	Grain's bar Nov + Paris	21.99
			7	7	S.B.	2nd Quarter Chimp II to R. II ML	12.00
			443	446	Bars	S. Lakota	6526.04
			444	447	Scrap	Ind	355.6
			445	448	Scrap	"	232.89

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 398 1/2	80 1/2	521 1/2	18			\$	\$		\$
✓ 996 1/2			0				Jester		
✓ 396 1/2	91 1/2	512 1/2	18			6 05 h.m.	Homestake		
✓ 964 1/2	0 1/2	35 1/2	6				John Roberts Mfg Co.		
✓ 932 1/2	2 1/2	65 1/2	13				Mokoroala		
✓ 776 1/2	162 1/2	62 1/2	13				"		
✓ 327 1/2	97 1/2	575 1/2	21			2 30 h.m.	Theodore F. Morse; Golden		
✓ 480 1/2	95 1/2	424 1/2	16			2 30 h.m.	Samuel Schuman; Chicago		
✓ 402 1/2	118 1/2	479 1/2	18			16 55 h.m.	Atlas Pawn Shop; Cheyenne		
✓ 396 1/2	102 1/2	502 1/2	18				Jester		
✓ 421 1/2	126 1/2	453 1/2	18			8 30 h.m.	"		
✓ 854 1/2	143 1/2	3 1/2	12				Franking & Plunker		
✓ 866 1/2	130 1/2	4 1/2	12				"		
✓ 837 1/2	150 1/2	12 1/2	12				"		
✓ 856 1/2	100 1/2	43 1/2	12			2 30 h.m.	"		
✓ 996 3/4			0				Homestake		
✓ 997 1/2			0				"		
✓ 589 1/2	100 1/2	311 1/2	18				J.W.S. & Ref Co.		
✓ 504 1/2	137 1/2	359 1/2	21			2 30 h.m.	"		
✓ 758 1/2	236 1/2	6 1/2	12				A.W. Josue; Golden Valley, Cal		
✓ 414 1/2	109 1/2	476 1/2	18				Jester		
✓ 422 1/2	160 1/2	418 1/2	16				"		
✓ 486 1/2	83 1/2	431 1/2	16				Globe Pawn Shop; Okla City, Okla.		
✓ 891 1/2	31 1/2	77 1/2	0			CHARGES Waived	First Nat. Customs; Haverhill, Tex		
✓ 757 1/2	122 1/2	120 1/2	13				Prof. Mr. H.P. Geigunheim; Columbus, Neb.		
✓ 753 1/2	64 1/2	182 1/2	0				Supt		
✓ 404 1/2	132 1/2	464 1/2	0				"		
✓ 997 1/2			0				Homestake		
✓ 556 1/2	54 1/2	390 1/2	21				Atlas Pawn Shop; Cheyenne		
✓ 935 1/2	31 1/2	61 1/2	13				Mokoroala		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 920300

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
12/12		114M	446	449	Gold Salt	Ind	192
			447	450	Scrap jewelry	"	1 046 17
			448	451	✓	"	1 091 91
			449	452	Wet Sweeps	"	457 26
			450	453	Scrap jewelry	"	44 48
			451	454	"	"	4 99
			452	455	Scrap	"	44 06
12/13	S.B.	114M	8	8	S.B. "K" Grains #5 Etc		21 17
12/15		3PM	453	456	Sludge	Ind	88 97
			454	457	Bars S. Black		2 235 70
			455	458	"	"	2 271 44
	Rejected		456	459	Amalgam Nats Grs Nugs	Deposit rejected because did not meet min requirements Added to deposit #457 B.M.	
			457	460	Nevada-Pershing	10.99	486
			458	461	Scrap jewelry	Ind	875 52
			459	462	✓	✓	869 03
			460	463	✓	✓	870 35
			461	464	✓	✓	1 650 58
			462	465	Emblems	✓	730 19
			463	466	Scrap jewelry	✓	1 001 38
			464	467	✓	✓	999 66
			465	468	✓	✓	1 024 17
			466	469	✓	✓	934 04
			467	470	Bars S. Black		5 118 55
			468	471	Retort Colo - Kilpin		3 33
12/19 Am			469	472	Scrap	Ind	322 54
	Reject Refract Refract		470	473	Scrap	Ind	553 33
			471	474	✓	✓	30 25 33 94
			472	475	✓	✓	317 23
			473	476	✓		369 27
			474	477	✓	Jewelry	331 55

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 992 ¹⁰	0 ¹⁰	8 ¹⁰	6			2 ³⁰ b.u.	\$	David H. Norton Jr;	\$
✓ 419 ¹ / ₂	137 ¹⁰	443 ¹ / ₂	16					Josten	
✓ 396 ¹ / ₂	105 ¹⁰	448 ¹ / ₂	18					"	
✓ 418 ¹⁰	129 ¹⁰	453 ¹⁰	18			8 ³⁰ b.u.		"	
✓ 527 ¹ / ₂	99 ¹⁰	373 ¹ / ₂	21					Star Jewellery Inc; Houston	
✓ 576 ¹ / ₂	273 ¹⁰	150 ¹ / ₂	16			2 ³⁰ b.u.		Advance Metal Lab; Denver	
✓ 268 ¹⁰	391 ¹⁰	41 ¹⁰	17					Motorola	
✓ 447 ¹⁰	114 ¹⁰	439 ¹⁰	0					Supt.	
✓ 855 ¹ / ₂	14 ¹⁰	130 ¹ / ₂	13			13 ⁵⁵ b.u.		Texas Inst. Inc.	
✓ 997 ¹⁰			0					Hamestake	
✓ 998 ³ / ₄			0					"	
Reject						4 ⁰⁵ melting charge		BOM Mining; Las Vegas, Nevada.	
✓ 810 ¹ / ₂	168 ¹⁰	21 ¹ / ₂	12			2 ³⁰ b.u.		BOM Mining; Las Vegas, Nevada	
✓ 340 ¹⁰	201 ¹⁰	459 ¹⁰	18					Josten	
✓ 397 ¹⁰	116 ¹⁰	487 ¹⁰	18					"	
✓ 371 ¹ / ₂	156 ¹⁰	472 ¹ / ₂	18					"	
✓ 392 ¹ / ₂	120 ¹⁰	487 ¹ / ₂	18					"	
✓ 393 ¹⁰	62 ¹⁰	545 ¹⁰	18					O. C. Tanner, Inc.	
✓ 387 ¹ / ₂	89 ¹⁰	523 ¹ / ₂	18					Josten	
✓ 398 ¹⁰	76 ¹⁰	526 ¹⁰	18					"	
✓ 390 ¹ / ₂	106 ¹⁰	503 ¹ / ₂	18					"	
✓ 387 ¹ / ₂	95 ¹⁰	517 ¹ / ₂	18					"	
✓ 996 ⁵ / ₈			0					Hamestake	
✓ 829 ¹⁰	166 ¹⁰	5 ¹⁰	12					Staniel Ranch, Black Hawk, Colo.	
✓ 925 ¹ / ₂	5 ¹⁰	69 ¹ / ₂	13					Motorola	Phoenix
✓ 118	2	880	20					Motorola	
Reject: Turn. Concordant Average								"	
✓ 860 ¹ / ₂	5 ¹⁰	134 ¹ / ₂	13			4 ⁵⁵ b.u.		"	
✓ 415 ¹ / ₂	101 ¹⁰	483 ¹ / ₂	18			6 ⁰⁵ b.u.		John Roberts Mfg Co.	
✓ 397 ¹ / ₂	114 ¹⁰	488 ¹ / ₂	18					Josten	

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 830500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
Dec.	15	3 PM	475	478	Scrap	Jewelry Ind	570.43
			476	479	✓	✓	1 051.98
12/19	PM		477	480	✓	✓	223.38
			478	481	Dent	✓	9.72
	20	2 PM	479	482	Bars	S. slak.	2 447.26
			480	483	"	"	4 264.92
			481	484	6-Retort Am ers	Colo - San Miguel	96.93
			482	485	PI Scrap	Ind	130.80
			483	486	✓	✓	852.29
			484	487	Scrap	Jewelry	961.74
	22	10:30 AM	485	488	✓	✓	887.96
	Rejct ?		486	489	✓	✓	2.24
			487	490	Wet Anceps	✓	449.00
			488	491	✓	✓	578.49
			489	492	Scrap	Jewelry	609.44
			490	493	✓	✓	608.79
			491	494	Wet Anceps	✓	545.24
Dec.	23	9 AM	492	495	Bars	S. slakata	5 153.18
			493	496	Scrap	Jewelry Ind	71.88
			494	497	Leaf	"	204.53
			495	498	Ret	Colo - Orony	836.17
			496	499	Scrap	Ind	1 048.52
Dec.	27	10 ¹⁵ AM	497	500	Scrap	Jewelry	1 031.93
			498	501	✓	✓	1 003.35
			499	502	✓	✓	635.94
			500	503	✓	✓	1 267.61
			501	504	Mut COIN	Mutilated 16 Coin	158.93
Dec.	29	10 ¹⁵ AM	502	505	Retort	Idaho - Jerome	5.33
	12/20/66		C-41	C-41	Coin	1-20 Peso	0.53
	✓		C-42	C-42	✓	1-5.00 U.S. Coin	0.26

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
389 ¹⁰	93 ¹⁰	518 ¹⁰	18			\$	\$		\$
388 ^{1/2}	114 ¹⁰	497 ^{1/2}	18				Jostin		
442 ^{1/2}	125 ¹⁰	432 ^{1/2}	16				"		
727 ¹⁰	142 ¹⁰	131 ¹⁰	13				J.L. Thorpe	Deadwood, S. Dak.	
997 ^{1/4}			0				Dr. Douglas F. Pincock,	Agden, Utah	
997 ^{1/2}			0				Honestake		
664 ^{1/2}	333 ¹⁰	2 ^{1/2}	12				"		
998 ^{1/2}			0				Koskineen Bros;	Tecknide, Colo.	
956 ¹⁰	3 ¹⁰	41 ¹⁰	6				Motorola		
430 ¹⁰	139 ¹⁰	431 ¹⁰	16				"		
423 ¹⁰	114 ¹⁰	463 ¹⁰	18				Jostin		
281 ^{1/2}	101 ¹⁰	617 ^{1/2}	21				"		
420 ¹⁰	131 ¹⁰	449 ¹⁰	16			8 ³⁰ h.M.	Rt. E. Widdows;	Fort Laramie, Colo.	
416 ^{1/2}	137 ¹⁰	446 ^{1/2}	16			9 ³⁰ "	Jostin		
413 ¹⁰	118 ¹⁰	469 ¹⁰	18				"		
422 ^{1/2}	135 ¹⁰	442 ^{1/2}	16				"		
419 ^{1/2}	138 ¹⁰	442 ^{1/2}	16			9 ⁰⁵ h.M.	"		
996 ^{1/4}			0				Honestake		
521 ¹⁰	64 ¹⁰	415 ¹⁰	21				Gordon Erickson Co,	Man, Minn.	
593 ¹⁰	120 ¹⁰	287 ¹⁰	18				S.W. D. & Ref Co;		
459 ^{1/2}	183 ¹⁰	357 ^{1/2}	16				Idaho Co.		
261 ¹⁰	1 ¹⁰	738 ¹⁰	23				Texas Inst. Luc.		
409 ¹⁰	131 ¹⁰	460 ¹⁰	18				Jostin		
373 ^{1/2}	169 ¹⁰	457 ^{1/2}	18				"		
401 ¹⁰	108 ¹⁰	491 ¹⁰	18				"		
400 ^{1/4}	113 ¹⁰	487 ¹⁰	18				"		
0 ¹⁰	894 ¹⁰	106 ¹⁰	0				Supt		
952 ¹⁰	47 ¹⁰	1 ¹⁰	6				Ther Stewart;	Burley; Idaho	
900 ¹⁰	0 ¹⁰	100 ¹⁰	0				Morris Adams M. ad.	St. Louis, Mo.	
900 ¹⁰	0 ¹⁰	100 ¹⁰	0				"	"	"

REGISTER OF ASSAYS,

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received 1966	Reported	Hour	Receipt	Assay			
Dec. 27			C-43	C-43	Coin	1-50 Peso Mex	133
			C-44	C-44	✓	1-50 Peso 1-20 " 1-10 "	234
			C-45	C-45	✓	1-20 Peso	053
Dec. 28	11 ²⁵		503	506	Retort	Celo - Jeff	744
			504	507	Scrap	Jewelry	96146
			505	508	✓	✓	110296
			506	509	✓	✓	50269
			507	510	✓	✓	1172
Dec. 28	3 ³⁰ P.M.		508	511	Bars	S. Dakota	168173
			509	512	✓	✓	383998
			510	513	Scrap	Jewelry	5164
			511	514	Scrap	"	40281
			512	515	Scrap	"	33989
			513	516	Scrap	Jewelry	316
			514	517	✓	✓	3404
Dec 29	3:30		515	518	Bars.	S. Dakota	524086
"	30	2:30	516	519	Scrap	Jud	38962
			517	520	Scrap	"	55430
			518	521	✓	"	104584
1967			519	522	met scrap	"	53512
Jan. 5	11 AM		520	523	Scrap	"	5462
			521	524	"	Hebital	791
			522	525	"	"	3829
Jan 3 1967			523	526	Bars	S. Dakota	485437
			"	527	"	"	472313
			524	528	"	"	409032
Jan 5	11 AM		525	529	Scrap	Jewelry	116158
			526	530	✓	✓	66294
			527	531	✓	✓	130289
			528	532	✓	✓	86861

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 900 ¹⁰	0 ¹⁰	100 ¹⁰		0		\$			
✓ 900 ¹⁰	0 ¹⁰	100 ¹⁰		0			Miss Eloris Gilbert; Tulsa, Okla.		
✓ 900 ¹⁰	0 ¹⁰	100 ¹⁰		0			Mr. H. M. Mose; Montebello, N. J.		
✓ 900 ¹⁰	0 ¹⁰	100 ¹⁰		0			Mrs. Joseph H. Ray; H. House, Mo.		
✓ 867 ¹⁰	129 ¹⁰	41 ¹⁰		12			Robert B. Ray & Suburban		
✓ 426 ^{1/2}	128 ¹⁰	445 ^{1/2}		16			Josten		
✓ 391 ^{1/2}	125 ¹⁰	483 ^{1/2}		18			"		
✓ 391 ¹⁰	125 ¹⁰	484 ¹⁰		18			"		
✓ 406 ^{1/2}	122 ¹⁰	471 ^{1/2}		18			Baum's; Wichita, Kans.		
✓ 996 ¹⁰				0			Hornestake		
✓ 997 ^{1/2}				0			"		
✓ 504 ^{1/2}	83 ¹⁰	412 ^{1/2}		21			Berger & Co; Houston		
✓ 883 ^{1/2}	1 ¹⁰	115 ^{1/2}		13			Motorola.		
✓ 413 ^{1/2}	89 ¹⁰	497 ^{1/2}		18		5 ³⁰ h.M.	John Roberts Mfg Co.		
✓ 516 ¹⁰	177 ¹⁰	307 ¹⁰		18			Arvel M. Beckman Sr; Texas City		
✓ 548 ¹⁰	78 ¹⁰	374 ¹⁰		21			Linsberg Jewelers; Cedar Rapids.		
✓ 997 ¹⁰				0			Hornestake		
✓ 798 ^{1/2}	2 ¹⁰	199 ^{1/2}		16			Motorola		
✓ 391 ^{1/2}	125 ¹⁰	483 ^{1/2}		18			Josten		
✓ 411 ¹⁰	114 ¹⁰	475 ¹⁰		18			"		
✓ 419 ¹⁰	122 ¹⁰	459 ¹⁰		18		9 ⁰⁵ h.M.	"		
✓ 602 ^{1/2}	111 ¹⁰	286 ^{1/2}		18			Louis Spiegel; Ranoga Park, Calif.		
✓ 624 ¹⁰	243 ¹⁰	133 ¹⁰		13		2 ³⁰ h.M.	Paul Blumrock; Denver.		
✓ 444 ^{1/2}	80 ¹⁰	425 ^{1/2}		16		2 ³⁰ "	Star Jewelry Co.; Houston, Tex		
✓ 996.8				0			Hornestake		
✓ 997.1				0			"		
✓ 997 ^{3/4}				0			"		
✓ 394 ¹⁰	113 ¹⁰	493 ¹⁰		18			Josten		
✓ 400 ¹⁰	47 ¹⁰	553 ¹⁰		21			"		
✓ 409 ¹⁰	89 ¹⁰	492 ¹⁰		18			"		
✓ 428 ^{1/2}	60 ¹⁰	511 ^{1/2}		18			"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 10-50000

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
1967							
Jan 5 11am			529	533	Scrap	Jewelry Ind	102931
			530	534	"	"	104650
			531	535	"	"	106085
			532	536	met Sweeps	"	47554
			533	537	Scrap	Jewelry	66463
			534	538	✓	"	104252
			535	539	Res. R Scrap	"	2203
Jan 6 11am. <i>Remelt</i>			6	6	6. Bar	Deposits December 1966	Re 19 97 20 44
			536	540	Bars	S. Dakota	136661
			537	541	Filings	Ind	59 14
			538	542	Scrap	"	14014
			539	543	Filings	"	29 85
			540	544	Retort	Colo-Jeff	20 71
<i>Remelt</i>			541	545	Scrap	Ind	Re 25 54 25 82
			542	546	✓	Jewelry	619 82
			543	547	✓	"	16749
1/9/67 3PM			544	548	✓	"	5002
			545	549	Bars	S. Dak.	527065
			546	550	"	"	380277
			547	551	Scrap	Ind	60534
			548	552	Sweeps	"	5600
			549	553	Retort	Colo - A.	16 27
			550	554	"	" - A.	1058
1/13 9am <i>L.B.</i>			9	9	"K" #6	"K" Grav's #6 from Cruc. Rec. etc.	19 90
			551	555	Retort	Colo - Adams	21 69
			552	556	Scrap	Jewelry Ind	106215
			553	557	✓	✓	67830
			554	558	Sweeps	✓	53350
			555	559	Scrap	Jewelry ✓	544 96
			556	560	✓	✓	410 65

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 300 ¹⁰	305 ¹⁰	395 ¹⁰	16			\$	\$	\$	\$
✓ 396 ^{1/2}	106 ¹⁰	497 ^{1/2}	18				<i>Jostin</i>		
✓ 408 ^{1/2}	122 ¹⁰	469 ^{1/2}	18				"		
✓ 420 ^{1/2}	122 ¹⁰	457 ^{1/2}	18			8 ³⁰ h.m.	"		
✓ 398 ^{1/2}	119 ¹⁰	482 ^{1/2}	18				"		
✓ 383 ¹⁰	114 ¹⁰	503 ¹⁰	18				"		
✓ 991 ^{1/2}	0 ¹⁰	8 ^{1/2}	6				<i>Madonala</i>		
✓ 719 ^{1/2}	65 ¹⁰	215 ^{1/2}	0				<i>Supt</i>		
✓ 997 ^{1/2}			0				<i>Homestake</i>		
✓ 514 ¹⁰	145 ¹⁰	341 ¹⁰	18			3 ⁰⁰ h.m.	<i>S.W. Smelt & Ref. Co.</i>		
✓ 599 ¹⁰	105 ¹⁰	296 ¹⁰	18				" " "		
✓ 450 ^{1/2}	162 ¹⁰	387 ^{1/2}	16				<i>Jessome Margulis; Portland, Ore.</i>		
✓ 852 ^{1/2}	143 ¹⁰	4 ^{1/2}	12				<i>Berkling & Plunker</i>		
✓ 544 ^{1/2}	85 ¹⁰	370 ^{1/2}	21			8 ⁰⁰ h.m.	<i>Tudor Smelting; Albuquerque</i>		
✓ 416 ^{1/2}	113 ¹⁰	470 ^{1/2}	18				<i>Jostin</i>		
✓ 529 ^{1/2}	79 ¹⁰	391 ^{1/2}	21				<i>S.W. Texas Precious Metals.</i>		
✓ 410 ^{1/2}	78 ¹⁰	511 ^{1/2}	18				<i>Moore Inc; Blytheville, Ark</i>		
✓ 997.4			0				<i>Homestake</i>		
✓ 997 ^{1/2}			0				"		
✓ 811 ^{1/2}	1 ¹⁰	187 ^{1/2}	16				<i>Madonala</i>		
✓ 535 ^{1/2}	39 ¹⁰	425 ^{1/2}	21				<i>Bischoff's Payor Diamond</i>		
✓ 872 ^{1/2}	124 ¹⁰	3 ^{1/2}	12				<i>Berkling & Pl.</i>		
✓ 902 ¹⁰	92 ¹⁰	6 ¹⁰	12				"		
✓ 448 ^{1/2}	137 ¹⁰	414 ^{1/2}	0				<i>Supt</i>		
✓ 856 ¹⁰	103 ¹⁰	41 ¹⁰	12				<i>Berkling & Plunker</i>		
✓ 384 ^{1/2}	69 ¹⁰	546 ^{1/2}	18				<i>Jostin</i>		
✓ 397 ¹⁰	119 ¹⁰	484 ¹⁰	18				"		
✓ 416 ¹⁰	122 ¹⁰	462 ¹⁰	18			9 ⁰⁰ h.m.	"		
✓ 398 ¹⁰	106 ¹⁰	496 ¹⁰	18				"		
✓ 397 ¹⁰	110 ¹⁰	493 ¹⁰	18				"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
1/13/67	9 AM.		557	561	Scrap jewelry	End	45603
			558	562			114220
			559	563	Rebut Idaho - Jerome		282
			560	564	Scrap jewelry	End	631
			561	565	✓	"	2179
			562	566	Bars. S. Lak		101306
			563	567	Scrap jewelry	End	196654
			564	568	✓	✓	84999
			565	569	wet sweeps	✓	52029
			566	570	Scrap jewelry	✓	94380
			567	571	✓	✓	26173
			568	572	Button	✓	180
			569	573	Scrap	✓	16903
1/13	3 PM		570	574	✓	Alutal	201
			571	575	✓	Jewelry	2202
			572	576	✓	✓	2444
1/18	9:15 AM.		573	577	Bars S. Lak.		332701
			574	578	"	"	257099
			575	579	Scrap	End	78203
			576	580	"	"	2817
			577	581	"	Jewelry	6024
			578	582	24-Bars	Fin Silver # 50396913	2502829
			"	583	25-Bars	" " # 50406937	2576540
	2:10 PM		579	584	filings	End	32259
			580	585	sweeps	"	119425
			581	586	filings	"	85095
			582	587	wet sweeps	"	44155
			583	588	filings	"	140377
			584	589	✓	"	133188
1/20	11 AM		585	590	Bars S. Lak.		329205

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
397 1/2	114 1/10	488 1/2		18		\$	\$		\$
337 1/2	205 1/10	458 1/2		18			Jostens		
458 1/2	41 1/10	1 1/10		6			"		
588 1/2	66 1/10	346 1/10		18			Thea Stewart; Burley, Idaho		
533 1/2	97 1/10	369 1/2		21			Charlie B. Scott; Austin, Texas		
996 1/2				0			Jacobson Jewelry; Omaha, Neb.		
396 1/2	105 1/10	499 1/10		18			Hornestake		
408 1/2	106 1/10	485 1/2		18			Jostens		
418 1/10	124 1/10	458 1/10		18	9 05 h.m.		"		
405 1/2	89 1/10	506 1/10		18			"		
567 1/2	49 1/10	383 1/2		21			Fischer's Tynor Tr. Co. minn.		
660 1/10	229 1/10	111 1/10		13			William Brown, Grand Jet, Colo.		
843 1/2	6 1/10	150 1/2		16	3 80 h.m.		Motorsola		
750 1/2	127 1/10	122 1/2		13			Mr. M. G. Hallenbump; Greeley, Colo.		
514 1/2	63 1/10	422 1/2		21	2 30 h.m.		Adam S. Pascal; Wichita Falls, Tex		
607 1/10	78 1/10	315 1/10		18			J. Wexler Jeweler; Houston, Tex		
997 3/4				0			Hornestake		
998 1/2				0			"		
402 1/2	103 1/10	494 1/2		18			Jostens		
530 1/10	117 1/10	353 1/10		21			Charles H. Staw; Phoenix		
507 1/2	71 1/10	421 1/2		21			Matt's Jeweler's; San Diego, Calif.		
0 1/10	998 1/2	1 1/2		0			Kennecott Copper Corp #K-106		
0 1/10	998 1/2	1 1/2		0			" " " #K-106		
398 1/10	129 1/10	473 1/10		18	6 05 h.m.		Jostens		
403 1/10	117 1/10	480 1/10		18	15 05 "		"		
406 1/10	90 1/10	504 1/10		18			"		
415 1/2	120 1/10	464 1/2		18	8 30 h.m.		"		
416 1/10	122 1/10	462 1/10		18			"		
385 1/10	126 1/10	489 1/10		18			"		
997 1/4				0			Hornestake		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 320500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
1/20	11 AM		586	591	Scrap	Ind	20323
			587	592	-	Jewelry	105179
			588	593	✓	-	46471
			589	594	✓	✓	68437
			590	595	✓	✓	68366
1/25	2:10 PM		591	596	²¹⁹⁰ Swaps	Ind	3731
			592	597	Scrap	"	289
	Remelt		593	598	✓	"	Re-2854 2864
			594	599	✓	"	5055
	Remelt		595	600	Ret	Quay - Colo.	Re-80677 81286
			596	601	Bars	S. Dak.	282666
			597	602	"	"	290202
	Remelt		598	603	Scrap	Ind	Re-111740 112621
			599	604	✓	✓	116883
			600	605	²¹⁹⁰ Swaps	✓	30190
			C-46	C-46	Coin	1-10 Peso 2-5 "	053
			C-47	C-47	"	1-5 Less	013
1/26			601	606	Scrap	Ind	1722
			602	607	✓	"	1879
			603	608	✓	"	235437
			604	609	^{met} Swaps	"	54677
			605	610	✓	"	42312
			606	611	Scrap	"	12210
			607	612	Bars	S. Dakota	334065
			608	613	²¹⁹⁰ Swaps	"	30852
			609	614	Scrap	"	112093
			610	615	✓	"	5674
	Remelt		611	616	✓	"	5516 5527
			612	617	^{met} Coin	Mutilated Coins	84838
			MCH-3	MCA-3	Coin	4-Mutilated Clad Halves	318

				AMOUNT OF CHARGES		AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.	Gold	Silver	Total
21°	82°	297°	18			\$	\$	\$
16°	83°	501°	18			S. W. S. & Ry Co.		
58°	163°	449°	16			Jostin		
86°	111°	503°	18			"		
86 1/2	117°	496 1/2	18			"		
56°	126°	418°	16		2 30 k.m.	Norman Berndt; Salt Lake		
20 1/2	96°	343 1/2	18			Loring Letterbury; Borate, Minn.		
59°	74°	369°	21		2 30 w. G. 800 melt	Peacock Jewellers; Dallas, Tex		
74 1/2	101°	424 1/2	16		2 30 k.m.	Louis W. Sprigel; Canoga Park, Calif		
504 1/2	191°	304 1/2	18		800 melt	Idarado		
96 3/4			0			Hornestake		
97 1/2			0			"		
414°	85°	501°	18		960 melt. Hold	Jostin		
416 1/2	102°	481 1/2	18			"		
98°	96°	506°	18		5 30 k.m.	John Roberts Mfg		
100°	0°	100°	0			Howard Lester Irons; Jacksonville, Fla.		
100°	0°	100°	0			Miss Dorothy Balzar; Bay City, Mich.		
548°	109°	343°	18			Barnes Jewelry & Loan Co; Seattle		
42 1/2	95°	412 1/2	16		2 30 w. G.	Aero Jewelry Mfg Co; Omaha. Neb.		
97°	98°	505°	18			Jostin		
410 1/2	127°	462 1/2	18		8 30 k.m.	"		
410 1/2	144°	445 1/2	16		7 55 k.m.	"		
537 1/2	99°	363 1/2	21			Pamphel Jewelry Co; Colorado Springs		
996 3/4			0			Hornestake		
770°	87°	543°	18		5 30 w. G.	John Roberts Mfg.		
750°	4°	246°	16			Motorola		
977°	0°	23°	6			"		
899°	0°	101°	13		7 30 Lm.	"		
0°	885°	115°	0			Supt		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 920500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
11/26 11/26			McQ-4	McQ-4	Mut Cain	169-Mutilated Clad 25¢	3004
			McQ-2	McQ-2	"	23- " " 10¢	161
1/30			613	618	Scrap jewelry	Ind	2381.2
			614	619	✓	✓	811.99
			615	620	✓	✓	1052.11
			616	621	✓	✓	1049.20
			617	622	Try Powder	✓	158.63
			618	623	Acrap	✓	1080.26
			619	624	-	✓	679.59
			620	625	✓	✓	823.58
			621	626	✓	✓	213
			622	627	19 Bars	✓	140.01
1/31 1:30			623	628	Res P-Scrap	✓	18.11
			624	629	Scrap jewelry	✓	9.13
			625	630	Bars	S. Dakota	1933.56
			626	631	✓	✓	3000.09
			627	632	Scrap jewelry	Ind	25.32
			628	633	✓	✓	54.43
			C-48	C-48	Cain	2-5 Reso 2-10 "	066
2/3/67			629	634	Bars	S. Dak	5246.58
			630	635	Acrap jewelry	Ind	281
			631	636	✓	✓	665.94
			632	637	W Sweeps	✓	537.14
			633	638	Hop Sweeps	✓	38.30
			634	639	Scrap jewelry	✓	18.26
			635	640	Scrap Sweeps	✓	344.87
2/3/67			636	641	Scrap	"	16.88
2/8/67 2PM			637	642	Bars	S. Dak	2145.44
			638	643	✓	✓	3859.63
			639	644	filings	Ind	63.88

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
						\$	\$	\$	\$
							Supt.		
							"		
✓ 442°	152°	434°	16				J. R. Sharpe & Co.		
✓ 400°	106°	494°	18				Josten		
✓ 396°	43°	521°	21				"		
✓ 396°	107°	497°	18				"		
✓ 395½	131°	473½	18			6 80 w.m.	"		
✓ 417°	61°	522°	18				"		
✓ 404½	101°	494½	18				"		
✓ 378°	126°	496°	18				"		
✓ 504°	146°	350°	18				George H. Pouch; Denver		
✓ 504°	177°	319°	18				S. Co. Texas Precious Metals.		
✓ 493°	0°	7°	6				Motorola		
✓ 495°	88°	417°	16				Bill Haws Jewelry; Denver		
✓ 496¼			0				Hornestake		
✓ 498½			0				"		
✓ 521½	57°	421½	21				Pauell's Jewelry; Houston		
✓ 536°	86°	378°	21				King Bros; Dallas		
✓ 900°	0°	100°	0				Sara Paulas; Colton, Calif.		
✓ 9966			0				Hornestake		
✓ 566°	210°	224°	16				Louis Werner; Denver		
✓ 402°	124°	474°	18				Josten		
✓ 423°	118°	459°	18			8 30 w.m.	"		
✓ 464½	93°	452½	18			2 30 w.m.	Star Jewelry Co.; Houston		
✓ 550½	57°	392½	21				Charlie B. Scott; Austin		
✓ 398°	155°	447°	16			5 30 w.m.	King Specialty Co.; Minn., Minn.		
✓ 544½	62°	393½	21				Blake Jewelry Co. - Denver		
✓ 996½			0				Hornestake		
✓ 997½			0				"		
✓ 400°	342°	358°	16			2 30 w.m.	S. Co. S & Ref Co.		

REGISTER OF ASSAYS,

DATE		NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay		
2/8/67	2 Pm		640	645	Scrap Ind.	314.66
			641	646	Scrap "	348.99
			642	647	Beads "	696.20
			643	648	Ret Colo-Jeff	8.27
			7	7	Grain's Bar Reports Jan Paris ^{Inc.} P-41-P-45	26.67
2/9/67	1:30 Pm		644	649	Scrap Jewelry Ind	97.2
			645	650	- - -	19.20
			646	651	Ret Colo-Adams	24.32
			647	652	Scrap Jewelry Ind.	1046.67
			648	653	✓ ✓ ✓	1039.42
			649	654	✓ ✓ ✓	1097.15
			650	655	Wet Snaps ✓	526.58
			651	656	Scrap Jewelry ✓	848.24
			652	657	✓ ✓ ✓	668.29
2/10	10:30		653	658	✓ ✓	47.12
			654	659	Bars S. Oak	4055.10
			655	660	Scrap Ind	112.88
			656	661	✓ ✓	81.88
			657	662	✓ ✓	45.15
			658	663	✓ Jewelry ✓	50.00
			659	664	✓ ✓ ✓	36.65
			660	665	✓ ✓	68.76
			661	666	✓ ✓ ✓	1378.35
			662	667	✓ ✓ ✓	30.84
			10	10	S.B. "15" Grain's #7 Crucible Rec. etc.	40.17
2/13	2 Pm		663	668	Scrap Rental Ind	6.76
			664	669	Retort Colo-Adams	73.7
			665	670	Scrap Ind	190.66
			666	671	Grain's Bl. Sand Alaska	191.85
2/15			667	672	Bars S. Oak	33.51
						2153.88

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 576 ¹ / ₂	88 ¹⁰ / ₁₀₀	335 ¹ / ₂	18			\$	\$ A.W. & Ref. Co.		\$
✓ 724 ¹ / ₂	71 ⁰ / ₁₀₀	268 ¹ / ₂	18				Motorola		
✓ 929 ¹⁰ / ₁₀₀	41 ⁰ / ₁₀₀	671 ⁰ / ₁₀₀	13				"		
✓ 872 ¹⁰ / ₁₀₀	103 ¹⁰ / ₁₀₀	251 ⁰ / ₁₀₀	12				Kerkling & Fleusker		
✓ 563 ¹ / ₂	167 ¹⁰ / ₁₀₀	279 ¹ / ₂	0				Lupit		
✓ 532 ¹ / ₂	204 ⁰ / ₁₀₀	263 ¹ / ₂	18				Petersen jewelry: Boulder		
✓ 430 ¹ / ₂	175 ¹⁰ / ₁₀₀	394 ¹ / ₂	16		2 ³⁰ / ₁₀₀ h.m.		Robt J. Stokes: Boulder.		
✓ 873 ¹⁰ / ₁₀₀	124 ¹⁰ / ₁₀₀	310 ⁰ / ₁₀₀	12				Kerkling & Fleusker		
✓ 396 ¹ / ₂	108 ¹⁰ / ₁₀₀	495 ¹ / ₂	18				Josten		
✓ 280 ¹⁰ / ₁₀₀	121 ¹⁰ / ₁₀₀	499 ¹⁰ / ₁₀₀	18				"		
✓ 425 ¹⁰ / ₁₀₀	123 ¹⁰ / ₁₀₀	452 ¹⁰ / ₁₀₀	18				"		
✓ 426 ¹⁰ / ₁₀₀	117 ¹⁰ / ₁₀₀	457 ¹⁰ / ₁₀₀	18		9 ⁰⁵ / ₁₀₀ h.m.		"		
✓ 389 ¹ / ₂	104 ¹⁰ / ₁₀₀	506 ¹ / ₂	18				"		
✓ 392 ¹ / ₂	81 ¹⁰ / ₁₀₀	526 ¹ / ₂	18				"		
✓ 554 ¹⁰ / ₁₀₀	121 ¹⁰ / ₁₀₀	325 ¹⁰ / ₁₀₀	18				Alvener jewelry Co.		
✓ 497 ¹ / ₄			0				Harnestake		
✓ 907 ¹⁰ / ₁₀₀	15 ¹⁰ / ₁₀₀	781 ¹⁰ / ₁₀₀	13		3 ⁰⁵ / ₁₀₀ h.m.		Motorola.		
✓ 986 ¹⁰ / ₁₀₀	3 ¹⁰ / ₁₀₀	11 ¹⁰ / ₁₀₀	6				"		
✓ 991 ¹ / ₂	2 ¹⁰ / ₁₀₀	6 ¹ / ₂	6				"		
✓ 538 ¹⁰ / ₁₀₀	86 ¹⁰ / ₁₀₀	376 ¹⁰ / ₁₀₀	21				Louis W. Spiegel; Congo Park, Calif.		
✓ 618 ¹ / ₂	52 ¹⁰ / ₁₀₀	325 ¹ / ₂	18				Harry E. Rogers; Denver		
✓ 407 ¹ / ₂	723 ¹⁰ / ₁₀₀	369 ¹ / ₂	16		2 ³⁰ / ₁₀₀ h.m.		Molberg's Gold Place; Denver		
✓ 379 ¹ / ₂	116 ¹⁰ / ₁₀₀	504 ¹ / ₂	18				Josten		
✓ 426 ¹ / ₂	111 ¹⁰ / ₁₀₀	462 ¹ / ₂	18				Ray Smith; Buena Park, Calif.		
✓ 457 ¹⁰ / ₁₀₀	118 ¹⁰ / ₁₀₀	425 ¹⁰ / ₁₀₀	0		2 ³⁰ / ₁₀₀ h.m.		Lupit		
✓ 698 ¹⁰ / ₁₀₀	128 ¹⁰ / ₁₀₀	174 ¹⁰ / ₁₀₀	16				Vivienne Barnett; Denver		
✓ 834 ¹⁰ / ₁₀₀	101 ¹⁰ / ₁₀₀	65 ¹⁰ / ₁₀₀	13		2 ³⁰ / ₁₀₀ h.m.		Kerkling & Fleusker		
✓ 522 ¹⁰ / ₁₀₀	88 ¹⁰ / ₁₀₀	390 ¹⁰ / ₁₀₀	21				S.W. Texas Prec. Metals.		
✓ 844 ¹⁰ / ₁₀₀	147 ¹⁰ / ₁₀₀	9 ¹⁰ / ₁₀₀	12				Estel Anderson, Spokane, Wash.		
✓ 997 ¹ / ₄			0				Harnestake		

REGISTER OF ASSAYS,

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
2/15			668	673	Bars	S. Dakota	189870
			669	674	Wire	Ind	1125
			670	675	4 Bars	"	28806
			671	676	Scrap Jewelry	"	1908
			672	677	✓	"	10059
			673	678	^{met} Sweeps	"	39301
			674	679	Scrap Jewelry	"	69843
			675	680	Sweeps	"	23869
Febr. 16			676	681	Sweeps	"	6307
			677	682	Bars	S. Dak	511435
			678	683	Scrap Jewelry	"	7407
			679	684	Ret	Colo Adams	9129
			680	685	Scrap Jewelry	"	93051
			681	686	✓	✓	124787
2/20			682	687	✓	✓	570
			683	688	Ret	Idaho - Boise	2051
			684	689	Scrap Metal	"	1507
			685	690	✓	Jewelry	275
			C-49	C-49	Coin	1-5 Peso	012
			C-50	C-50	"	1-50 Sole Peruvian	074
			C-51	C-51	"	1-Turkish Medallion	115
			C-52	C-52	"	2-2 1/2 Peso Mex	012
			C-53	C-53	"	1-50 Peso Mex	133
2/23			686	691	Scrap	Ind	382
			687	692	Bars	S. Dak	145083
			688	693	"	"	582953
			689	694	2 Bars 4 chips	Ind	Re- 37474 37477
			690	695	Scrap	"	29883
			691	696	Scrap	"	1586
			692	697	✓	"	Re 46292 46335

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
998 ¹⁰				0		\$	\$		\$
914 ¹²	80 ¹⁰	5 ¹²	12				Hornestake		
517 ¹⁰	180 ¹⁰	303 ¹⁰	18				Wm. Finsworth & Sons. Denver		
495 ¹²	97 ¹⁰	407 ¹²	16				W.A. Sheaffer Pen Co. Fort Moh, Minn.		
433 ¹⁰	73 ¹⁰	494 ¹⁰	18				Massey L. Kiker; Aurora, Colo.		
417 ¹²	118 ¹⁰	464 ¹²	18			6 ⁸⁰ M.	Genard Jewelers; St. Paul, Minn.		
422 ¹⁰	120 ¹⁰	458 ¹⁰	18				Joesten		
390 ¹²	98 ¹⁰	511 ¹²	18			4 ⁵⁰ M.	John Roberts Saff Co.		
364 ¹²	55 ¹⁰	580 ¹²	21			4 ⁵⁰ M.	" " " "		
997.5			0				Hornestake		
646 ¹⁰	65 ¹⁰	389 ¹⁰	21				Gordon Erickson Co. Minn.		
878 ¹²	114 ¹⁰	7 ¹²	12				Corley Grand Co.		
414 ¹²	158 ¹⁰	427 ¹²	16				Joesten		
375 ¹⁰	106 ¹⁰	599 ¹⁰	18				"		
470 ¹²	73 ¹⁰	456 ¹²	18				Hansen & Hansen; Denver		
764 ¹⁰	22 ¹⁰	10 ¹⁰	12				A.W. Josue; Garden Valley, Idaho		
622 ¹²	265 ¹⁰	112 ¹²	13			2 ⁸⁰ M.	University Park Hotel; Denver.		
547 ¹⁰	131 ¹⁰	322 ¹⁰	18				R.B. Bramblette; Denver		
900 ¹⁰	0 ¹⁰	100 ¹⁰	0				Blanche J. Richards; Port Arthur, Tex.		
900 ¹⁰	0 ¹⁰	100 ¹⁰	0				Philip H. Rastoff; Englewood, Colo.		
916 ¹²	0 ¹⁰	83 ¹²	0				Bedia M. Rodali; Hornetau, Tex.		
900 ¹⁰	0 ¹⁰	100 ¹⁰	0				George C. Stephens; "		
900 ¹⁰	0 ¹⁰	100 ¹⁰	0				Stephan J. Kauffman; West Hartford, Conn.		
439 ¹⁰	82 ¹⁰	479 ¹⁰	18				W.L. Warner; Salina, Kans.		
997 ¹⁰			0				Hornestake		
998.6			0				"		
989 ¹²	4 ¹⁰	6 ¹²	6				Pueblo Army Depot		
400 ¹²	90 ¹⁰	509 ¹²	18			5 ⁸⁰ M.	John Roberts Saff Co.		
943 ¹⁰	0 ¹⁰	57 ¹⁰	13				Hornetau		
921 ¹²	3 ¹⁰	75 ¹²	13				"		

REGISTER OF ASSAYS,

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
7/28 3:15 Pm.			693	698	Black Powder met	Ind	6 00
2/23			694	699	Sweeps	Ind	454.38
			695	700	Scrap	"	779.84
			696	701	✓ Jewelry	"	442.58
			697	702	met Sweeps	"	478.41
			698	703	Scrap Jewelry	"	581.74
			699	704	✓	"	966.06
			700	705	✓	"	1 217.24
			701	706	✓	"	1 034.79
			702	707	✓	"	857.96
7/28 3:15			703	708	Bars S. Blak		6 607.81
			704	709	✓	✓	278.47
			705	710	Ref Scales - assay		642.57
			706	711	mut. Can	Mutilated Can	943.07
			707	712	Scrap Jewelry		638.5
Director's letter 9/17/67	New Number 217	Rejoice	708	713	✓	Ind	3.11
			709	714	Filings	"	3.50
			710	715	Scrap Jewelry	"	146.13
			711	716	✓	"	1757.72
			712	717	✓	"	590.36
			713	718	Bars S. Blak		2073.66
			714	719	✓	✓	3801.94
			715	720	Ref Scrap	Ind	62.12
			716	721	✓	"	287.94
2/2			717	722	✓ Jewelry	"	10.93
			718	723	✓ Mental	"	10.56
			719	724	✓ Jewelry	"	122.14
			720	725	✓	"	248.15
			721	726	✓	"	608.45
			722	727	Wet Sweeps	"	418.74

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
791 1/2	88 1/2	120 1/2	13			2 30 h.m.	\$ Motorola		\$
415 1/2	114 1/2	471 1/2	18			7 55 h.m.	Jostens		
397 1/2	134 1/2	469 1/2	18				"		
398 1/2	109 1/2	493 1/2	18				"		
420 1/2	112 1/2	468 1/2	18			8 30 h.m.	"		
399 1/2	104 1/2	497 1/2	18				"		
414 1/2	115 1/2	470 1/2	18				"		
397 1/2	96 1/2	506 1/2	18				"		
372 1/2	77 1/2	550 1/2	21				"		
387 1/2	129 1/2	484 1/2	18				"		
997.8			0				Homestake		
516 1/2	91 1/2	353 1/2	21				L.W. Smeat & Ref		
458 1/2	159 1/2	383 1/2	16				Idorado		
-	825 1/2	175 1/2	0				Sept		
400 1/2	101 1/2	498 1/2	18				Meyers Loan & Jewelry Co. Houston		
72 1/2	12 1/2	916 1/2	0			Preliminary Assay	Florence Adams: Pasadena		
451 1/2	409 1/2	140 1/2	7			2 30 h.m.	Advanced Mental Lab: Newer		
410 1/2	233 1/2	356 1/2	16				R.A. Thomason: Wichita Falls		
391 1/2	110 1/2	498 1/2	18				Jostens		
400 1/2	108 1/2	491 1/2	18				"		
997 1/2			0				Homestake		
998 1/4			0				"		
998 1/2	0 1/2	2 1/2	0				Motorola		
817 1/2	2 1/2	180 1/2	16				"		
576 1/2	92 1/2	331 1/2	18			2 30 h.m.	Baron Jewelers; Billings, Mont.		
699	142 1/2	159	16			2 30 h.m.	Mr. Richard Hall; Albuquerque.		
507	88 1/2	405	21				Frager's Jewelers Inc, Wichita Falls, Tex		
449 1/2	125 1/2	425 1/2	16				Ed. Sharpe: Alachua, Fla.		
380 1/2	114 1/2	505 1/2	18				Jostens		
420 1/2	112 1/2	467 1/2	18			6 30 h.m.	"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 230500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received 1967	Reported	Hour	Receipt	Assay			
3/4			723	728	Scrap	Jewelry Ind	796.90
✓	1:35		724	729	Bars	S. Oak	546.29
			725	730	³¹⁹⁵ Swaps	Ind	336.48
			726	731	✓	✓	118.36
			727	732	✓	✓	607.5
			728	733	2ling's	✓	24.99
			729	734	Scrap	✓	228.78
			730	735	^{PL} Scrap	✓	734.74
			731	736	Scrap	Alental ✓	6.88
			C-54	C-54	Coin	2-5 Peso Mex	0.26
3/6	2:15 PM		732	737	Scrap	Alental Ind	4.24
			733	738	^{with} Swaps	"	404.76
			734	739	Scrap	Jewelry "	485.21
		L.B.	8	8	Gr. Bars	Gr. Bar - Deposits Fed. Coin	20.36
		S.B.	11	11	S.B.	3rd 1/4 Chip Swire - HM.R	15.17
3/8	3:30		735	740	Bars	S. Oak	2808.59
			736	741	"	" "	3413.85
			737	742	Scrap	Jewelry Ind	503.49
			738	743	✓	✓	535.11
			739	744	1-Bar		33.90
			740	745	Scrap	Ind	60.87
			741	746	✓	✓	93.99
			742	747	^{Wet} Swaps	✓	1274.50
			743	748	Scrap	Jewelry ✓	1190.45
		S.B.	12	12	S.B.	"15" Gramin #8	49.84
3/10	2 PM		744	749	Bars	S. Oak	5511.58
			745	750	Ret	Colo - Jeff	11.83
			746	751	✓	✓ Adams	160.2
			747	752	Scrap	Ind	157.22
			748	753	✓	Jewelry "	430.82

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
407 $\frac{1}{2}$	103 $^{\circ}$	489 $\frac{1}{2}$	18			\$	\$	\$	\$
9977			0				Josten		
405 $^{\circ}$	91 $^{\circ}$	504 $^{\circ}$	18			5 30 h.m.	Hamestake		
453 $^{\circ}$	156 $^{\circ}$	391 $^{\circ}$	16			3 45 h.m.	John Roberts Mfg.		
506 $^{\circ}$	100 $^{\circ}$	394 $^{\circ}$	21			2 30 h.m.	S.W. Texas Prec. Metals		
430 $\frac{1}{2}$	41 $^{\circ}$	528 $\frac{1}{2}$	18				S.W. S. Ref. Co.		
531 $^{\circ}$	88 $^{\circ}$	381 $^{\circ}$	21				✓ ✓ ✓ ✓		
944 $\frac{1}{2}$	2 $^{\circ}$	53 $\frac{1}{2}$	13				Motorola		
706 $^{\circ}$	128 $^{\circ}$	166 $^{\circ}$	16				Glenn M. Barrett, Alameda		
900 $^{\circ}$	0 $^{\circ}$	100 $^{\circ}$	0				Mrs. Frances L. McHester, N.Y., N.Y.		
747 $^{\circ}$	139 $^{\circ}$	114 $^{\circ}$	13				Tr. James S. McIntyre; Golden		
415 $^{\circ}$	123 $^{\circ}$	462 $^{\circ}$	18			7 15 h.m.	Josten		
395 $\frac{1}{2}$	109 $^{\circ}$	495 $\frac{1}{2}$	18				✓		
634 $\frac{1}{2}$	120 $^{\circ}$	245 $\frac{1}{2}$	0				Supt		
417 $\frac{1}{2}$	128 $^{\circ}$	454 $\frac{1}{2}$	0				Supt		
998 $\frac{1}{4}$			0				Hamestake		
998 $\frac{1}{2}$			0				"		
400 $^{\circ}$	107 $^{\circ}$	493 $^{\circ}$	18				Josten		
348 $\frac{1}{2}$	162 $^{\circ}$	489 $\frac{1}{2}$	18				"		
703 $^{\circ}$	170 $^{\circ}$	127 $^{\circ}$	13				Centrade B. Hills; Alameda		
360 $^{\circ}$	64 $^{\circ}$	576 $^{\circ}$	21				Senecor & Senecor; Waco, Tex		
524 $\frac{1}{2}$	93 $^{\circ}$	382 $\frac{1}{2}$	21				Louis W. Spiegel; Buena Vista, Calif.		
399 $^{\circ}$	118 $^{\circ}$	483 $^{\circ}$	18			15 30 h.m.	Josten		
384 $\frac{1}{2}$	113 $^{\circ}$	502 $\frac{1}{2}$	18				1		
491 $\frac{1}{2}$	99 $^{\circ}$	409 $\frac{1}{2}$	0				Supt		
9975			0				Hamestake		
808 $^{\circ}$	146 $^{\circ}$	46 $^{\circ}$	12				Kerklung & Alameda		
872 $^{\circ}$	125 $^{\circ}$	3 $^{\circ}$	12				"		
545 $\frac{1}{2}$	89 $^{\circ}$	365 $\frac{1}{2}$	21				S.W. Texas Precious Metals		
400 $\frac{1}{2}$	110 $^{\circ}$	489 $\frac{1}{2}$	18				Josten		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 1935500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
3/10			749	754	Scrap	Jewelry Ind	911.90
3/15	1147M.	P.M. R 3/7	C-55	C-55	Coin	1-20 Peso Mex.	0.53
			C-56	C-56	"	1-10 Peso Mex.	0.26
			C-57	C-57	"	2-50 Peso Mex.	2.67
			750	755	Filings	Ind.	26.39
			751	756	Scrap	"	23.63
			752	757	Scrap	"	400.24
			753	758	Scrap	"	486.62
			754	759	"	"	1648.39
			755	760	Bars	S. Alakuta	1405.58
			756	761	"	"	1750.29
3/16	W.M. Rutter	4/5/67	757	762	PI Scrap	Ind	33.66
			758	763	Scrap	Ind	363.64
			759	764	"	"	258.86
			760	765	"	"	640.95
			761	766	"	"	790.62
3/16			762	767	Bars	S. Alakuta	6248.54
			763	768	PI Scrap	Ind	862.86
			764	769	✓	✓	751.53
			765	770	✓	✓	95.61
			766	771	✓	✓	31.01
			767	772	✓	✓	339.31
3/21			768	773	Ret	Calo-Jeff	12.51
			769	774	Bars	S. Alakuta	1470.14
			770	775	✓	✓	5520.75
			771	776	Scrap	Jewelry Ind	11.95
			772	777	✓	"	143.84
			773	778	Casting Filings	"	235.41
			774	779	Scrap	Jewelry	42.86
3/23			775	780	Bars	S. Alakuta	5366.04

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
412 ¹⁰	114 ¹⁰	474 ¹⁰		18		\$	\$	\$	\$
900 ¹⁰	0 ¹⁰	100 ¹⁰		13			Jostens		
900 ¹⁰	0 ¹⁰	100 ¹⁰		13			Charles K. Bull; Bartlesville, Okla.		
900 ¹⁰	0 ¹⁰	100 ¹⁰		13			James H. Murphy; Muskogee, Okla.		
423 ^{1/2}	215 ¹⁰	361 ^{1/2}		16	2 ³⁰ h.m.		Jerome Smith, Dallas, Tex		
520 ¹⁰	64 ¹⁰	416 ¹⁰		21			Albuquerque funders service		
417 ^{1/2}	119 ¹⁰	463 ^{1/2}		18	6 ³⁰ h.m.		Spreckman & Co., Inc. Chicago, Ill		
398 ¹⁰	93 ¹⁰	509 ¹⁰		18			Jostens		
400 ^{1/2}	112 ¹⁰	487 ^{1/2}		18			"		
997 ^{1/2}				0			Harnestake		
999 ¹⁰				0			"		
97 ¹⁰	880 ¹⁰	23 ¹⁰		4	2 ³⁰ h.m.		Motorola		
468 ¹⁰	100 ¹⁰	492 ¹⁰		18	6 ⁰⁵ h.m.		John Roberts Mfg Co. Norman, Okla.		
560 ¹⁰	85 ¹⁰	355 ¹⁰		21			S. West & Ref Co.		
398 ¹⁰	101 ¹⁰	501 ¹⁰		18			Jostens		
400 ^{1/2}	66 ¹⁰	533 ^{1/2}		18			"		
997 ⁷				0			Harnestake		
997 ^{1/2}	0 ¹⁰	2 ^{1/2}		0			Motorola		
887 ^{1/2}	1 ¹⁰	111 ^{1/2}		13			"		
855 ¹⁰	1 ¹⁰	144 ¹⁰		13	3 ⁰⁵ h.m.		"		
969 ¹⁰	19 ¹⁰	12 ¹⁰		6			"		
547 ¹⁰	7 ¹⁰	446 ¹⁰		21	6 ⁰⁵ h.m.		"		
871 ^{1/2}	124 ¹⁰	4 ^{1/2}		12			Robt B. Ray		
996 ^{3/4}				0			Harnestake		
998 ⁰				0			"		
571 ^{1/2}	97 ¹⁰	331 ^{1/2}		18	2 ³⁰ h.m.		Salase funders; Albuquer		
579 ¹⁰	123 ¹⁰	358 ¹⁰		21			S. W. Texas Precious Metals.		
445 ¹⁰	124 ¹⁰	431 ¹⁰		16			J. L. Thorpe; Muskogee, Okla.		
514 ¹⁰	86 ¹⁰	400 ¹⁰		21			Burger & Co; Houston, Tex		
997 ⁶				0			Harnestake		

REGISTER OF ASSAYS, 102

U. S. GOVERNMENT PRINTING OFFICE 906500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
3/23			776	781	Scrap	Ind	323.22
			777	782	Scrap	"	49.11
			778	783	✓	"	134.18
			779	784	✓		203.86
			780	785	Reg	"	198.08
			781	786	Hgs Swaps	"	105.97
3/27			782	787	Mut Coin	Mutilated Coin	303.04
3/28	Remelt		783	788	Scrap	Ind	42.63
			784	789	Swaps	"	571.12
			785	790	Scrap	"	823.74
			786	791	✓	"	874.09
			787	792	✓	"	1048.24
			788	793	✓	"	43.49
			789	794	✓	"	5.27
			790	795	Refert	Calo-Duray	501.56
			791	796	Emb	Ind	1087.16
	W.M.		C-58	C-58	Emb.	1-Winston Churchill	0.10
	3/21/67		C-59	C-59	Pain	1-Queen Elizabeth II	0.25
			C-60	C-60	"	1-10 Pesos	0.11
			C-61	C-61	"	1-20 " "	2.39
			C-62	C-62	"	1-50 " "	0.05
						1-20 " "	1.87
3/29			792	797	Bars	S. Duck	2780.21
✓			793	798	✓	✓	2942.29
3/28			794	799	Bars.	Nevado-Cunka	5253.57
			795	800	✓	✓	5143.31
			796	801	Scrap	Ind	1020.48
			797	802	✓	"	1054.85
			798	803	✓	"	227.51
3/29			799	804	Scrap	"	296.31
			800	805	✓	"	864.03

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 400 ¹⁰	95 ¹⁰	505 ¹⁰	18			5.30 p.m.	John Roberts mfg.	\$	
✓ 989 ¹⁰	0 ¹⁰	11 ¹⁰	6				Motorsola		
✓ 916 ^{1/2}	18 ¹⁰	65 ^{1/2}	13			3 ²⁵ h.m.	✓		
✓ 960 ^{1/2}	1 ¹⁰	38 ^{1/2}	6				✓		
✓ 551 ¹⁰	84 ¹⁰	365 ¹⁰	21				S.W.S & Ref. Co.		
✓ 443 ¹⁰	166 ¹⁰	391 ¹⁰	16			3 ²⁵ h.m.	S.W.S & Ref. Co.		
✓ 0 ¹⁰	870 ^{1/4}	129 ^{3/4}	0				Sup'r		
✓ 170 ¹⁰	74 ¹⁰	156 ¹⁰	23			2 ³⁰ w.6.	Rocky Mtn. Clock & Repair; Elmer		
✓ 417 ^{1/2}	117 ¹⁰	465 ^{1/2}	18			8 ³⁰ h.m.	Joatun		
✓ 403 ^{1/2}	77 ¹⁰	519 ^{1/2}	18				"		
✓ 412 ¹⁰	139 ¹⁰	449 ¹⁰	16				"		
✓ 409 ¹⁰	87 ¹⁰	504 ¹⁰	18				"		
✓ 467 ^{1/2}	89 ¹⁰	443 ^{1/2}	16				Louis Spiegel; Pomona Park, Calif.		
✓ 429 ¹⁰	179 ¹⁰	392 ¹⁰	16				R.F. Patterson; Shawnee Mission, Kans.		
✓ 460 ^{1/2}	168 ¹⁰	371 ^{1/2}	16				Idaada		
✓ 429 ^{1/2}	72 ¹⁰	498 ^{1/2}	18				O.C. Tanner; Salt Lake		
✓ 900 ¹⁰	0 ¹⁰	100 ¹⁰	0				Mrs Hazel Shulay; Lubbock, Tex.		
✓ 916 ^{1/2}	0 ¹⁰	83 ^{3/4}	13				Maria Juana Ambroz; Los Angeles		
✓ 900 ¹⁰	0 ¹⁰	100 ¹⁰	13				Mr. Robert E. Eggers; Hermosa, Tex.		
✓ 900 ¹⁰	0 ¹⁰	100 ¹⁰	13				Rosa Maria Aguilera; Chicago		
✓ 900 ¹⁰	0 ¹⁰	100 ¹⁰	13				Mr. Warren J. Herman; Okla City, Okla.		
✓ 997 ^{3/4}			0				Homestake		
✓ 997 ^{3/4}			0				"		
✓ 945.1			0				Caslin Gold Mfg Co; Elko, Nevada		
✓ 945.3			0				" " " " " "		
✓ 371 ¹⁰	144 ¹⁰	485 ¹⁰	18				Joatun		
✓ 396 ¹⁰	105 ¹⁰	499 ¹⁰	18				"		
✓ 532 ¹⁰	75 ¹⁰	393 ¹⁰	21				S.W.S & Ref Co; Dallas		
✓ 381 ^{1/2}	122 ¹⁰	496 ^{1/2}	18				Joatun		
✓ 389 ^{1/2}	69 ¹⁰	541 ^{1/2}	18				"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 980500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received 1967	Reported	Hour	Receipt	Assay			
3/29			801	806	net sweeps	Ind	452.75
			805	807	Scrap	"	1193.69
			803	808	✓	"	1787.80
3/31			804	809	Bars	S. Dakota	665.59
			805	810	Scrap	Ind	383.68
			806	811	✓	✓	200.26
			807	812	✓	✓	37.75
			808	813	Ret	Calo - Adams	75.46
			809	814	Scrap	Ind	929.39
			810	815	✓	"	650.65
3/30		S.B.	13	13	S.B.	Clean up - Behind Fur	61.95
3/31			811	816	Bars	S. Dakota	2053.30
			812	817	"	" "	3516.90
4/3			813	818	Scrap	Ind	42.24
			814	819	Scrap	"	60.54
			815	820	Scrap	"	28.12
			816	821	Scrap	"	206.84
			817	822	"	"	9.80
			818	823	"	"	40.57
			819	824	"	Netal Ind	3.82
			820	825	Ret	Calo - Jeff	13.22
			821	826	Scrap	Jewelry Ind	820.62
			822	827	"	"	703.58
			823	828	"	"	682.79
			824	829	net sweeps	"	407.71
			825	830	Scrap	"	7.11
			826	831	"	"	19.02
		4B	9	9	For Bar	Travis - March C-54 55 C-56 57	20.01
4/6			827	832	Bars	S. Dakota	5622.25
			828	833	Scrap	Jewelry Ind	10.43

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 418°	117°	465°	18		75 ⁵ h.m.	\$	Joatun	\$	\$
✓ 396°	94°	510°	18			"	"		
✓ 391°	84°	525°	18			"	"		
497.5			0				Homestake		
✓ 388°	01°	62°	13				Snakesala		
✓ 498 1/2	01°	1 1/2	0				"		
✓ 481 1/2	01°	18 1/2	6				"		
✓ 86 1/2	116°	21 1/2	12				Cooley Sand & Gravel		
✓ 398°	124°	478°	18				Joatun		
✓ 403 1/2	102°	444 1/2	18				"		
✓ 464°	129°	407°	0				Supt.		
✓ 497 1/2			0				Homestake		
✓ 498 1/2			0				"		
✓ 454°	90°	456°	18		23 ³⁰ h.m.		Star Jewelry Co. Houston, Tex.		
✓ 515°	101°	384°	21				T.A. Sarumpa Co. Man. Mex.		
✓ 440°	139°	421°	16				S.R. Jewelers - Houston Tex.		
✓ 405 1/2	101°	493 1/2	18		53 ³⁰ h.m.		John Robert Mfg. Norman, Okla.		
✓ 552°	62°	386°	21				Charles B. Scott Austin, Tex		
✓ 431°	145°	424°	16				Tom Holleran Mfg. Co. Jeweler; Battle Creek Mich.		
✓ 704°	149°	147°	13		2 ³⁰ h.m.		Patrick S. Pooni, NDS; Alenver.		
✓ 853 1/2	143°	3 1/2	12		2 ³⁰ h.m.		Kerkling & Shucker		
✓ 394 1/2	119°	486 1/2	18				Joatun		
✓ 396°	109°	495°	18				"		
✓ 429°	115°	456°	18				"		
✓ 422°	112°	406°	18		7 ⁵⁵ h.m.		"		
✓ 438 1/2	95°	466 1/2	18				Samuel Schuman; Chicago, Ill.		
✓ 517 1/2	94°	388 1/2	21				Harry Goldblatt, Los Angeles.		
✓ 706°	74°	220°	0				Supt.		
✓ 497.4			0				Homestake		
✓ 484 1/2	105°	410 1/2	16				Lesley B. Black; Alenver.		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 230500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
4/6			829	834	Scrap	Ind	86 18
			830	835	—	"	239 09
			831	836	^{PI} Scrap	"	43 54
			832	837	"	"	378 93
			833	838	"	"	421 58
			834	839	"	"	11 12
			835	840	"	"	48 77
4/10			836	841	"	"	341 47
			837	842	"	"	7 97
			838	843	Ret	Calo-Alameda	32 69
			839	844	Scrap	Ind	624 30
			840	845	"	"	1021 59
			841	846	"	"	995 59
			842	847	"	"	592 26
4/12			843	848	"	"	25 40
			844	849	Bars S. Alaska		3834 09
			845	850	—	—	4343 46
			846	851	Swamp	Ind	191 99
			847	852	Scrap	"	192 84
			848	853	Powder Alaska	"	31 23
			849	854	Ret.	Alaska	126 99
			850	855	Scrap	"	176 79
			851	856	Bar	"	36 78
			852	857	Scrap	"	58 6
			853	858	S-Retorts	Idaho-Jerome	50 9
			854	859	Scrap	"	76 3
			855	860	with swamps	"	456 53
			856	861	Scrap	"	831 34
			857	862	—	"	677 10
			858	863	—	"	1031 34

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 88 1/2	119 1/2	392 1/2	16			\$	\$		\$
✓ 54 1/2	97 1/2	349 1/2	18				S.W. Pmelt & Ref Co.		
✓ 97 1/2	0 1/2	29 1/2	6				" " "		
✓ 84 1/2	7 1/2	144 1/2	13		5 30 h.m.		Motorola		
✓ 91 1/2	0 1/2	90 1/2	13				"		
✓ 51 1/2	41 1/2	439 1/2	21		2 30 h.m.		Lucien's Gold Jewellers: Denver		
✓ 53 1/2	118 1/2	328 1/2	18				Louis Spiegel; Buena Park, Calif.		
✓ 398 1/2	110 1/2	441 1/2	18				Joesten		
✓ 479 1/2	125 1/2	396 1/2	16				Lloyd Stanc Co; Denver		
✓ 884 1/2	112 1/2	3 1/2	12				Franking & Menaker		
✓ 393 1/2	119 1/2	487 1/2	18				Joesten		
✓ 387 1/2	104 1/2	508 1/2	18				"		
✓ 394 1/2	117 1/2	489 1/2	18				"		
✓ 410 1/2	116 1/2	473 1/2	18				"		
✓ 527 1/2	132 1/2	340 1/2	18				Atlas Loan & Jewelry; Buena Park, Calif.		
✓ 997 3/4			0				Sametake		
✓ 998 1/2			0				"		
✓ 418 1/2	129 1/2	453 1/2	18		4 15 h.m.		John Roberts Mfg Co.		
✓ 442 1/2	133 1/2	424 1/2	16				J. L. Thorpe		
✓ 446 1/2	830 1/2	24 1/2	4		2 30 h.m.		Motorola.		
✓ 881 1/2	112 1/2	7 1/2	12				Manuel Creek Mng. Via Aniak, Alaska		
✓ 531 1/2	98 1/2	370 1/2	21				S.W. Texas Precious Metals.		
✓ 331 1/2	179 1/2	490 1/2	18				Reichmanix Corp; Salt Lake City		
✓ 547 1/2	129 1/2	323 1/2	18				John Alby Co; Oakland, Calif.		
✓ 449 1/2	49 1/2	1 1/2	18				Thea Stewart, Berkeley, Idaho		
✓ 563 1/2	121 1/2	315 1/2	18				K. Otompalik; Missoula, Mo.		
✓ 422 1/2	116 1/2	461 1/2	18		7 15 h.m.		Joesten		
✓ 397 1/2	116 1/2	486 1/2	18				Joesten		
✓ 404 1/2	104 1/2	442 1/2	18				"		
✓ 396 1/2	106 1/2	448 1/2	18				"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
1967							
	N.M.R.					1-20 Pess	
	4/7/67		C-63	C-63	Pain	1-10 Billes (clutch) 30.74	
	P.M.R.					1-5 Pess	
	4/7/67		C-64	C-64	"	1-2 1/2 "	0.19
4/13		SB	14	14	S.B.	" 1/2 " Grains # 9 Cruc Res etc.	37.70
4/14			859	864	Scrap	End	14.47
			860	865	Bars	2 blk	270.01
			861	866	Ret	Calo-Adams	17.89
			862	867	"	" - Jeff	13.39
			863	868	re Scrap	End	135.10
			864	869	"	"	86.86
			865	870	"	"	67.73
			866	871	Scrap	"	11.45
			867	872	"	"	162.58
			868	873	"	"	539.52
			869	874	"	"	427.85
4/17			870	875	"	"	1041.92
			871	876	"	"	370.81
			872	877	"	"	488.83
			873	878	"	"	416.85
			874	879	"	"	440.50
			875	880	"	"	503.79
4/18			876	881	Bars	1. blk.	1707.66
			877	882	"	"	3786.98
			878	883	3-Bars	Nevada-Eureka	3726.71
			879	884	3-Bars	" "	4055.31
			880	885	Scrap	End	11.97
			881	886	with Snips	"	458.74
			882	887	Scrap	"	706.12
4/19			883	888	"	"	305
			884	889	Scrap Snips	"	729
			885	890	Scrap	"	1128

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 900 ⁰	0 ¹⁰	100 ¹⁰		13		\$	\$		\$
✓ 900 ⁰	0 ¹⁰	100 ¹⁰		13			Mrs George Mendell; Highland Park		Ill.
✓ 900 ⁰	0 ¹⁰	100 ¹⁰		13			Mr. John F. Lakase; Illinois, Ill.		
✓ 460 ^{1/2}	103 ¹⁰	436 ^{1/2}		0			Supt		
✓ 389 ¹⁰	156 ¹⁰	455 ¹⁰		18			Rio Grande Wholesale Jewellers; Albuq. N. Mex.		
✓ 997 ^{1/2}				0			Honestake		
✓ 880 ⁰	113 ¹⁰	71 ⁰		12	2 ³⁰ h.m.		Jensking & Shaker		
✓ 842 ^{1/2}	150 ¹⁰	7 ^{1/2}		12			"		
✓ 846 ^{1/2}	21 ¹⁰	132 ^{1/2}		13			Maharala		
✓ 974 ¹⁰	1 ⁰	25 ⁰		6			"		
✓ 987 ^{1/2}	4 ¹⁰	8 ^{1/2}		6			"		
✓ 476 ¹⁰	172 ¹⁰	402 ¹⁰		16			Jacobson Jewellers, Omaha, Neb.		
✓ 373 ^{1/2}	110 ¹⁰	576 ^{1/2}		18			Joeten		
✓ 397 ^{1/2}	111 ¹⁰	491 ^{1/2}		18			"		
✓ 398 ¹⁰	109 ¹⁰	493 ¹⁰		18			"		
✓ 405 ^{1/2}	161 ¹⁰	433 ^{1/2}		16			Joeten		
✓ 400 ¹⁰	109 ¹⁰	491 ¹⁰		18			"		
✓ 396 ¹⁰	109 ¹⁰	495 ¹⁰		18			"		
✓ 397 ^{1/2}	109 ¹⁰	493 ^{1/2}		18			"		
✓ 398 ¹⁰	106 ¹⁰	496 ¹⁰		18			"		
✓ 397 ^{1/2}	109 ¹⁰	493 ^{1/2}		18			"		
✓ 998 ¹⁰				0			Honestake		
✓ 998 ¹⁰				0			"		
✓ 993 ^{3/4}				6			Leachin Hall Mfg Co; Elko, Nev.		
✓ 992 ^{3/4}				6			"		
✓ 543 ¹⁰	59 ¹⁰	398 ¹⁰		21			Blake Jewelry Co; Denver		
✓ 409 ^{1/2}	118 ¹⁰	472 ^{1/2}		18	7 ⁵⁵ h.m.		Joeten		
✓ 398 ¹⁰	106 ¹⁰	496 ¹⁰		18			"		
✓ 635 ^{1/2}	136 ¹⁰	228 ^{1/2}		16			R. J. Storm; La Prairie, Kans.		
✓ 383 ^{1/2}	168 ¹⁰	448 ^{1/2}		16	2 ³⁰ h.m.		L. G. Christopherson, Pomeroy, Wash.		
✓ 513 ¹⁰	206 ¹⁰	281 ¹⁰		18	2 ³⁰ h.m.		Gregg Hunk Mfg Jewellers, Burlington, Iowa		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 1330000

DATE		NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay		
4/19			886	891	Scrap Central Ind	550
4/21			887	892	Bars S. Dakota.	5543.37
			888	893	Scrap Ind	43.32
			889	894	✓	257.49
			890	895	pl. Scrap	36.01
			891	896	✓	77.81
			892	897	✓	25.29
			893	898	✓	70.09
			894	899	✓	265.05
			895	900	Scrap	47.55
			896	901	✓	2.53
	4/17/67		C-65	C-65	Coin 1-50 Peso	187
			C-66	C-66	" 1-20 "	133
			C-67	C-67	U.S. Coin 1-100 H.D.	0.53
			C-68	C-68	Coin 1-50 Peso	133
			C-69	C-69	" 1-50 Peso	0.13
4/24			897	902	Scrap Ind	744.56
			898	903	✓	445.73
			899	904	✓	1049.88
			900	905	✓	1001.80
			901	906	✓	689.94
			902	907	Refers Idaho - Boise	23.37
			903	908	pl. Scrap Ind	82.27
			904	909	Scrap Ind	11.04
4/21			905	910	Bars S. Dakota	2227.10
			906	911	" " "	3733.69
4/25			907	912	Coin Mutilated Coin	1273.02
4/27			908	913	Scrap Ind	6.69
			909	914	✓	532.27
			910	915	✓	1012.54

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
605 1/2	280 10	114 1/2	13			\$	\$	\$	\$
997 6			0				Dr. D. V. Robinson, Oakland, Calif		
432 1/2	164 0	403 1/2	16			2 30 x L	Homestake		
552 1/2	99	348 1/2	18				Santomas 20 Ref. Co.		
983 10	0 10	17 10	6				"		
737 1/2	5	257 1/2	18			305 x L	Matarola		
989 10	0 10	11 10	6				"		
984 10	0 10	16 10	6				"		
998 10	0 10	2 10	0				"		
575 1/2	101	303 1/2	18				Louis A. Spiegel; Longue Port, Calif.		
550 1/2	64	385 1/2	21				Austin Jewelry; Albuq., N. Mex		
900 10	0 10	100 10	13				Mr. Frank J. Linsen; Menasha, Wis.		
900 10	0 10	100 10	13				Mrs. Lucille M. Hunt; Dallas, Tex		
900 10	0 10	100 10	0				Yuen Mang Wong; Bronx, N. Y.		
900 10	0 10	100 10	13				Miss Adeline M. Lee, N. Y., N. Y.		
900 10	0 10	100 10	13				Mr. Alan Kram; Lafayette, Ind		
404 1/2	112 0	483 1/2	18				Josten		
421 1/2	105 0	473 1/2	18				"		
395 1/2	60 0	544 1/2	18				"		
414 0	105 0	481 0	18				"		
390 0	64 0	546 0	18				"		
770 1/2	222 0	7 1/2	12				A. W. Jones; Garden Valley, Idaho		
960 0	0 0	40 0	6				Matarola		
532 0	101 0	367 0	21				John B. Weida, Jeweler, Idaho Falls, Id.		
997 3/4			0				Homestake		
997 3/4			0				"		
0 0	889 0	111 0	0				Sup't		
572 1/2	32 10	395 1/2	21				Charles B. Scott, Austin, Texas		
402 10	98 10	500 0	18				Josten		
400 1/2	109 10	490 1/2	18				"		

REGISTER OF ASSAYS, 103

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
4/27			911	916	Wet Sweeps	Ind	416 13
			912	917	1-Bar	"	35 48
			913	918	3/4's Sweeps	"	16 12
			914	919	Bars S. Hark		563237
			915	920	Pl. Scrap		22 10
			916	921	"	"	241 23
			917	922	"	"	37 71
			918	923	"	"	89 81
			919	924	3/4's Sweeps	"	344 03
4/28	Remelt		920	925	3/4's	"	36 48
			921	926	Scrap	"	39 48
			922	927	✓	"	218227
			923	928	✓	"	616 74
			924	929	✓	"	784 31
			925	930	Pl. Scrap	"	111398
			926	931	3/4's	"	778 08
5/2			927	932	Pl. Scrap	"	145 95
			928	933	Scrap	"	136 26
			929	934	Ret Colo - Duray	"	9 67
			930	935	Bars S. Hark		364 80
			931	936	" " "		1586 83
			932	937	containing 3/4's	Ind	3533 55
			933	938	Ret Colo - Adams		224 55
5/3			934	939	Scrap	Ind	11 94
			935	940	✓	"	4 10
			936	941	23-Bars	"	757 41
			937	942	Scrap	"	171 38
			938	943	✓	"	1051 22
			939	944	✓	"	664 47
			940	945	✓	"	667 84
							643 90

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 415°	131°	454°	18			\$ 6 ²⁵ / ₁₀₀ M.	\$ Jostin	\$	\$
✓ 999°	0°	1°	0				Matosala		
✓ 384 1/2	211°	404 1/2	16			2 ³⁰ / ₁₀₀ M.	Levin Schmitz; Denver		
✓ 997 3			0				Homestake		
✓ 998°	0°	22°	6				Matosala		
✓ 997°	0°	103°	13				"		
✓ 484 1/2	0°	15 1/2	6				"		
✓ 888 1/2	24°	87 1/2	13				"		
✓ 400 1/2	143°	456 1/2	18			6 ²⁵ / ₁₀₀ M.	John Roberts Mfg Co; Norman, Okla		
✓ 467 1/2	63°	464 1/2	18			2 ³⁰ / ₁₀₀ M.	Fachin Craft; Chicago, Ill.		
✓ 390 1/2	95°	514 1/2	18				Jostin		
✓ 397°	97°	506°	18				"		
✓ 402°	111°	487°	18				"		
✓ 407 1/2	118°	474 1/2	18				"		
✓ 973 1/2	0°	26 1/2	6				Texas Luit Inc. Dallas		
✓ 428°	83°	489°	18			3 ²⁵ / ₁₀₀ M.	Wilbur Coating Co; Buffalo, N.Y.		
✓ 994°	0°	61°	6				STI Corp; Petaluma, Calif.		
✓ 366°	227°	407°	16			2 ³⁰ / ₁₀₀ M.	Al. W. Hanson; Sioux City, Iowa		
✓ 399°	150°	451°	18				Idorado.		
✓ 997 1/4			0				Homestake		
✓ 997 3/4			0				"		
✓ 427 1/2	145°	427 1/2	16				J. L. Thorpe; Leadwood, S. W.		
✓ 891 1/2	96°	12 1/2	12			2 ³⁰ / ₁₀₀ M.	Geckling & Shuster		
✓ 553°	55°	392°	21				Anthony J. Kayk; Denver		
✓ 405°	120°	475°	18				Jostin		
✓ 455°	137°	408°	16				S. W. Texas Precious Metals.		
✓ 414 1/2	126°	459 1/2	18				Jostin		
✓ 375 1/2	165°	459 1/2	18				"		
✓ 397°	104°	499°	18				"		
✓ 252 1/2	121°	626 1/2	21				"		

REGISTER OF ASSAYS, 100

U. S. GOVERNMENT PRINTING OFFICE 530500

DATE 1967			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
5/3			941	946	Scrap	Ind	816.99
					pl. Bol		
			942	947	PP4		148.23
5/8			C-70	C-70	Gold	1-10 Peso	0.26
			C-71	C-71	-	1-20 Peso	0.52
			943	948	Scrap	Ind	52.54
			944	949	Ret	Idaho - Jerome	53.8
			945	950	"	Nevada	23.1
			946	951	Scrap	Ind	378.7
			947	952	"	"	415.79
			948	953	"	"	949.71
			949	954	Scrap	"	201.51
			950	955	"	"	22.27
			951	956	Ret	Calo - Jeff	19.17
			952	957	Scrap	Ind	866.08
			953	958	Scrap	"	1184.20
			954	959	Scrap	"	663.63
			955	960	"	"	764.02
			956	961	"	"	798.34
			957	962	Scrap	"	329.27
			958	963	Scrap	"	546.37
			959	964	"	"	687.12
	5/12	4 P.	10	10	Grain's Bar	MONTH April Poinc C-56 - C-69 Inc.	30.05
5/5			960	965	Scrap	Ind	19.96
			961	966	Bars	South Dakota	5638.66
			962	967	"	"	2043.98
			963	968	"	"	3903.47
	5/12		964	969	Ass. Sheet	Ind	156.3
5/8			965	970	Wet Sweeps	"	325.18
			966	971	Scrap	"	1072.36
			967	972	Sweeps	"	200.27

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
363 1/2	116 1/2	520 1/2	18			\$	\$		\$
0 1/2	948 1/2	2 1/2	12				Joesten		
900 1/2	0 1/2	100 1/2	13				Motarsala		
900 1/2	0 1/2	100 1/2	13				Mrs Joseph W. Mason; Grand Rapids, Mich.		
452 1/2	96 1/2	452 1/2	18				Mr. Charles McManis; Parrottton, Tex.		
951 1/2	47 1/2	1 1/2	6				Midtown Mfg. Machine, Inc. Salt Lake		
906 1/2	92 1/2	1 1/2	12			2 3/4 m.	Idea Stewart; Burley Idaho		
981 1/2	2 1/2	16 1/2	6				Edward J. Meets; Sparks, Nev.		
990 1/2	2 1/2	7 1/2	6				Motarsala		
845 1/2	2 1/2	103 1/2	13				"		
559 1/2	84 1/2	357 1/2	21				"		
515 1/2	99 1/2	385 1/2	21				S.W. S. Ref Co; Dallas		
844 1/2	144 1/2	12 1/2	12				Roberts Wholesale Dist. Inc. Phoenix		
397 1/2	102 1/2	501 1/2	18				Resolving & Shuster		
409 1/2	112 1/2	478 1/2	18			14 3/4 m.	Joesten		
390 1/2	119 1/2	490 1/2	18				"		
348 1/2	101 1/2	501 1/2	18				"		
397 1/2	100 1/2	503 1/2	18				"		
421 1/2	115 1/2	464 1/2	18			6 0 1/2 m.	"		
393 1/2	97 1/2	509 1/2	18				"		
403 1/2	101 1/2	496 1/2	18				"		
637 1/2	206 1/2	156 1/2	0				Supt		
502 1/2	105 1/2	393 1/2	21				Leslie D. Crampton Albuquerque N.M.		
997 1/2			0				Hornetthe		
997 3/4			0				"		
997 3/4			0				"		
999 1/2	0	1 1/2	0				N.B.S. Boulder - Au Exchange		
406 1/2	119 1/2	454 1/2	18			6 0 1/2 m.	Joesten		
405 1/2	105 1/2	490 1/2	18				"		
403 1/2	159 1/2	438 1/2	16			5 30 p.m.	John Roberts - Norman, Okla		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 230802

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
5/8			968	973	Scrap	Ind	92.05
	5/12		969	974	Scrap	"	17.54
		SB	15	15	S.B	Mag. mat's Remains from Dep	5.01
		SB	16	16	S.B	from: "K" Grains #10	35.47
			C-72	C-72	Coin	1- Caracas - Venezuelan	0.67
	5/12		C-73	C-73	"	1-50 Peso mex	1.33
			C-74	C-74	"	1-10 Peso 1-20 Peso 1-5 " 1-2 1/2 " mex	5.1
5/9			C-75	C-75	"	1-100 Corona - Austrian	1.08
			C-76	C-76	"	1-50 Peso mex	1.33
			C-77	C-77	"	1-50 Peso mex	1.33
			C-78	C-78	"	1-50 Peso 1-10 " mex 1-5 "	1.73
			C-79	C-79	"	1-50 Peso mex	0.13
			970	975	Bars	So Dakota	5703.08
			971	976	"	" "	843.25
			972	977	Scrap	Ind	226.85
			973	978	"	"	48.95
			974	979	"	"	355.41
5/11			975	980	"	"	65.94
			976	981	Emblems	"	461.17
			977	982	Retort	Jefferson	13.38
5/12			978	983	5 Bars	Nevada, Eureka	5535.17
	5/18		979	984	Scrap	Ind	46.46
			980	985	"	"	22.08
			981	986	"	"	662.15
			982	987	"	"	551.77
			983	988	"	"	827.24
			984	989	"	"	642.26
			985	990	"	"	505.76
			986	991	Bars	South Dakota	1937.41
			987	992	"	" "	2871.92

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 464 1/2	100 °	435 1/2		16		\$ 455.00	\$ John Roberts,		\$ Norman Okla
✓ 554 °	113 °	333 °		18			Roy River, Jewelry		Tulsa, Okla
✓ 578 °	59 °	363 °		0			Supt,		
✓ 429 1/2	115 °	455 1/2		0			"		
✓ 390 °	0 °	110 °							
✓ 900 °	0 °	100 °		13			Gualberto G. Pumaroso,		Salvadorias, Tex
✓ 900 °	0 °	100 °		13			James F. Waddick -		Ind. Ind.
✓ 900 °	0 °	100 °		13			Customs - Houston,		Tex
✓ 900 °	0 °	100 °		13			Karin F. Nelson,		Santa Barb. Cal
✓ 900 °	0 °	100 °		13			Esther Aotello,		Sterling, Ill
✓ 900 °	0 °	100 °		13			Virginia Kees,		mt Kisco, N. Y.
✓ 900 °	0 °	100 °		13			Edwin H. Vele,		Bremen, Indiana
✓ 900 °	0 °	100 °		13			John C. Squire,		Tranger, Ind.
✓ 997.1				0			Homestake		
✓ 997 1/2				0			"		
✓ 916 1/2	0 °	83 1/2		13 1/4			Motorola,		Phoenix, Ariz
✓ 974 1/2	0 °	25 1/2		6			"		"
✓ 847 1/2	16 °	136 1/2		13			"		"
✓ 547 1/2	122	330 1/2		18			Louis W. Spiegel,		Canoga Park, Cal
✓ 394 1/2	63	542 1/2		18			O. C. Tanner,		Salt Lake City, Utah
✓ 871 1/2	125	3 1/2		12			Robert B. Ray & Suburban Gold Co		Black Hawk, Colo
✓ 993 3/4				6			Carlin Gold Mining Co.		Elko, Nev.
✓ 578 1/2	59	362 1/2		21			Morris Jewelry Co.		Denver, Colo
✓ 521 1/2	73	405 1/2		21			Hubbard-Denn Jewellers,		Salt Lake City, Utah
✓ 400 °	108 °	492 °		18			Justini		
✓ 399 °	114 °	487 °		18			"		
✓ 398 °	93 °	509 °		18			"		
✓ 398 °	103 °	499 °		18			"		
✓ 398 1/2	120 °	481 1/2		18			"		
✓ 998 °				0			Homestake		
✓ 997 3/4				0			"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 1030000

DATE 1967			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
5/12	5/18		988	993	Plate Scrap	Ind	65 25
5/15			989	994	Wet Scrap	"	314 65
			990	995	Scrap	"	502 44
5/16	5/22		991	996	"	"	126 90
			992	997	Bars	South Dakota	6 224 31
			993	998	Plate Scrap	Ind	26 52
			994	999	"	"	44 21
			995	1000	"	"	249 14
	5/24		996	1001	"	"	178 89
			997	1002	Plate Scrap	"	65 37
			998	1003	Beards	"	1 083 47
			999	1004	Scrap	"	136 62
5/18	5/24		1000	1005	"	"	45 57
			1001	1006	Dent Scrap	"	6 82
	5/22		1002	1007	Bars	Eureka, Nev	4 366 28
5/19	5/24		1003	1008	Scrap	Ind	1 557 11
			1004	1009	"	"	1 049 33
			1005	1010	Wet Scrap	"	391 99
			1006	1011	Ag Coin	Mululated Silver Coin	156 27
			1007	1012	Bars	South Dakota	2 897 72
			1008	1013	"	"	3 170 14
			1009	1014	Scrap	Ind	5 23
			1010	1015	"	"	905 04
	5/25 <i>Remer</i>		1011	1016	"	"	73 07
			1012	1017	"	"	74 37
			1013	1018	Dent	"	146 53
5/22			1014	1019	Scrap	"	985
			1015	1020	"	"	55 52
			1016	1021	"	"	32 13
			1017	1022	Retort	Bair, Idaho	17 30
							25 96

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 996 °	0 °	4 °	0			\$	\$ Motorola	\$	\$ Phoenix Ariz
✓ 423 ½	117 °	459 ½	18			605 x lb	Jostens		
✓ 409 ½	103 °	487 ½	18				Jostens		
✓ 995 °	0 °	5 °	0				G.T.I. Corp.		Petaluma, Cal
✓ 997.7	0 °	0 °	0				Homestake		
✓ 928 °	3 °	69 °	13			305 x lb	Motorola -		Phoenix, Ariz
✓ 981 ½	0 °	18 ½	6				"	"	
✓ 808 °	0 °	192 °	16				"	"	
✓ 623 °	10 °	367 °	21			380 x lb	"	"	
✓ 955 ½	0 °	44 ½	6				Motorola,		Phoenix, Ariz
✓ 758 ½	7 °	234 ½	16			1355 x lb	"	"	
✓ 997 °	0 °	3 °	0				"	"	
✓ 514 ½	88 °	397 ½	21				Berger & Co,		Houston, Tex
✓ 758 °	127 °	115 °	13				Drs Nuckelisen & Whiteside,		Sioux City Iowa
✓ 995 ½	0 °		0				Carlin Gold Mining Company,		Elko Nev
✓ 404 ½	89 °	506 ½	18				Jostens		
✓ 393 °	120 °	487 °	18				"		
✓ 417 °	118 °	465 °	18			680 x lb	"		
✓ 0 °	870 ¾	129 ¼	0				Supt.		
✓ 991 ½			0				Homestake		
✓ 998 ¼			0				"		
✓ 549 ½	139 °	311 ½	18			230 x lb	Al-Car Jewellers - Denver,		Colo
✓ 409 °	138 °	453 °	18			530 x lb	John Roberts mfg -		Norman Okla
✓ 490 °	114 °	393 °	16			230 x lb	Dennis & Redford,		Salt Lake City, Utah
✓ 422 °	87 °	491 °	18			380 x lb	Wallace Casting Co.		Buffalo, NY
✓ 731 ½	120 °	148 ½	13			230 x lb	De Malters & Arthur H. Robbins,		Denver Colo
✓ 527 ½	93 °	379 ½	21				M.Y. Imkelman Co.		Chicago, Ill
✓ 549 ½	89	361 ½	21				Laron Bros -		Duluth - Minn
✓ 476 °	141 °	383	16				A. F. Jensen Co		Omaha, Neb
✓ 769 °	221 °	10 °	12				A.W. Josue -		Garden Valley, Idaho

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 230800

DATE 1967

NUMBER

MODE
OF
PAYMENT

DESCRIPTION

WEIGHT
AFTER
MELTING

Received

Reported

Hour

Receipt

Assay

5/22			1018	1023	Scrap	Ind	229.72
5/23			1019	1024	"	"	667.66
			1020	1025	Bars	South Dakota	557.55
	5/31		1021	1026	Scrap	Ind	151.22
			1022	1027	"	"	135.64
			1023	1028	"	"	28.97
			1024	1029	"	"	30.22
			1025	1030	"	"	182.26
5/24			1026	1031	"	"	927.30
			1027	1032	"	"	880.52
			1028	1033	"	"	32.32
5/25			1029	1034	nat Grains	Mont. Powell Co	13.03
			1030	1035	Scrap	Ind	8.78
			1031	1036	Bars	Ind	175.77
			1032	1037	Scrap	"	39.99
5/26			1033	1038	"	"	2.49
			1034	1039	"	"	712.77
			1035	1040	"	"	671.61
			1036	1041	"	"	875.14
			1037	1042	"	"	816.93
			1038	1043	"	"	909.62
			1039	1044	Retort	Colo - Duray	401.25
	6/2		1040	1045	Bars	South Dakota	1757.27
			1041	1046	"	"	3699.35
			1042	1047	Snaps	Ind	222.75
5/29			1043	1048	Wet Snaps	"	430.95
			1044	1049	Scrap	"	1426.15
6/1			SB 17	SB 17	SB	from C+D Mint #8 Abandoned Lots + 60 day Letters	26.49
6/5			1045	1050	Bars PI	S. Flek	6342.85
			1046	1051	Scrap	Ind	18.83

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 576 ⁰	92 ⁰	382 ⁰	21			\$	\$	\$	\$
✓ 409 ¹ / ₂	103 ⁰	487 ¹ / ₂	18				Southwest Texas P.M. San Antonio, Tex		
✓ 997.3			0				Istern		
✓ 615 ⁰	0 ⁰	385 ⁰	21				Hornestake		
✓ 997 ⁰			0				Matricula		
✓ 978 ⁰	0 ⁰	22 ⁰	6			2 ³⁰ x Lm	"		
✓ 862 ⁰	0 ⁰	138 ⁰	13				"		
✓ 505 ⁰	103 ⁰	392 ⁰	21				Southwest Texas S+R Dallas, Tex		
✓ 382 ¹ / ₂	110 ⁰	507 ¹ / ₂	18				Istern		
✓ 395 ¹ / ₂	103 ⁰	501 ¹ / ₂	18				"		
✓ 438 ¹ / ₂	157 ¹⁰	410 ¹ / ₂	16			2 ³⁰ x Lm			
✓ 915 ¹⁰	82 ¹⁰	3 ¹⁰	12				A. K. Scharf, Deer Lodge, Mont		
✓ 353 ¹⁰	87 ¹⁰	56 ¹⁰	21				Samuel Schmarin, Chicago, Ill		
✓ 463 ¹ / ₂	129 ¹⁰	407 ¹ / ₂	16				South West Texas P.M. San Antonio - Tex		
✓ 305 ⁰	206 ¹⁰	489 ¹⁰	18			2 ³⁰ x Lm	A. F. Jensen Mfg. Co., Omaha, Neb.		
✓ 757 ¹⁰	123 ¹⁰	126 ¹⁰	13				Dr. Nyrum Bergstrom, Salt Lake City		
✓ 397 ¹⁰	102 ¹⁰	501 ¹⁰	18				Istern		
✓ 407 ¹ / ₂	97 ¹⁰	495 ¹ / ₂	18				"		
✓ 377 ⁰	104 ¹⁰	579 ¹⁰	18				"		
✓ 338 ⁰	129 ¹⁰	533 ¹⁰	18				"		
✓ 382 ⁰	135 ¹⁰	483 ¹⁰	18				"		
✓ 430 ¹⁰	163 ¹⁰	407 ¹⁰	16				Idarado Mng Co, Durin, Colo		
✓ 997 ⁰			0				Hornestake		
✓ 998 ¹ / ₄			0				"		
✓ 414 ¹ / ₂	97 ¹⁰	488 ¹ / ₂	18			5 ³⁰ x Lm	John Roberts Mfg Co, Norman, Okla		
✓ 420 ¹⁰	112 ¹⁰	468 ⁰	18			7 ⁵⁵ x Lm	Istern		
✓ 391 ¹ / ₂	103 ⁰	505 ¹ / ₂	18				"		
✓ 90 ¹ / ₂	244 ¹⁰	565 ¹ / ₂	0				Supt		
✓ 997.9			0				Hornestake		
✓ 959 ¹⁰	0 ¹⁰	41 ¹⁰	6			2 ³⁰ x Lm	Matricula		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 980000

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
6/5			1047	1052	PI Scrap	Irrel.	587.56
			1048	1053	PI Beads	"	414.81
			1049	1054	PI Scrap	"	214.02
			1050	1055	Scrap Jewelry	"	21.61
			1051	1056	"	"	19.06
			1052	1057	"	"	58.70
			1053	1058	" Jewelry	"	849.57
			1054	1059	"	"	449.61
			1055	1060	"	"	611.93
			1056	1061	"	"	1008.45
			1057	1062	charcoal & Carbon	Re	36.27
6/6			1058	1063	Bars I. Nak		1119.05
			1059	1064	"		4938.33
			1060	1065	Scrap Jewelry		25.66
			1061	1066	"		1904.72
			1062	1067	Report Colo-Jeff		21.75
			1063	1068	"	"	215.28
			1065	1070	Bars Nevada Eureka		4301.07
6/7			1064	1069	Report Colo-Adams		21.74
			1066	1071	" Idaho-Jerome		5.04
			1067	1072	PI Scrap	Ind	12.76
			118	18	S.B. 4th Q. Philip H. M.R. - Newk		13.64
			11	11	S.B. North May: Pania to thru 79	Re	40.85
6/9			1068	1073	Bars S. Dakota		6694.38
			1069	1074	Sweep	Ind	149.72
			1070	1075	Report Colo-Adams		158.23
			19	19	S.B. Sweeps Pellar Met.		61.23
			20	20	S.B. "15" Grant's Bar #11		21.89
			1071	1076	Net Bars Colo. Boulder		38.91
			1072	1077	Scrap	Ind	695.61

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
940 ¹⁰	0 ¹⁰	60 ¹⁰		13		\$	\$		\$
662 ¹⁰	8 ¹⁰	330 ¹⁰		18		6 ⁸⁰ h.m.	Motarsla		
945 ¹⁰	2 ¹⁰	53 ¹⁰		13			"		
377 ¹⁰	172 ¹⁰	451 ¹⁰		18					
533 ¹⁰	147 ¹⁰	320 ¹⁰		18			Nebo Jewelry: Denver		
717 ¹⁰	104 ¹⁰	179 ¹⁰		16		2 ³⁰ h.m.	Jacobson Jewelry: Omaha		
396 ¹⁰	99 ¹⁰	504 ¹⁰		18			Louis W. Spiegel; Ponaga Park, Calif		
407 ¹⁰	120 ¹⁰	472 ¹⁰		18			Josten		
398 ¹⁰	109 ¹⁰	493 ¹⁰		18			"		
376 ¹⁰	120 ¹⁰	503 ¹⁰		18			"		
868 ¹⁰	5 ¹⁰	127 ¹⁰		13		27 ⁰⁵ h.m.	"		
497 ^{3/4}				0			Hamestake		
498 ^{3/4}				0			"		
422 ¹⁰	162 ¹⁰	416 ¹⁰		16			The Atlas Co. Denver.		
225 ¹⁰	78 ¹⁰	696 ¹⁰		21			Harold R. Gilbert: St. Petersburg, Fla		
772 ¹⁰	139 ¹⁰	891 ¹⁰		13			Herkling & Skusker		
845 ¹⁰	143 ¹⁰	121 ¹⁰		12			"		
993 ^{3/4}				6			Pashin Gold Mfg Co. Eureka, Cal.		
881 ¹⁰	104 ¹⁰	14 ¹⁰		12		2 ³⁰ h.m.	Herkling & Skusker		
950 ¹⁰	48 ¹⁰	21 ¹⁰		6			Thea Stewart: Burley, Id.		
959 ¹⁰	22 ¹⁰	19 ¹⁰		6			Stonewall Enterprises, Los Alamos		
332 ¹⁰	183 ¹⁰	485 ¹⁰		0			Supt		
760 ¹⁰	40 ¹⁰	200 ¹⁰		0			Supt		
997.6				0			Hamestake		
429 ¹⁰	123 ¹⁰	447 ¹⁰		16		4 ⁵⁵ h.m.	John Roberts Mfg.		
974 ¹⁰	119 ¹⁰	7 ¹⁰		12			Crosby Land & Mineral Co.		
247 ¹⁰	252 ¹⁰	500 ¹⁰		0			Supt		
450 ¹⁰	110 ¹⁰	439 ¹⁰		0			"		
916 ¹⁰	82 ¹⁰	1 ¹⁰		12			Edward L. Woodfield. Denver		
400 ¹⁰	93 ¹⁰	506 ¹⁰		18			Josten		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 890500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
			1073	1078	met Scrap	Ind.	338.13
			1074	1079	Scrap	"	
			1075	1080	"	"	
6/12			1076	1081	Bars.	Nevada-Eureka	5045.62
			1077	1082	Bars	Ind.	22.74
			1078	1083	"	"	41.14
			1079	1084	6 Bars		69.32
6/14			1080	1085	Bars	S. Dakota	2 0538.3
			1081	1086	"	"	3038.35
			1082	1087	pl Scrap	Ind.	240.83
			1083	1088	"	"	366.53
			1084	1089	"	"	509.01
			1085	1090	"	"	44.77
			1086	1091	"	"	18.63
			1087	1092	"	"	21.26
6/15			1088	1093	Scrap	"	2063.71
			1089	1094	-	"	30.97
			1090	1095	✓	"	60.27
			1091	1096	✓	"	9.57
			1092	1097	Bars	S. Dak.	7420.63
			1093	1098	Scrap	Ind.	784.50
			1094	1099	"	"	641.80
			1095	1100	"	"	330.44
			1096	1101	"	"	224.81
			1097	1102	pl Scrap	"	36.35
			1098	1103	"	"	66.99
			1099	1104	"	"	212.44
			1100	1105	"	"	199.41
			1101	1106	"	"	789.81
			1102	1107	"	"	8.54

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
419 ¹⁰	113 ¹⁰	468 ¹⁰	18			6 ⁰⁵ h.m.	\$		\$
401 ^{1/2}	102 ¹⁰	496 ^{1/2}	18						
397 ¹⁰	110 ¹⁰	493 ¹⁰	18						
996.4			0						
495 ^{1/2}	79 ¹⁰	425 ^{1/2}	16			2 ³⁰ h.m.			
415 ^{1/2}	111 ¹⁰	413 ^{1/2}	16			2 ³⁰ h.m.			
441 ¹⁰	59 ¹⁰	500 ¹⁰	18						
996 ^{3/4}			0						
997 ^{3/4}			0						
960 ¹⁰	0 ¹⁰	40 ¹⁰	6			4 ⁵⁵ h.m.			
713 ^{1/2}	1 ¹⁰	285 ^{1/2}	18						
65 ^{1/2}	5 ¹⁰	343 ^{1/2}	18			8 ³⁰ h.m.			
899 ¹⁰	5 ¹⁰	103 ¹⁰	13			2 ³⁰ h.m.			
988 ¹⁰	0 ¹⁰	12 ¹⁰	6			2 ³⁰ h.m.			
997 ^{1/2}	1 ¹⁰	1 ^{1/2}	0						
374 ^{1/2}	87 ¹⁰	538 ^{1/2}	18						
516 ^{1/2}	76 ¹⁰	407 ^{1/2}	21						
564 ^{1/2}	103 ¹⁰	332 ^{1/2}	18						
479 ¹⁰	197 ¹⁰	324 ¹⁰	13						
997.1			0						
368 ¹⁰	123 ¹⁰	509 ¹⁰	18						
396 ¹⁰	86 ¹⁰	548 ¹⁰	18						
402 ^{1/2}	152 ¹⁰	445 ^{1/2}	16			6 ⁰⁵ h.m.			
429 ¹⁰	122 ¹⁰	449 ¹⁰	16						
986 ^{1/2}	0 ¹⁰	13 ^{1/2}	6			2 ³⁰ h.m.			
987 ¹⁰	2 ¹⁰	11 ¹⁰	6						
970 ¹⁰	0 ¹⁰	130 ¹⁰	13						
997 ¹⁰	0 ¹⁰	3 ¹⁰	0						
508 ^{1/2}	7 ¹⁰	484 ^{1/2}	23			12 ⁰⁵ h.m.			
898 ¹⁰	93 ¹⁰	9 ¹⁰	12						

Joesten

Baslin Gold Mng. Co., Nev.

Star Jewelry Co. Houston

" " "

Wilbur Packing Co. Buffalo, N. Y.

Hornestake

"

Matarsala

"

"

"

"

"

Joesten

O'Donnell Jewelry Co. San Antonio

Carl Blockrock; Alhambra, Cal.

Peterson Jewelry, Boulder, Cal.

Hornestake

Joesten

John Roberts' Mfg.

A. L. Sharpe

Matarsala

"

"

"

"

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
6/15	Rimner		1103	1108	PL Scrap	Lead	153.93
			1104	1109	Sweeps	"	190.93
			1105	1110	Scrap	"	412.01
			1106	1111	"	"	800.41
	S.B.		21	21	S.B.	"1" Granis #1V	922.64
6/21	G.B.		12	12	G.B.	Grains deposits 6/67	33.70
							14.75

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
695 ¹⁰	57 ¹⁰	300 ¹⁰	18			3 ⁰⁰ h.m.	\$	Basco Porcelain Co; Golden.	\$
413 ¹⁰	113 ¹⁰	474 ¹⁰	18			6 ⁸⁰ h.m.		Joaten	
409 ¹⁰	101 ¹⁰	490 ¹⁰	18					"	
401 ¹⁰	108 ¹⁰	491 ¹⁰	18					"	
460 ¹⁰	106 ¹⁰	434 ¹⁰	0					Sup't	
604 ^{1/2}	65 ¹⁰	330 ^{1/2}	0					Sup't	

REGISTER OF ASSAYS,

DATE		NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay		
6/26			1	1	Bars S. Nak	1631.51
			2	2	" "	5775.35
			3	3	Scrap Sud	46.18
			4	4	Emblems	42.31
			5	5	Scrap	192.59
			6	6	1-1/2 ling	Re 32.31
			7	7	Retest Idaho - Boise	32.99
			8	8	Scrap Sud	24.06
			9	9	with Sweeps	79.131
			10	10	Scrap	1063.45
			11	11	Bars S. Nak	1936.61
			12	12	Re Scrap Sud	710.55
			13	13	"	305.17
			14	14	"	73.42
			15	15	"	86.83
			16	16	"	24.72
			17	17	31N66 Sweeps	70.395
			18	18	Scrap	136.69
			19	19	"	116.50
			20	20	Filings	39.06
			21	21	Scrap	132.03
			22	22	with Sweeps	797.64
			23	23	Scrap	508.03
			24	24	"	922.05
			25	25	Gold	1295.85
6/28			26	26	Bars S. Nak	358.09
✓			27	27	✓ S. Nak	225.84
6/26			28	28	Scrap Sud	3733.41
			29	29	"	316.49
			30	30	"	1024.12
						878.45

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 630500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
6/26		PART	31	31	Bars	Nevada, Eureka	5242.18
			"	32	✓	✓	343.56
6/28			32	33	Scrap	Ind.	32.33
			33	34	"	"	12.51
6/29			34	35	Bars	S. Klak	6572.70
			35	36	Refuse	Idaho - Boise	6.16
			36	37	Scrap	Idaho	9.75
			C-1	C-1	Coin	1 - Saudi Arab	0.25
			C-2	C-2	"	1 - 20 U.S.	1.07
			C-3	C-3	"	1 - Guinea	0.25
			"	C-4	"	1 - 10 S. Franc. (Austria)	0.10
			C-4	C-5	"	3 - 10 U.S.	1.51
			C-5	C-6	"	1 - 2 1/2 Peso	0.31
			C-6	C-7	"	1 - 10 Peso	0.46
			C-7	C-8	"	3 - Mex Gold Coin	1.37
			C-8	C-9	"	1 - 20 Peso	0.51
			C-9	C-10	"	1 - 2 1/2 Peso	0.06
			C-10	C-11	"	4 - 2 1/2 Peso	0.26
7/6			37	38	Wet Sweeps	Ind	466.51
			38	39	Scrap	"	796.83
			39	40	✓	"	1002.84
			40	41	3 - Bars	Nevada - Eureka	3749.37
			41	42	Refuse	Pelo. - Duray	341.74
			42	43	"	" - Adams	20.47
			43	44	"	" - Jeff	31.58
			44	45	Bars	S. Klak	36.67
			45	46	"	"	1909.82
			46	47	P.L. Scrap	Ind	4371.74
			47	48	Filings	"	23.07
			48	49	"	"	69.02
							45.77

Remelt

Remelt

Lat	Long	Alt	Dist	Locality
990.7		6		Cashin Cold Mng.
990.5		6		" " "
404° 127° 469°		18		Manassas Inc, Blytheville, Ark.
536° 183° 281°		18		George F. Hill; Caladapp, Colo.
997.2		0		Hamestake
594° 396° 10°		12	2 ³⁰ h.m.	Ralph E. Bradley; Boise Idaho.
797 1/2 117° 85 1/2		13		Mr. George E. Wingerson, Hanter, Iowa
915° 0° 85°		13		Mrs Agnes P. Jorard, Houston, Tex
900° 0° 100°		0		Mrs Velma F. Johnson, Houston, Tex
916 3/4 0° 83 3/4		13		Mrs Velma F. Johnson, Houston, Tex
985° 0° 15°		6		" " "
900° 0° 100°		0		Mrs Poncher San, Jamaica, N. Y.
900° 0° 100°		13		Mr. Garner H. Mahry; Houston, Tex
900° 0° 100°		13		Mr. Thomas F. Weigand, Arlington, Va.
900° 0° 100°		13		Patience H. Koshewar; Dallas, Tex
900° 0° 100°		13		Mr. Richard C. Falk; Park Ridge, Ill.
900° 0° 100°		13		Mr. James E. Stumblough; Richardson, Tex
900° 0° 100°		13		Mr. Alfred H. Turner; Albuquerque, N. Mex
477° 111° 472°		18	8 ³⁰ h.m.	Josten
398° 106° 496°		18		"
406° 83° 511°		18		"
993 3/4		6		Cashin Fu Mng Co.
364° 131° 505°		18		Idasado.
874 1/2 107° 18 1/2		12	2 ³⁰ h.m.	Keckling & Klecker
950° 137° 13°		12		" "
996 1/4		0		Hamestake
998 1/4		0		"
698 1/2 0° 301 1/2		18	2 ³⁰ h.m.	Barri's Rocalain
457° 76° 467°		18	2 ³⁰ h.m.	Triad Manufacturers Group; Buffalo, N. Y.
464° 66° 470°		18	2 ³⁰ h.m.	Fashion Craft Corp; Chicago, Ill.

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
7/6			49	50	Scrap	Jewelry Ind	17.50
			50	51	Gilings	"	19.78
			51	52	Smuggs	"	60.30
			52	53	Bars	J. H. K.	75.87
			53	54	Pl Scrap	Ind	339.91
			54	55	RR Scrap	"	398.20
			55	56	Pl Scrap	Ind	53.43
			56	57	"	"	59.36
Jan 6/30			C-11	C-12	Medal	1-Gold Medal Gerson	0.14
J.M. 6/30			C-12	C-13	Gold	1-10 Guilder R	1.95
Forfeited			"	C-14	"	14-Mex 100 Canico	2.65
"						1-100 Peso The Bank Note	828.52
7/10			57	58	H. Somo	Ind.	61.40
			58	59	Beads	"	118.74
			59	60	Pl	"	42.82
			60	61	Scrap	"	248.23
			61	62	"	"	1017.17
			62	63	"	"	794.14
			63	64	Scrap	"	878.54
			64	65	"	"	400.31
			65	66	"	"	1378.25
			66	67	"	"	812.89
			67	68	"	"	1033.44
			68	69	"	"	284.53
			69	70	"	"	12.69
			70	71	Robert	Colo - Jeff	3.21
			71	72	Amala	Arizona - Maricopa	4.60
			72	73	met	"	533.65
			73	74	Scrap	"	116.10
			74	75	Spec. Fr.	"	775.05
			75	76	Smuggs	Ind	
					Scrap	"	
					"	"	

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 529 ¹⁰	79 ¹⁰	392 ¹⁰		21		\$	\$		
✓ 533 ^{1/2}	63 ¹⁰	403 ^{1/2}		21	2 ³⁰ km.		\$		
✓ 410 ^{1/2}	111 ¹⁰	478 ^{1/2}		18	9 ⁸⁰ km.				
999.4				0					
✓ 945 ¹⁰	2 ¹⁰	53 ¹⁰		13					
✓ 969 ¹⁰	2 ¹⁰	29 ¹⁰		6					
✓ 986 ^{1/2}	8 ¹⁰	5 ^{1/2}		6					
✓ 965 ^{1/2}	0 ¹⁰	34 ^{1/2}		6	2 ³⁰ km.				
✓ 986 ¹⁰	0 ¹⁰	4 ¹⁰		6					
✓ 900 ¹⁰	0 ¹⁰	100 ¹⁰		13					
✓ 366 ¹⁰	104 ¹⁰	530 ¹⁰		18					
✓ 820 ¹⁰	1 ¹⁰	169 ¹⁰		16	10 ¹⁵ km.				
✓ 922 ¹⁰	0 ¹⁰	78 ¹⁰		13	2 ³⁰ "				
✓ 988 ¹⁰	0 ¹⁰	12 ¹⁰		6					
✓ 981 ¹⁰	0 ¹⁰	19 ¹⁰		6					
✓ 637 ^{1/2}	0 ¹⁰	362 ^{1/2}		21					
✓ 404 ¹⁰	101 ¹⁰	495 ¹⁰		18					
✓ 303 ^{1/2}	344 ¹⁰	352 ^{1/2}		16	9 ⁸⁰ km.				
✓ 396 ¹⁰	103 ¹⁰	501 ¹⁰		18					
✓ 396 ¹⁰	106 ¹⁰	498 ¹⁰		18					
✓ 398 ¹⁰	101 ¹⁰	501 ¹⁰		18					
✓ 398 ¹⁰	103 ¹⁰	499 ¹⁰		18					
✓ 401 ¹⁰	99 ¹⁰	500 ¹⁰		18					
✓ 398 ^{1/2}	102 ¹⁰	499 ^{1/2}		18	7 ⁵⁵ km.				
✓ 867 ¹⁰	129 ¹⁰	4 ¹⁰		12					
✓ 377 ^{1/2}	65 ¹⁰	557 ^{1/2}		21	2 ³⁰ km.				
✓ 303 ¹⁰	67 ¹⁰	630 ¹⁰		21					
✓ 417 ^{1/2}	112 ¹⁰	470 ^{1/2}		18	9 ⁰⁵ km.				
✓ 428 ^{1/2}	118 ¹⁰	453 ^{1/2}		18					
✓ 409 ¹⁰	118 ¹⁰	473 ¹⁰		18					
							Finch Jewelers;ovina, Calif.		
							G. Herrera; Fort Worth, Tex		
							Josten		
							Homestake		
							Motorola		
							"		
							Motorola		
							"		
							Port Director of Pustons; Perumond, Tex		
							Dist. Director Pustons, Laredo, Tex		
							" " " " "		
							Motorola		
							"		
							"		
							"		
							Josten		
							"		
							"		
							"		
							"		
							"		
							John Roberts.		
							Robt B. Ray		
							Mr. Virgil P. Young; Phoenix		
							Samuel Schuman;		
							Josten		
							"		
							"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930800

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
7/10			76	77	Scrap	Ind	842.45
7/11			77	78	Silver Amalgam	"	28.11
			78	79	PI Scrap	"	26.57
			79	80	Bars	S. Alaska	1595.13
			78	81	"	"	4630.70
7/14			81	82	Scrap	Ind	989.39
			82	83	✓	✓	710.26
			83	84	✓	✓	1259.43
			84	85	✓	✓	461.14
			85	86	✓	✓	393.51
			86	87	✓	✓	1025.44
			87	88	✓	✓	944.26
			88	89	✓	✓	564.95
			89	90	✓	✓	78.11
			90	91	✓	✓	11.53
			91	92	✓	✓	270.23
			92	93	Bars	S. Alaska	3203.09
			93	94	Scrap	Ind	187.75
			94	95	✓	✓	185.73
7/18	2. L. 7/11/67		C-15	C-15	Coin	1-10 Peso	0.26
			95	96	Scrap Residue	Ind	493
			96	97	Nat. Bars	Alaska - Kuskokwim	174.14
			97	98	Scrap	Ind	87.11
7/20			98	99	Bars	S. Alaska	1727.05
			99	100	✓	✓	4004.28
			100	101	Scrap	Ind	301.83
			101	102	"	"	59.92
7/27			102	103	Scrap	"	39.75
			103	104	Ret Wet	Idaho - Baine	20.44
			104	105	Retort	Colorado - Moffat	6.92

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
390 ¹⁰	103 ¹⁰	507 ¹⁰	18			\$	\$	\$	
0 ¹⁰	139 ¹⁰	261 ¹⁰	10			2 ³⁰ h.m.	Josten Capt H.E.W. Oklahoma City, Okla. G.T.I. Corp; Petaluma, Calif. Homestake		
994 ¹⁰	0 ¹⁰	6 ¹⁰	6						
997 ¹⁰			0						
998 ¹⁰			0						
403 ¹⁰	112 ¹⁰	484 ¹⁰	18				Josten		
398 ¹⁰	106 ¹⁰	495 ¹⁰	18				"		
400 ¹⁰	107 ¹⁰	493 ¹⁰	18				"		
417 ¹⁰	112 ¹⁰	471 ¹⁰	18			7 ⁵⁵ h.m.	"		
405 ¹⁰	101 ¹⁰	493 ¹⁰	18				"		
418 ¹⁰	108 ¹⁰	473 ¹⁰	18				"		
362 ¹⁰	309 ¹⁰	328 ¹⁰	13				"		
433 ¹⁰	92 ¹⁰	475 ¹⁰	18				"		
536 ¹⁰	94 ¹⁰	370 ¹⁰	21				Santher Jewelry Co; San Antonio		
551 ¹⁰	107 ¹⁰	342 ¹⁰	18				Charlie B. Scott; Austin		
545 ¹⁰	83 ¹⁰	371 ¹⁰	21				J.W. Texas Precious Metals		
997 ¹⁰			0				Homestake		
245 ¹⁰	66 ¹⁰	688 ¹⁰	21				Harold R. Gilbert; St. Petersburg, Fla.		
446 ¹⁰	119 ¹⁰	434 ¹⁰	16				J. L. Thorpe & Co; Leadwood, S.D.		
900 ¹⁰	0 ¹⁰	100 ¹⁰	13				Mr. Edwin A. Allen; Hamilton, Tex		
557 ¹⁰	72 ¹⁰	371 ¹⁰	21				Scott Paris; Worland, Wyo.		
879 ¹⁰	114 ¹⁰	6 ¹⁰	12				Manuel Creek Mfg Co; Chulavita, Alaska		
444 ¹⁰	105 ¹⁰	448 ¹⁰	16				Harold's Trading Post; Arkansas City, Kan.		
996 ¹⁰			0				Homestake		
998 ¹⁰			0				"		
370 ¹⁰	143 ¹⁰	487 ¹⁰	18			9 ⁰⁵ h.m.	John Roberts Mfg Co.		
476 ¹⁰	158 ¹⁰	366 ¹⁰	16				Louis W. Spiegel; Anapa Park, Calif		
431 ¹⁰	73 ¹⁰	495 ¹⁰	18				Sweeney & Co. - Houston		
769 ¹⁰	229 ¹⁰	1 ¹⁰	12				A.W. Jones; Garden Valley, Idaho		
944 ¹⁰	52 ¹⁰	3 ¹⁰	12			2 ³⁰ h.m.	Bruce W. Zimmerman; Craig, Colo.		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 190200

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
7/27			105	106	Scrap	Ind	59.39
			106	107	"	"	29.73
7/25			107	108	4-Bars	Nevada - Eureka	5017.0
✓			109	109	3-Bars	" "	4028.39
7/27			108	110	Bars	I. H. H. H.	6507.6
			109	111	✓	- -	2253.95
			110	112	✓	✓ -	3822.72
			111	113	Scrap	Ind	251.86
			112	114	✓	"	68.05
			113	115	✓	"	145.59
			114	116	✓	"	133.44
			115	117	✓	"	556.38
			116	118	✓	"	58.69
			117	119	Pl Scrap	Ind	424.25
			118	120	"	"	348.39
			119	121	"	"	271.20
7/26			120	122	Mut Coin	Wutilated silver Coin	95.91
7/31 → 8/1			121	123	Pl 6rs	Montana - Meagher	2.84
			122	124	Bars	I. H. H. H.	5989.59
			123	125	Scrap	Ind	23.59
			124	126	"	"	88.06
			125	127	"	"	38.81
			126	128	"	"	39.06
			127	129	Bars	Nevada - Eureka	5531.71
			128	130	Scrap	Ind	6.95
			129	131	✓	-	121.88
			130	132	Bars	Nevada - Eureka	5951.28
			131	133	Bars	I. H. H. H.	2255.62
			132	134	"	" "	3587.74
8/2			133	135	Scrap	Ind	264.49

8/4 Remelt

Part in assay Bar #20

6/34/68

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
442 1/2	63 1/10	494 1/2	18			2 30 ^{\$} h.m.			
510 1/2	83 1/10	406 1/2	21						
991.4			6						
991.9			6						
997.3			0						
996 3/4			0						
997 3/4			0						
509 1/2	99 1/10	391 1/2	21			2.30 w.g.			
457 1/2	142 1/10	400 1/2	16			4.00 h.m.			
427 1/2	92 1/10	480 1/2	18			3 80 h.m.			
423 1/10	84 1/10	493 1/10	18			3 80 h.m.			
395 1/2	63 1/10	541 1/2	18			13.80 w.g.			
442 1/10	70 1/10	488 1/10	18			2 30 h.m.			
938 1/2	2 1/10	59 1/2	13						
746 1/10	0 1/10	254 1/10	18						
848 1/2	3 1/10	148 1/2	13			5 30 h.m.			
0 1/10	757 3/4	242 1/4	0						
847 1/2	149 1/10	3 1/2	17						
997.5			0						
472 1/2	77 1/10	450 1/2	18			2 30 h.m.			
529 1/10	91 1/10	380 1/10	21						
504 1/10	88 1/10	408 1/10	21						
855 1/10	45 1/10	100 1/10	13			2 30 h.m.			
993.9			6						
565 1/2	50 1/10	384 1/2	21						
460 1/10	140 1/10	400 1/10	16			3 05 h.m.			
993.9			6						
997 3/4			0						
998 1/10			0						
384 1/10	148 1/10	468 1/10	18			7 55 h.m.			
							Fashion Craft Mfg Co; Buffalo, N. Y.		
							N. Y. Finkelman Co., Chicago		
							Cashin Mining Co. Elka, Nev.		
							"		
							Hornestake		
							"		
							"		
							S. W. S. Ref Co.		
							" " " "		
							Wilber Packing Co, Inc. Buffalo, N. Y.		
							" " "		
							Joeten		
							Triad Mfgs Group; Buffalo, N. Y.		
							Malarsala		
							"		
							"		
							Supt		
							Robt J. Williamson; Bell, Mont.		
							Hornestake		
							Star Jewelry Co, Hamilton		
							Southern Jewelry Co, San Antonio		
							Berger & Co; Hamilton		
							George R. Rammie; Bridgefield, N. J.		
							Cashin Mfg Co, Elka, Nev.		
							Blake Jewelry Co.		
							S. W. Texas Precious Metals.		
							Cashin Mfg Co.		
							Hornestake		
							"		
							John Roberts Mfg; Norman, Okla		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
8/3			134	136	Scrap	Ind	1449
			135	137	✓	"	779
	S.B.		136	138	Grains		
	N.M. Letter				Bar	Grains - July + Gold Coins	3031
	7/31/67		C-14	C-16	Coin	1-20 Peso	053
	✓		C-15	C-17	"	1-Guilder: Netherlands	031
	✓		C-16	C-18	"	1-20 Peso	
	✓		C-17	C-19	"	2-10 " " "	134
	✓		C-18	C-20	"	1-50 Peso	134
	✓		C-19	C-21	"	1-20 Peso	053
	✓				"	1-50 Peso	013
8/4			136	138	Bars	S. Mak.	7366.5
			137	139	Scrap	Ind	227.51
			138	140	PI Scrap	"	✓ 557.73
			139	141	"	"	14674
			140	142	"	"	81443
			141	143	"	"	3239
	N.M. Lr. 8/3/67						
	Seizure		C-21	C-23	Coin	1-10 A.S.	053
	N.M. 8/2/67		C-22	C-24	"	1-Max - Comm.	001
8/8	N.M. 7/31/67		142	144	Artec Gold	Ind. Figure	N.M. 040
			143	145	Scrap	Ind	1170
			144	146	Bars.	Nevada-Eureka	368795
			145	147	Scrap	Ind	40474
	S.B.		1	1	S.B.	"15" Grains #1	3047
8/9	8/11		146	148	Net Gts B. Sand	Alaska - Ind - Kostokum	28365
			147	149	Scrap	Ind	3302
			148	150	Bars	S. Mak	255463
			149	151	✓	- -	399465
			150	152	Scrap	Ind	1306
			151	153	Ref	Leads - Jeff	2059
			152	154	✓	" - Adams	2551
			153	155	✓	Calc - Moffat	131

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
634 ¹⁰	119 ¹⁰	247 ¹⁰	16			\$	\$		
468 ¹⁰	148 ¹⁰	383 ¹⁰	16				George L. Kyzeth; Clarion, Iowa		
687 ¹⁰	62 ¹⁰	250 ¹⁰	0				Lucien S. Mins; Denver, Colo.		
900 ¹⁰	0 ¹⁰	100 ¹⁰	13				Supt		
750 ¹⁰	86 ¹⁰	164 ¹⁰	0				Homer V. Fleming; Houston		
900 ¹⁰	0 ¹⁰	100 ¹⁰	13				Bureau of Customs; Houston		
900 ¹⁰	0 ¹⁰	100 ¹⁰	13				Jan Menna, Pineblowood, Ill.		
900 ¹⁰	0 ¹⁰	100 ¹⁰	13				Robert A. Strickler; Harrisonburg, Va.		
900 ¹⁰	0 ¹⁰	100 ¹⁰	13				Mrs Mary E. Harris; Amarillo, Tex		
900 ¹⁰	0 ¹⁰	100 ¹⁰	13				C. A. Talier; St. Louis, Mo.		
997.5			0				Honestake		
429 ¹⁰	144 ¹⁰	426 ¹⁰	16				J. L. Sharpe & Co; Meadowood		
478 ¹⁰	1 ¹⁰	25 ¹⁰	6				Naturala.		
603 ¹⁰	7 ¹⁰	389 ¹⁰	21			4 ⁵⁰ h.m.	"		
399 ¹⁰	107 ¹⁰	494 ¹⁰	18				Josten		
413 ¹⁰	198 ¹⁰	388 ¹⁰	16			2 ³⁰ h.m.	Louis Spiegel, Concord Park, Calif.		
900 ¹⁰	0 ¹⁰	100 ¹⁰	0				Director of Customs; Houston		
900 ¹⁰	0 ¹⁰	100 ¹⁰	13				William L. Haugherty; Belvoir, Tex		
560 ¹⁰	112 ¹⁰	327 ¹⁰	0				Port Director of Customs; Brownsville, Tex		
671 ¹⁰	113 ¹⁰	216 ¹⁰	16				Lewis Weidenbaum; Wichita, Texas		
487 ¹⁰	3 ¹⁰	9 ³⁰	6				Carlin Mfg Co.		
418 ¹⁰	115 ¹⁰	467 ¹⁰	18			7 ⁵⁰ h.m.	Josten's		
435 ¹⁰	100 ¹⁰	464 ¹⁰	0				Supt		
874 ¹⁰	114 ¹⁰	12 ¹⁰	12				Manuel Creek Mfg Co. Via Quick		
431 ¹⁰	70 ¹⁰	498 ¹⁰	18			2 ³⁰ h.m.	Wilbur Pectus; Co. Buffalo, N. Y.		
996 ¹⁰			0				Honestake		
998 ¹⁰			0				"		
733 ¹⁰	112 ¹⁰	155 ¹⁰	16				Jacobson Jewelry Co. Omaha		
848 ¹⁰	137 ¹⁰	14 ¹⁰	12				Keeshing & Klucker		
858 ¹⁰	106 ¹⁰	39 ¹⁰	12			2 ³⁰ h.m.	"		
947 ¹⁰	51 ¹⁰	21 ¹⁰	12			2 ³⁰ h.m.	Owie W. Gunnerman, Craig, Colo.		

DATE 1967			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
8/9 Wae	Wae	2-31-67	C-20	C-22 Mex C-20 Cam	12-50 Pass 6-20" 2-5"	1- Emp Mex 1865	4.7-19.38
			154	156 Scrap		Lud	755
			155	157 "		"	342
			156	158 Grant's Sand		Mont-Meagher	7686
			157	159 Bars		S. Klak	1351.08
			158	160 "		"	2269.66
			159	161 Scrap		Lud	8739.2
			160	162 "		"	457.24
			161	163 "		"	348.98
			162	164 "		"	448.58
			163	165 "		"	724.35
8/10			164	166 "		"	221.70
8/14			165	167 3-Bars		Nevada, Eureka	4017.91
8/17			166	168 Scrap		Lud	275.25
			167	169 Bars		S. Klak	3052.11
			168	170 " "		" "	1943.40
			169	171 pl Scrap		Lud	1803.50
			170	172 "		"	53.06
			171	173 "		"	495.06
			172	174 "		"	165.96
			173	175 Scrap		"	70.60
			174	176 "		"	95.74
			175	177 "		"	474.22
			176	178 Ret Am brs		Calo - Ourey	403.07
			177	179 Retest		Idaho - Mine	16.40
8/18			178	180 Bars		S. Klak	3846.24
			179	181 Scrap		Lud	933.48
			180	182 ✓		✓	Re-845.50 848.56
			181	183 ✓		✓	434.54
			182	184 ✓		✓	566.32

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
900 ¹⁰	2 ¹⁰	98 ¹⁰	0			\$	\$	\$	Post Director of Customs; Brownsville
282 ^{1/2}	48 ¹⁰	669 ^{1/2}	23						Samuel Johnson; Chicago, Ill
757 ^{1/2}	128 ¹⁰	114 ^{1/2}	13						James P. Ryan U.S. Littleton
786 ^{1/2}	187 ¹⁰	26 ^{1/2}	12						Glen H. Allman; White Sulphur ^{Spa}
997 ^{3/4}			0						Hornestake
997 ^{3/4}			0						"
391 ¹⁰	104 ¹⁰	505 ¹⁰	18						Joeten
414 ^{1/2}	114 ¹⁰	471 ^{1/2}	18			8 ³⁰ h.m.			"
404 ^{1/2}	94 ¹⁰	501 ^{1/2}	18						"
420 ¹⁰	119 ¹⁰	461 ¹⁰	18			7 ⁵⁵ h.m.			"
405 ^{1/2}	101 ¹⁰	493 ^{1/2}	18						"
997 ¹⁰	0 ¹⁰	31 ⁰	0						G. T. I. Corp, Petaluma, Cal.
993 ^{1/4}			6						Carlin Gold Mng. Co, Elko, Nev.
55 ⁰	87 ¹⁰	388 ¹⁰	21						S.W. Texas Precious Metals.
997 ^{3/4}	2 ^{1/4}	0 ¹⁰	0						Hornestake
997 ^{3/4}	2 ^{3/4}	0 ¹⁰	0						"
928 ¹⁰	31 ⁰	69 ¹⁰	13						Matonsala
976 ^{1/2}	0 ¹⁰	23 ^{1/2}	6						"
985 ¹⁰	0 ¹⁰	15 ¹⁰	6						"
811 ¹⁰	21 ⁰	187 ¹⁰	16						"
412 ^{1/2}	131 ¹⁰	456 ^{1/2}	18						Louis W. Spiegel, Canoga Park, Calif.
435 ¹⁰	73 ¹⁰	492 ¹⁰	18			3 ⁰⁵ h.m.			Welbar Pasting Co; Buffalo, N. Y.
398 ¹⁰	132 ¹⁰	470 ¹⁰	18			6 ⁵⁰ h.m.			John Roberts Mfg Co.
361 ^{1/2}	118 ¹⁰	520 ^{1/2}	18						Idarado Mng. Co.
774 ¹⁰	222 ¹⁰	41 ⁰	12						A.W. Joene, Garden Valley, Idaho.
997 ^{1/2}	2 ^{1/2}	0 ¹⁰	0						Hornestake
369 ^{1/2}	173 ¹⁰	457 ^{1/2}	18						Joeten
400 ^{1/2}	140 ¹⁰	459 ^{1/2}	18						"
423 ¹⁰	116 ¹⁰	461 ¹⁰	18			7 ⁵⁵ h.m.			"
396 ^{1/2}	101 ¹⁰	502 ^{1/2}	18						"

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 900500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
8/18			183	185	Scrap	Ind	496.9
			184	186	"	"	883.61
8/24			185	187	Ref	Colo-Adams	17.14
8/24	split heat		186	188	Bars	Nevada-Eureka	4823.5
	"		✓	189	✓	" "	3636.2
			✓	188	7-Gold Bars	Settle-Average	8459.71
			187	190	Bars	S. Hak	2088.71
			188	191	"	" "	4119.81
			189	192	Pl Scrap	Ind	304.4
			190	193	✓	✓	480.21
			191	194	Scrap	✓	342.88
			192	195	✓	✓	201.33
			193	196	✓	✓	89.61
			194	197	✓	✓	799.66
			195	198	✓	✓	900.61
			196	199	✓	✓	1071.88
			197	200	✓	✓	479.45
			198	201	✓	✓	514.25
8/28			2-23	2-25	Latin	10-20 Canadian	58.1
			199	202	Bars	S. Hak	5754.01
			200	203	Pl Scrap	Ind	3044.17
			201	204	Pl Scrap	"	360.06
			202	205	Pl Scrap	"	34.37
			203	206	Scrap	Ind	760.07
			204	207	Refret	Colo-Adams	90.45
			205	208	rr #	Milled to Poin #22	18.44
			206	209	1/2-1/4 1/10	" " "	555.07
			207	210	Bars	Nevada-Eureka	5251.08
			208	211	Refret	Montana-Rossell	22.02
9/30			209	212	Scrap	Ind	57.92

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
385 ⁰	100 ¹⁰	55 ¹⁰	18			\$	\$	\$	
400 ¹⁰	107 ¹⁰	493 ¹⁰	18			9 ⁸⁰ h.m.	Jostin		
801 ^{1/2}	149 ¹⁰	49 ^{1/2}	12			2 ³⁰ h.m.	"		
994.9							Henshaw & Henshaw		
995.3							Carlin Mng Co., Elko, Nevada		
995.0	2 ¹⁵	2 ¹⁵	0				"	"	✓
996 ^{3/4}	2 ^{1/4}	1 ¹⁰	0				"	"	✓
997 ^{1/4}	1 ^{3/4}	1 ¹⁰	0				Hornetake		
577 ^{1/2}	8 ¹⁰	44 ^{1/2}	21			3 ⁸⁰ h.m.	"		
889 ¹⁰	0 ¹⁰	111 ¹⁰	13				Matosala		
388 ^{1/2}	122 ¹⁰	489 ^{1/2}	18			5 ³⁰ h.m.	"		
534 ^{1/2}	95 ¹⁰	370 ^{1/2}	21				John Roberts Mfg. Norman, Okla.		
466 ^{1/2}	139 ¹⁰	394 ^{1/2}	16			3 ²⁵ h.m.	S.W. S. Ref. Co., Dallas.		
401 ¹⁰	110 ¹⁰	489 ¹⁰	18				"	"	
405 ¹⁰	107 ¹⁰	488 ¹⁰	18				Jostin		
399 ¹⁰	110 ¹⁰	491 ¹⁰	18				"		
423 ¹⁰	118 ¹⁰	459 ¹⁰	18			8 ³⁰ h.m.	"		
399 ¹⁰	110 ¹⁰	491 ¹⁰	18				"		
844 ¹⁰	0 ¹⁰	101 ¹⁰	0				Rich. Henshaw & Henshaw, Great Falls		
998.1	1 ⁹	0 ¹⁰	0				Hornetake		
912 ^{1/2}	3 ¹⁰	84 ^{1/2}	13				Matosala		
867 ¹⁰	2 ¹⁰	131 ¹⁰	13				"		
972 ^{1/2}	0 ¹⁰	27 ^{1/2}	6				"		
396 ¹⁰	89 ¹⁰	55 ¹⁰	18				Jostin		
833 ¹⁰	108 ¹⁰	59 ¹⁰	13				Carlin Mng Co.		
—	900 ^{1/2}	99 ^{1/2}	0				Wesley Travel Co.		
—	865 ^{1/2}	134 ^{1/2}	0				Supt		
994.6	3 ^{1/4}	2 ¹⁰	6				"		
915 ^{1/2}	81 ¹⁰	3 ^{1/2}	12				Carlin Mng Co.		
476 ¹⁰	59 ¹⁰	465 ¹⁰	18			2 ³⁰ h.m.	Mrs. H. K. Schaefer, Deer Lodge, Mont.		
							Jackson Craft Mfg Co., Buffalo, N.Y.		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 1930000

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
8/30			210	213	Scrap	Ind.	123
			211	214	Ret	Colo-Jeff	1683
			212	215	Scrap	Ind.	41342
			213	216	"	"	69343
			214	217	"	"	63124
			215	218	"	"	713
8/31			216	219	Grains Blk Sands	Alaska - Kuskokwim	17636
	See scrap #708 Aug 713		217	220	Scrap	"	311
8/31			218	221	Bars	S. Alaska	219944
			219	222	"	"	408073
9/1			220	223	Scrap	Ind	680
			221	224	"	"	2779
			222	225	Bars	S. Alaska	619756
			223	226	Pl Scrap	Ind	26295
			224	227	"	"	17688
			225	228	"	"	68641
			226	229	"	"	115352
			227	230	Scrap	"	5501
			228	231	"	"	2333
			229	232	"	Antal	552
			C-24	C-24	U.S. Coin	1-#10 U.S.	371 051
9/5			230	233	Ret	Colo-Jeff	1560
			231	234	Bars	Nevada - Eureka	568502
9/7			232	235	Scrap	Ind	24914
			233	236	✓	✓	36459
			234	237	✓	✓	35036
9/15	Remelt		235	238	✓	✓	7172
			236	239	✓	✓	7289
			237	240	Bars	S. Alaska	1155
			238	241	✓	✓	166071
							432420

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
381 $\frac{1}{2}$	107 $\frac{1}{10}$	511 $\frac{1}{2}$	18			\$	\$	\$	\$
391 $\frac{1}{10}$	83 $\frac{1}{10}$	26 $\frac{1}{10}$	12			2 $\frac{30}{100}$ h.m.	Capital Loan; Denver, Colo		
422 $\frac{1}{10}$	117 $\frac{1}{10}$	461 $\frac{1}{10}$	18			7 $\frac{15}{100}$ h.m.	Gerkling & Slensker.		
461 $\frac{1}{10}$	105 $\frac{1}{10}$	494 $\frac{1}{10}$	18				Joster		
397 $\frac{1}{2}$	101 $\frac{1}{10}$	501 $\frac{1}{2}$	18				"		
452 $\frac{1}{10}$	190 $\frac{1}{10}$	358 $\frac{1}{10}$	16				"		
876 $\frac{1}{10}$	115 $\frac{1}{10}$	9 $\frac{1}{10}$	12				William Pickering; San Diego, Calif		
68 $\frac{1}{2}$	29 $\frac{1}{10}$	902 $\frac{1}{2}$	23				Marcel Creek Mng Co., Alaska		
997 $\frac{1}{4}$	1 $\frac{1}{2}$	1 $\frac{1}{4}$	0				Mrs Florence Adams; Pasadena, Calif		
997 $\frac{3}{4}$	1 $\frac{1}{10}$	1 $\frac{1}{4}$	0				Homestake		
865 $\frac{1}{2}$	49 $\frac{1}{10}$	385 $\frac{1}{2}$	21				"		
970 $\frac{1}{10}$	10 $\frac{1}{10}$	20 $\frac{1}{10}$	6			2 $\frac{30}{100}$ h.m.	Charlie B. Scott; Austin, Texas		
992 $\frac{1}{2}$	2 $\frac{1}{4}$	0 $\frac{1}{10}$	0				Copps Portland Co. Golden		
892 $\frac{1}{2}$	2 $\frac{1}{10}$	105 $\frac{1}{2}$	13				Homestake		
665 $\frac{1}{10}$	6 $\frac{1}{10}$	329 $\frac{1}{10}$	18			3 $\frac{80}{100}$ h.m.	Matosola		
854 $\frac{1}{10}$	1 $\frac{1}{10}$	145 $\frac{1}{10}$	13				"		
759 $\frac{1}{10}$	5 $\frac{1}{10}$	236 $\frac{1}{10}$	16			14 $\frac{30}{100}$ h.m.	"		
538 $\frac{1}{2}$	79 $\frac{1}{10}$	382 $\frac{1}{2}$	21				"		
543 $\frac{1}{10}$	71 $\frac{1}{10}$	386 $\frac{1}{10}$	21				J. A. Jansen & Co; Minn		
744 $\frac{1}{10}$	128 $\frac{1}{10}$	128 $\frac{1}{10}$	13				E. Lachman & Sons Co; Seattle		
900 $\frac{1}{10}$	0 $\frac{1}{10}$	100 $\frac{1}{10}$	0				Mrs Patricia Buckner; Denver		
872 $\frac{1}{10}$	125 $\frac{1}{10}$	3 $\frac{1}{10}$	12				Mrs Leo B. Andrews; New Orleans, La		
994 $\frac{1}{10}$	2 $\frac{1}{2}$	2 $\frac{1}{2}$	6				Robert B. Ray, Ind & Travel		
998 $\frac{1}{10}$	0 $\frac{1}{10}$	2 $\frac{1}{10}$	0				Carlin Gold Mng. Co.		
428 $\frac{1}{10}$	118 $\frac{1}{10}$	454 $\frac{1}{10}$	18			6 $\frac{80}{100}$ h.m.	C. F. I. Corporation; Petaluma, Calif		
412 $\frac{1}{10}$	108 $\frac{1}{10}$	480 $\frac{1}{10}$	18				Joster		
558 $\frac{1}{10}$	64 $\frac{1}{10}$	378 $\frac{1}{10}$	21				"		
984 $\frac{1}{2}$	8 $\frac{1}{10}$	7 $\frac{1}{2}$	6				London Erickson Co; Minn		
997 $\frac{1}{2}$	2 $\frac{1}{2}$	0 $\frac{1}{10}$	0				McKay Melt Co; Salt Lake		
998 $\frac{1}{2}$	1 $\frac{1}{2}$	0 $\frac{1}{10}$	0				Homestake		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 230500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
9/7			239	242	Scrap	Ind	113.74
			240	243	"	"	203.23
			241	244	"	"	247.91
			242	245	"	"	216.24
			243	246	Retort	Colo - Jeff	31.09
			244	247	"	" - Adams	37.50
			245	248	"	"	17.15
	L.B.		2	2	Grains Bar	Deposits August	50.58
	12. L.					Plus Coin	
	9/1/67		C-25	C-27	Coin	2-5.00 U.S.	
	"		C-27	C-29	"	1-2.50 "	.65
	"		C-28	C-30	"	1-50 Peso	133
4/8	"		C-26	C-28	Coin	1 - Austrian	2.10
	W.M. better		246	249	Scrap	76 - Foreign	11.01
	9/1/67					1 - Gold Max Medal	1.85
9/15	Rince		248	251	Scrap	Ind: Jewelry in C-28	1.85
			249	252	"	"	414.73
			250	253	"	"	33.96
9/15	Rince		251	254	8-Ret	Colo - Lunnison	68.44
			252	255	Scrap	Ind	466.59
			253	256	"	"	644.11
			254	257	"	"	859.32
			255	258	"	"	617.32
			256	259	"	"	366.23
			257	260	"	"	907.20
			258	261	"	"	469.88
			259	262	"	"	41.82
	S.B.		3	3	S.B.	"15" Grains #2	27.80
9/11	S.B.		2	2	S.B.	Dark & Light - 1st Q. day	300.7
9/15			260	263	Bars	S. Oak	3676.64
			261	264	"	"	1626.33

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE			
Gold	Silver	Base	Melt-ing	P and R.	Bar Chg.		Gold	Silver	Interest	Total
997 ¹⁰	1 ¹⁰	2 ¹⁰	0			\$	\$			\$
568 ¹⁰	80 ¹⁰	351 ¹⁰	21				Maborala			
412 ¹⁰	131 ¹⁰	457 ¹⁰	18			5 ³⁰ b.m.	S.W.S. Ref Co.			
458 ¹⁰	116 ¹⁰	426 ¹⁰	16				John Roberts Mfg.			
853 ¹⁰	141 ¹⁰	5 ¹⁰	12				J. L. Thorpe & Co.			
885 ¹⁰	110 ¹⁰	4 ¹⁰	12				Peckling & Shucker			
912 ¹⁰	80 ¹⁰	7 ¹⁰	12			2 ³⁰ b.m.	"			
826 ¹⁰	31 ¹⁰	143 ¹⁰	0				Supt			
900 ¹⁰	0 ¹⁰	100 ¹⁰	0				Dist Collector Pustams; Laredo, Tex			
849 ¹⁰	0 ¹⁰	101 ¹⁰	13				Mr. Harry Klein; Woodhous, N.Y			
984 ¹⁰	5 ¹⁰	10 ¹⁰	6				Mrs Karla Michackis, Stuberwille, Ohio			
891 ¹⁰	6	102 ¹⁰	0				Truister Pustams; Laredo,			
501 ¹⁰	99 ¹⁰	400 ¹⁰	0				W.W. Pustams; Laredo, Tex			
998 ¹⁰	1.8	0.0	0				Honestake			
830 ¹⁰	3 ¹⁰	167 ¹⁰	16			3 ⁰⁵ X hr	Maborala			
923 ¹⁰	0 ¹⁰	77 ¹⁰	13				"			
561 ¹⁰	150 ¹⁰	289 ¹⁰	18			2 ³⁰ X hr	Louis W. Spiegel; Buaga Park, Calif			
804 ¹⁰	133 ¹⁰	62 ¹⁰	13			2 ³⁰ X hr	Estate of J.C. Terushan; Humson, Colo.			
428 ¹⁰	115 ¹⁰	457 ¹⁰	18			8 ³⁰ b.m.	Joster			
382 ¹⁰	102 ¹⁰	515 ¹⁰	18				"			
391 ¹⁰	155 ¹⁰	453 ¹⁰	18				"			
400 ¹⁰	111 ¹⁰	488 ¹⁰	18			7 ⁵⁵ b.m.	"			
405 ¹⁰	125 ¹⁰	470 ¹⁰	18			6 ⁰⁵ b.m.	"			
351 ¹⁰	84 ¹⁰	564 ¹⁰	21				"			
410 ¹⁰	110 ¹⁰	479 ¹⁰	18			7 ⁵⁵ b.m.	"			
395 ¹⁰	129 ¹⁰	476 ¹⁰	18				"			
445 ¹⁰	112 ¹⁰	442 ¹⁰	0				Supt			
351 ¹⁰	86 ¹⁰	563 ¹⁰	0				"			
997 ¹⁰	2 ¹⁰	0 ¹⁰	0				Honestake			
996 ¹⁰	3 ¹⁰	0 ¹⁰	0				"			

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930590

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
9/15			262	265	Scrap	Ind.	12384
			263	266	✓	✓	823
			264	267	✓	✓	1581
			265	268	✓	✓	1400
			266	269	✓	✓	10485
			267	270	✓	✓	70261
			268	271	✓	✓	64735
	H.M.R.		C-29	C-31	Poin	1-20 Aero	64.066
	9/13/67					1-5 "	
	"		C-30	C-32	"	1-20 Granet	" 021
9/18			269	272	Bars	S. Black	514328
			270	273	Pl Scrap	Ind	7409
			271	274	"	"	19285
			272	275	"	"	7324
			273	276	"	"	70950
			274	277	"	"	5766
			275	278	"	"	2653
			276	279	Scrap	"	1088
			277	280	"	"	784
			278	281	Bars	Nevada-Eureka	61173
			279	282	Scrap	Ind	92608
			280	283	"	"	59386
			281	284	"	"	98290
			282	285	"	"	59018
9/21			283	286	Rebut	Mont. Meagher	456
			284	287	Scrap	Ind	1202
			285	288	Bars	S. Black	592377
			286	289	Pl Scrap	Ind	41690
			287	290	✓	✓	13147
			288	291	✓	✓	25575
			289	292	Scrap	✓	56183

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 572 ⁰	48 ⁰	380 ⁰	21			\$	\$	\$	\$
✓ 309 1/2	112 ⁰	578 1/2	21			2 ³⁰ km.	Kischner's Kaynor & Co.; Minn., Minn.		
✓ 533 1/2	82 ⁰	384 1/2	21				Samuel Schwanen, Chicago, Ill.		
✓ 526 1/2	105 ⁰	368 1/2	21				Peters Jewelry Store, Alamosa, Colo.		
✓ 399 1/2	86 ⁰	514 1/2	18				Argenzio Bros, Denver		
✓ 402 ⁰	106 ⁰	492 ⁰	18				Josten		
✓ 396 1/2	75 ⁰	528 1/2	18				"		
✓ 900 ⁰	0 ⁰	100 ⁰	13				Mr. Jerry Jackson, Quon Lake, Mich.		
✓ 899 ⁰	0 ⁰	101 ⁰	13				Mr. Peter F. Laband, Guadalajara, Mex.		
✓ 998.3	1 ⁷	0 ¹⁰	0				Hornestake		
✓ 941 ¹⁰	4 ¹⁰	55 ¹⁰	13				Motorola		
✓ 932 1/2	8 ¹⁰	59 1/2	13				"		
✓ 778 1/2	9 ¹⁰	212 1/2	16			2 ³⁰ km.	"		
✓ 940 ¹⁰	4 ¹⁰	56 ¹⁰	13				"		
✓ 944 ¹⁰	2 ¹⁰	54 ¹⁰	13				"		
✓ 994 1/2	1 ¹⁰	4 1/2	6				"		
✓ 559 ⁰	77 ¹⁰	364 ¹⁰	21				Anthony A. Makovic; Denver		
✓ 528 ¹⁰	200 ¹⁰	272 ¹⁰	18			2 ³⁰ km.	Petersen Jewelry; Boulder		
✓ 992.1	2 ¹⁶	5 ¹³	6				Carline		
✓ 407 1/2	109 ¹⁰	483 1/2	18				Josten		
✓ 411 ⁰	108 ¹⁰	481 ¹⁰	18			8 ³⁰ km.	"		
✓ 378 1/2	127 ¹⁰	494 1/2	18				"		
✓ 398 1/2	110 ¹⁰	491 1/2	18				"		
✓ 850 ⁰	146 ¹⁰	4 ¹⁰	12				Robert J. Williamson; Belt, Mont.		
✓ 233 1/2	55 ¹⁰	711 1/2	21				Andrey J. Caldwell; Denver		
✓ 998.6	1 ⁴	0 ¹⁰	0				Hornestake		
✓ 924 1/2	7 ¹⁰	68 1/2	13			6 ⁰⁵ km.	Motorola		
✓ 993 ¹⁰	0 ¹⁰	7 ¹⁰	6				"		
✓ 930 1/2	6 ¹⁰	63 1/2	13			4 ⁵⁵ km.	"		
✓ 865 ⁰	156 ¹⁰	479 ¹⁰	18			11 ³⁰ km.	John Roberts Mfg.		

REGISTER OF ASSAYS,

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
9/21			290	293	Pl Scrap	Attak Ind	216.12
			291	294	Scrap	"	11.42
			292	295	✓	"	891.89
			293	296	✓	"	853.91
			294	297	✓	"	320.81
			295	298	✓	"	1 012.49
			296	299	✓	"	995.40
9/22			297	300	Bars	S. Mak	8312.17
			298	301	Pl Scrap	Ind	234.13
			299	302	"	"	42.73
			300	303	"	"	524.04
			301	304	"	"	317.75
			302	305	Retent	"	18.72
			303	306	Scrap	"	82.76
9/26			304	307	✓	"	14.45
	Rement 9/28		305	308	Ret	Quay. Polo	Re-431.33
			306	309	Bars	New-Eureka	436.30
			307	310	Retent	Colo-Moffat	741.57
	9/28		308	311	Bars	S. Mak	714
	✓		309	312	✓	✓	1690.64
	✓		310	313	Scrap	Ind	7464.44
	✓		311	314	✓	"	150.26
			312	315	Mut Coin	114 Mut. Dollars.	148.73
			313	316	✓	✓	94.91
9/28			314	317	Scrap	Halves; Quarters; Minors	2073.06
			315	318	✓	Ind	464.62
			316	319	✓	"	620.65
			317	320	✓	"	233.23
10/2			318	321	Bars	S. Mak	344
			319	322	Scrap	Ind	7569.60
							32.56

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 993 ¹⁰	0 ¹⁰	7 ¹⁰	6			\$	\$		\$
✓ 837 ¹²	93 ¹⁰	69 ¹²	13		2 ³⁰ h.m.		Bendix Corp; Kansas City, Mo.		
✓ 412 ¹⁰	123 ¹⁰	465 ¹⁰	18				Stonewall Enterprises; Los Alamos, N.M.		
✓ 424 ¹⁰	117 ¹⁰	459 ¹⁰	18				Joaten		
✓ 420 ¹⁰	112 ¹⁰	468 ¹⁰	18		6 ⁰⁵ h.m.		"		
✓ 412 ¹²	120 ¹⁰	467 ¹²	18				"		
✓ 404 ¹²	98 ¹⁰	497 ¹²	18				"		
✓ 997.5	2 ¹²	0 ¹⁰	0				Hamestake		
✓ 151 ¹⁰	7 ¹⁰	442 ¹⁰	21		3 ⁵⁰ h.m.		Motorola		
✓ 979 ¹⁰	2 ¹⁰	19 ¹⁰	6				"		
✓ 941 ¹⁰	7 ¹⁰	52 ¹⁰	13				"		
✓ 893 ¹⁰	7 ¹⁰	100 ¹⁰	13		5 ³⁰ h.m.		"		
✓ 774 ¹⁰	223 ¹⁰	3 ¹⁰	12				A.W. Jones; Garden Valley, Idaho		
✓ 527 ¹²	83 ¹⁰	389 ¹²	21				Matt's Jewelers; San Diego, Calif		
✓ 464 ¹⁰	72 ¹⁰	474 ¹⁰	18				Alexander Jewelers, Scottsdale, Ariz		
✓ 476 ¹⁰	156 ¹⁰	368 ¹⁰	16				Idaho.		
✓ 991.7	2 ¹⁸	5 ¹⁵	6				Cashin		
✓ 945 ¹⁰	54 ¹⁰	1 ¹⁰	12		2 ³⁰ h.m.		Orvie W. Zimmerman; Craig, Colo.		
✓ 998 ¹⁴	1 ³⁴	0 ¹⁰	0				Hamestake		
✓ 997 ³⁴	2 ¹⁴	0 ¹⁰	0				"		
✓ 859 ¹⁰	2 ¹⁰	138 ¹⁰	13				Motorola		
✓ 453 ¹⁰	72 ¹⁰	475 ¹⁰	18		3 ⁰⁵ h.m.		Fashion Craft Mfg Co; Buffalo, N.Y.		
✓ 0 ¹⁰	898 ¹²	101 ¹²	0				Supt		
✓ 0 ¹⁰	887 ¹⁰	113 ¹⁰	0				"		
✓ 422 ¹²	112 ¹⁰	465 ¹²	18		8 ³⁰ h.m.		Joaten		
✓ 374 ¹⁰	102 ¹⁰	524 ¹⁰	18				"		
✓ 414 ¹⁰	105 ¹⁰	481 ¹⁰	18				"		
✓ 486 ¹⁰	124 ¹⁰	390 ¹⁰	16				Whight Ellsworths; Rapid City, S.D.		
✓ 997.3	2 ¹⁷	0 ¹⁰	0				Hamestake		
✓ 469 ¹⁰	111 ¹⁰	420 ¹⁰	16				Roy S. Utter; Greeley, Colo.		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 340500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
10/2			320	323	Scrap	Ind	5259
			321	324	✓	✓	1759
			322	325	✓	✓	37936
			323	326	✓	✓	5020
			324	327	✓	✓	10345
			325	328	✓	✓	6379
			326	329	✓	✓	8973
			327	330	✓	✓	8066
10/3			328	331	✓	✓	13689
			329	332	✓	✓	58348
			330	333	✓	✓	52078
			331	334	✓	✓	2142
			332	335	Retort	Mont.	2187
	10/5		333	336	Scrap	Ind	14166
			334	337	Bars	Nevada-Eureka	69538
	W.M. Fisher		C-31	C-33	Coin	3-Austrian	0233
	9/29/67		C-32	C-34	"	6-Mex Km Paris	239
	✓						
10/5			335	338	Bars	J. Klak	169729
			336	339	✓	✓	420601
			337	340	Scrap	Ind	32607
			338	341	✓	✓	23562
			339	342	✓	"	4379
			340	343	✓	"	7042
			341	344	✓	"	7144
			342	345	✓	"	27721
			343	346	✓	"	49679
			344	347	✓	"	48208
			345	348	Retort	Calo-Adams	9842
			346	349	Scrap	Ind	46373
			347	350	✓	"	41334

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
894 1/2	310	102 1/2	13			680 h.m.	Motorsola	\$	\$
994 10	110	510	6				"		
993 10	310	410	6				"		
880 1/2	410	115 1/2	13			680 h.m.	"		
775 1/2	610	218 1/2	16				"		
964 10	010	4610	6				"		
994 1/2	310	2 1/2	6				"		
994 1/2	310	2 1/2	6				"		
548 10	810	371 10	21				S.W. Texas Precious Metals.		
399 1/2	10610	494 1/2	18				Joeten		
426 1/2	11410	459 1/2	18			905 h.m.	"		
548 10	9210	36010	21				Raymond Martinez; Phoenix		
917 1/2	7810	4 1/2	12				Mrs G.K. Scharf; Blue Lodge; Mont		
972 10	110	2710	6			380 h.m.	Cress Porcelain Co; Golden, Colo		
990 5	310	615	6				Carlin Mining Co.		
985 10	010	1510	6				Adolph J. Abenle; Lake Charles, La.		
900 10	010	10010	13				Ranleigh H. Pardo; Fayetteville, Ark		
997 10	310	010	0				Homestead		
997 3/4	2 1/4	010	0				"		
582 1/2	9010	327 1/2	18				S.W. Smet & Ref Co.		
414 10	11810	46810	18				F.L. Sharpe & Co. Leadwood, S.H.		
978 10	010	2210	6				Motorsola		
986 10	010	1410	6				"		
415 10	17610	40910	16			230 h.m.	S.W. Smet & Ref Co.		
392 1/2	11010	497 1/2	18			530 h.m.	John Robert Mfg Co.		
402 10	11510	48310	18				"	"	"
398 10	11510	48710	18				"	"	"
872 10	11810	1010	12				Bailey Gravel Co;		
368 1/2	9910	532 1/2	18				Joeten		
420 1/2	11310	466 1/2	18			7 1/2 h.m.	"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 250500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
10/5			348	351	Scrap	Ind	594.40
			349	352	"	"	1020.45
10/9			350	353	Bars	S. Blak	7264.4
			351	354	Scrap	Ind	39.24
			352	355	✓	✓	25.6
			353	356	✓	✓	753.1
			354	357	✓	✓	92.91
			355	358	✓	✓	156.2
			356	359	✓	✓	141.43
			357	360	✓	✓	74.41
			358	361	✓	✓	168.45
			359	362	✓	✓	77.3
10/10			360	363	✓	✓	253.7
			361	364	Retort	Colo - Adams	327.9
			362	365	✓	- - Jeff	18.86
			363	366	Bars	Nevada - Enoka	565.24
			364	367	Scrap	Ind	34.93
			365	368	✓	✓	51.86
			3	3	Trans B	Trans Bar Sept - Plus Coin	362.7
10/11			366	369	Scrap	Ind	2.92
			367	370	Bars	S. Blak	1716.77
			368	371	"	"	4600.87
			369	372	Scrap	Ind	29.55
			370	373	Retort	Colo - Moffat	25.6
			371	374	Scrap	Ind	199.6
			372	375	"	"	22.16
			373	376	"	"	275.25
			374	377	"	"	547.77
			375	378	"	"	162.70
			376	379	"	"	190.17

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
397 ¹⁰	54 ¹⁰	54 ¹⁰	18			\$	\$		\$
398 ²	106 ¹⁰	496 ¹⁰	18				Justin		
997.8	2.2	0.0	0				"		
990 ^{1/2}	5 ¹⁰	4 ^{1/2}	6				Hametake		
984 ^{1/2}	9 ¹⁰	6 ^{1/2}	6				Motorola		
990 ¹⁰	1 ¹⁰	9 ¹⁰	6				"		
990 ¹⁰	1 ¹⁰	9 ¹⁰	6				"		
988 ^{1/2}	1 ¹⁰	10 ^{1/2}	6				"		
985 ²	0 ¹⁰	15 ¹⁰	6				"		
962 ^{1/2}	9 ¹⁰	28 ^{1/2}	6			2 ³⁰ h.m.	"		
974 ^{1/2}	1 ¹⁰	24 ^{1/2}	6				"		
399 ^{1/2}	192 ¹⁰	408 ^{1/2}	16			2 ³⁰ h.m.	Paul Neil; Corvallis, Ore.		
412 ^{1/2}	107 ¹⁰	420 ^{1/2}	16				Sisto Obregan; Houston, Tex		
885 ^{1/2}	107 ¹⁰	7 ^{1/2}	12				Kerkling & Hensker		
859 ²	137 ¹⁰	4 ¹⁰	12				"		
992.7	3 ^{1/2}	4 ^{1/2}	6				Carlin		
434 ¹⁰	125 ¹⁰	441 ¹⁰	16			2 ³⁰ h.m.	Norman Barrett, Mfg Jewellers; Salt Lake		
531 ¹⁰	151 ¹⁰	318 ¹⁰	18			2 ³⁰ h.m.	Louis W. Spiegel; Conger Park, Calif		
769 ¹⁰	97 ¹⁰	134 ¹⁰	0				Supt		
414 ¹⁰	471 ¹⁰	115 ¹⁰	7			2 ³⁰ h.m.	Neil Rental Lab; Denver.		
996 ^{1/2}	3 ^{1/2}	0 ¹⁰	0				Hametake		
998 ^{1/2}	1 ^{1/2}	0 ¹⁰	0				"		
546 ¹⁰	78 ¹⁰	376 ¹⁰	21				Finchmer's Kaynor Diamond; Mon, Minn		
944 ¹⁰	53 ¹⁰	3 ¹⁰	12			2 ³⁰ h.m.	Orrie W. Zimmerman; Craig, Colo		
663 ^{1/2}	149 ¹⁰	187 ^{1/2}	16				Mr. Ross A. Penny; Omaha, Neb		
353 ^{1/2}	216 ¹⁰	430 ^{1/2}	16			2 ³⁰ h.m.	E. O. Jewelry Service; Colo Spgs, Colo		
946 ¹⁰	3 ¹⁰	51 ¹⁰	13				Motorola		
946 ¹⁰	3 ¹⁰	51 ¹⁰	13				"		
896 ¹⁰	0 ¹⁰	104 ¹⁰	13				"		
991 ^{1/2}	2 ¹⁰	6 ^{1/2}	6				"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930600

DATE 1967			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
10/11			377	380	Scrap	Ind	844.48
	SB		4	4	S. B	"K" Grain's bar #3.	38.16
10/12			378	381	Scrap	Ind	370.55
			379	382	✓	✓	610.62
			380	383	✓	✓	441.31
			381	384	✓	✓	988.11
			382	385	✓	✓	996.15
10/13	10/16		383	386	✓	✓	145.64
			384	387	Bars	L. H. H. H.	2464.27
			385	388	✓	✓	3375.74
			386	389	Scrap	Ind	538.67
			387	390	✓	✓	493.83
			388	391	✓	✓	542.01
			389	392	✓	✓	297.55
			390	393	✓	✓	59.98
			391	394	✓	✓	173.15
			392	395	✓	✓	65.19
			393	396	✓	✓	17.18
10/12	10/11		394	397	Retest	Adams	266.9
			395	398	"	"	32.98
10/13			396	399	Bars	Nevada	6777.42
			397	400	"	Ind	228.93
10/16			398	401	Scrap	✓	498.09
			399	402	"	✓	303.60
			400	403	"	✓	673.84
	10/19		401	404	Bars	So Dakota	3440.79
			402	405	"	"	3256.18
10/17			403	406	Scrap	Ind	498.40
			404	407	✓	✓	1616.0
			405	408	✓	✓	86.26

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 951°	21°	471°		6		\$	\$ Motorola	\$	\$
✓ 491 1/2	941°	424 1/2		0			Supt		
✓ 393°	98°	5091°		18			Josten		
✓ 379°	1021°	5191°		18			"		
✓ 413°	1111°	4761°		18		755 h.m.	"		
✓ 394 1/4	104°	501 1/4		18			"		
✓ 385 1/4	144°	470 1/2		18			"		
✓ 402 1/2	79°	518 1/2		18			Willbor Posing Co. Inc, Buffalo, N. Y.		
✓ 997 1/2	2 1/2	0°		0			Homestake		
✓ 997 1/4	23/4	0°		0			"		
✓ 945°	7°	48°		12			Motorola		
✓ 925°	8°	57°		13			"		
✓ 946°	7°	47°		12			"		
✓ 945 1/2	7°	47 1/2		12			"		
✓ 983 1/2	3°	13 1/2		6			"		
✓ 996°	0°	4°		0			"		
✓ 947°	3°	50°		12		230 x ln	"		
✓ 981 1/2	1°	17 1/2		6		230 x ln	"		
✓ 890°	87°	23°		12		230 x ln			Kirkling & Hensley, Lockwood
✓ 883 1/2	110°	6 1/2		12			"		"
✓ 995.3	2.7	2.0		0			Carlisle Gold Mining Co., Elko, Nev		
✓ 525 1/2	122°	352 1/2		21			South West Precious Metals, San Antonio, Tex		
✓ 403 1/2	113°	473 1/2		18		830 x ln	Josten's Inc.		
✓ 418 1/2	113°	468 1/2		18		605 x ln	"		
✓ 398 1/2	102°	499 1/2		18			"		
✓ 997 3/4	2 1/4	0°		0			Homestake		
✓ 998°	2°	0°		0			"		
✓ 909°	2°	89°		13			Motorola		
✓ 994°	0°	6°		6			"		
✓ 993°	0°	7°		6			"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 220800

DATE 1967			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
10/17			406	409	Scrap	Ind	45.58
			407	410	✓	✓	354.07
			408	411	✓	✓	507.40
			409	412	✓	✓	96.41
			410	413	✓	✓	105.46
	10/20		411	414	✓	✓	133.19
			412	415	✓	✓	134.26
			413	416	Retort	Montana	1.88
	10/24		414	417	Scrap	Ind	697.39
10/18	10/20		415	418	✓	✓	418.90
			416	419	✓	✓	423.86
			417	420	✓	✓	420.17
	10/23		418	421	Bars	So Dakota	4596.63
			419	422	Retort	Idaho	6.59
			420	423	Scrap	Ind	808.15
10/19	10/23		421	424	Retort	Adams	222.7
			422	425	"	Jefferson	17.81
			423	426	Scrap	Ind	801.29
			424	427	"	✓	442.57
10/20	D.M. Letter 10/18/67		C-33	C-35	Ant. Medals	1-John F Kennedy } medals 1-El Chamezgal } coins	3.43
	"		C-34	C-36	Coins	1-50 Peso 1-20 " 1-200 Mex	2.39
	"		C-35	C-37	"	2-2 1/2 Peso 2-2 " Mex	0.23
	10/24		425	428	Bars	Yucata	7195.46
			426	429	Scrap	Ind	15.40
	10/25		427	430	"	✓	134.61
10/20	10/31		428	431	"	✓	567.21
10/23	10/25		429	432	Bars	South Dakota	1634.77
			430	433	✓	✓ ✓	4461.81
	10/27		431	434	Scrap	Ind	912.61
			432	435	✓	✓	479.10

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 913 ⁰	0 ⁰	87 ⁰	13			\$ 2 ³⁰ x Lm	\$ Motorola	\$	\$
✓ 910 1/2	3 ⁰	86 1/2	13				"		
✓ 910 ⁰	3 ⁰	87 ⁰	13				"		
✓ 970 1/2	2 ⁰	27 1/2	6				"		
✓ 984 ⁰	1 ⁰	15 ⁰	6				"		
✓ 408 ⁰	94 ⁰	498 ⁰	18			3 ³⁰ x Lm	Wellbar Casting Co, Inc, Buffalo, N.Y.		
✓ 423 1/2	67 ⁰	509 1/2	18			3 ³⁰ x Lm	" "	" "	" "
✓ 841 1/2	145 ⁰	13 1/2	12						
✓ 396 ⁰	103 ⁰	501 ⁰	18			10 ⁵⁵ x Lm	John Roberts Mfg. Norman, Okla		
✓ 419 ⁰	110 ⁰	471 ⁰	18			7 ⁵⁵ x Lm	Losten's Inc.		
✓ 416 ⁰	110 ⁰	474 ⁰	18			7 ⁵⁵ x Lm	" "		
✓ 400 1/2	100 ⁰	499 1/2	18				" "		
✓ 997 3/4	2 1/4	0 ⁰	0				Homestake		
✓ 659 1/2	319 ⁰	21 1/2	12				Wendell Morse, Grindorf, Idaho		
✓ 391 1/2	67 ⁰	541 1/2	18				Gold Exchange O.C. Tarnover, Salt Lake City, Utah		
✓ 865 1/2	107 ⁰	27 1/2	12			2 ³⁰ x Lm	Kierkling & Sheskie		
✓ 825 ⁰	156 ⁰	19 ⁰	12				" "		
✓ 400 ⁰	107 ⁰	493 ⁰	18				Losten's Inc.		
✓ 419 ⁰	110 ⁰	471 ⁰	18			8 ³⁰ x Lm	" "		
Remelted and given: Deposit #445; Assay #448							D.D. of Customs Houston - Tex.		
✓ 899 ⁰	0 ⁰	101 ⁰	13				George Donald M ^{rs} Daniel Hamilton - Ohio		
✓ 899 ⁰	0 ⁰	101 ⁰	13				John A. Sigrist Houston - Tex		
✓ 996.4	1.7	1.9	0				Carlin Gold Mining Co, Eureka, Nev.		
✓ 531 ⁰	111 ⁰	358 ⁰	21				James B. Andrews, Houston, Tex.		
✓ 653 ⁰	153 ⁰	194 ⁰	16			3 ⁰⁵ x Lm	Motorola		
✓ 914 1/2	16 ⁰	69 1/2	13			49.34 Bushm ^x Chg 8 ³⁰ x Lm	Coors Porcelain Co, Golden Colo		
✓ 997 1/4	2 3/4	0 ⁰	0				Homestake		
✓ 998 1/4	1 3/4	0 ⁰	0				✓		
✓ 907 ⁰	6 ⁰	87 ⁰	13				Motorola		
✓ 991 1/2	2 ⁰	6 1/2	6				✓		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE 1967			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
10/23	10/24		433	436	Scrap	Ind	54300
			434	437	✓	✓	402.5
			435	438	✓	✓	4460
			436	439	✓	✓	383.83
			437	440	✓	✓	34.57
	11/1		438	441	✓	✓	482.31
			439	442	✓	✓	483.28
	10/27		440	443	✓	✓	101.98
10/24	10/30		441	444	✓	✓	103.45
			442	445	✓	✓	186.07
			443	446	Retort	Idaho, Boise	49.45
			444	447	Scrap	Ind	238.22
	DM Letter 10/18/67		445	448	Medals	1- John F. Kennedy 1- El Chamizal } Medallions	19.77
10/25			446	449	Scrap	Ind	202.9
10/25			447	450	Retort	Colo - Auray	3.41
	10/30		448	451	Scrap	Ind	18.62
			449	452	✓	✓	384.77
	10/30		450	453	✓	✓	594.29
10/25	10/27		451	454	ag Coin	271 1/2 \$ 577 1/4 \$ 890 1/10 \$	657.62
			452	455	ag Coin	22 \$	915.87
			MCD-4	MCD-4	mint Coin	158 mutilated clad 1/4 & 1/10 \$	281.89
			MCH-4	MCH-4	mint Coin	17 mutilated clad 1/2 \$	18.42
			453	456	Bars	So Dakota	22.74
			454	457	Scrap	Ind	6.15
			455	458	✓	✓	5.08430
			456	459	✓	✓	41.50
			457	460	✓	✓	79.02
			458	461	✓	✓	39.02
10/27	10/1		459	462	✓	✓	168.57
10/30	11/1		460	463	Bars	So Dakota	208.23
							9.59
							2189.50

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 929 ⁰	3 ⁰	68 ⁰		13		\$	\$ Motorola	\$	\$
✓ 846 ⁰	6 ⁰	148 ⁰		13		5 ³⁰ x ¹ / ₂ in	✓		
✓ 918 ¹ / ₂	5 ⁰	16 ¹ / ₂		6			✓		
✓ 847 ¹ / ₂	5 ⁰	147 ¹ / ₂		13		5 ³⁰ x ¹ / ₂ in	✓		
✓ 936 ¹ / ₂	0 ⁰	63 ¹ / ₂		13		2 ³⁰ x ¹ / ₂ in	✓		
✓ 540 ¹ / ₂	9 ⁰	450 ¹ / ₂		23		6 ⁸⁰ x ¹ / ₂ in	✓		
✓ 932 ¹ / ₂	0 ⁰	67 ¹ / ₂		13			✓		
✓ 996 ⁰	3 ⁰	1 ⁰		0			✓		
✓ 550 ¹ / ₂	74 ⁰	375 ¹ / ₂		21			Louis W. Spiegel, Canoga Park, Cal.		
✓ 448 ¹ / ₂	126 ⁰	425 ¹ / ₂		16			J. L. Thorpe & Co. Deadwood, S. Dak.		
✓ 770 ¹ / ₂	225 ⁰	4 ¹ / ₂		12			A. W. Isaac, Garden Valley, Idaho		
✓ 478 ⁰	81 ⁰	441 ⁰		16		2 ³⁰ x ¹ / ₂ in	Atlas Jewelry Co. Inc., Houston, Tex		
✓ 894 ⁰	25 ⁰	81 ⁰		0			D. D. of Customs Houston, Tex		
✓ 572 ⁰	37 ⁰	391 ⁰		21			Jacobson Jewelry, Omaha, Neb.		
✓ 306 ⁰	111 ⁰	583 ⁰		21			Idarado Mining, Duran, Colo		
✓ 414 ¹ / ₂	110 ⁰	475 ¹ / ₂		18		9 ⁸⁰ x ¹ / ₂ in	Lortene, Inc.		
✓ 385 ¹ / ₂	99 ⁰	515 ¹ / ₂		18			"	"	
✓ 389 ⁰	110 ⁰	501 ⁰		18			"	"	
✓ 0 ⁰	869 ¹ / ₄	130 ³ / ₄		0			Supt.		
✓ 0 ⁰	908 ¹ / ₄	91 ³ / ₄		0			✓		
							Supt.		(Value 30.92)
							✓		(Value 8.22)
✓ 997.3	2.7	0.0		0			Homestake		
✓ 991 ¹ / ₂	0 ⁰	8 ¹ / ₂		6			Motorola, Phoenix, Ariz		
✓ 993 ¹ / ₂	0 ⁰	6 ¹ / ₂		6			"	"	
✓ 977 ⁰	0 ⁰	23 ⁰		6		2 ³⁰ x ¹ / ₂ in	"	"	
✓ 985 ⁰	1 ⁰	14 ⁰		6			"	"	
✓ 966 ⁰	2 ⁰	32 ⁰		6			"	"	
✓ 324 ¹ / ₂	98 ⁰	577 ¹ / ₂		21			P. J. Patterson, Shawnee Mission, Kansas		
✓ 997 ⁰	3 ⁰	0 ⁰		0			Homestake		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930000

DATE 1967

NUMBER

MODE
OF
PAYMENT

DESCRIPTION

WEIGHT
AFTER
MELTING

Received

Reported

Hour

Receipt

Assay

11/30

11/2

461

464

Bars

South Dakota

415331

10/31

462

465

Scrap

Ind

801.66

463

466

✓

✓

1021.60

464

467

✓

✓

884.14

465

468

✓

✓

574.14

466

469

✓

✓

532.29

11/3

467

470

✓

✓

316.98

468

471

✓

✓

221.13

11/1

469

472

✓

✓

24.68

470

473

Bars

So Dakota

6356.93

11/8

471

474

Scrap

Ind

548.71

472

475

✓

✓

535.92

473

476

✓

✓

18.31

474

477

✓

✓

161.85

475

478

✓

✓

550.75

476

479

✓

✓

268.17

477

480

✓

✓

463.72

478

481

✓

✓

413.31

479

482

✓

✓

463.84

480

483

✓

✓

445.25

481

484

✓

✓

709.31

482

485

✓

✓

195.28

11/2

11/14

483

486

✓

✓

161.34

11/3

484

487

✓

✓

835.89

485

488

✓

✓

308.17

486

489

✓

✓

639.40

487

490

✓

✓

488.27

GB

GB 4

GB 4

Grain
Bar

Grain Act Dupont
C-31, 32, 34, 35

29.00

11/14

488

491

Scrap

Ind

13.42

11/6

489

492

Bars

So Dakota

2 137.56

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 998 °	2 °	0 °	0			\$	\$ Homestake	\$	\$
✓ 394 °	145 °	461 °	18				Sartin's		
✓ 402 °	119 °	479 °	18				"		
✓ 430 ½	93 °	476 ½	18				"		
✓ 421 °	107 °	472 °	18			905 X Lm	"		
✓ 411 ½	131 °	457 ½	18			830 X Lm	"		
✓ 398 ½	103 °	498 ½	18			680 X Lm	John Roberts Mfg Norman, Okla		
✓ 376 °	159 °	465 °	18			530 X Lm	" " " "		
✓ 458 ½	105 °	436 ½	16			230 X Lm	Star Jewelry, Houston, Tex		
✓ 997.7	2.3	0.0	0				Homestake		
✓ 894 °	4 °	102 °	13				Motorola Phoenix Ariz		
✓ 992 ¾	1 °	6 ¾	6				"		
✓ 880 °	5 °	115 °	13			230 X Lm	"		
✓ 891 ½	2 °	106 ½	13				"		
✓ 901 ½	3 °	95 ½	13				"		
✓ 852 ¾	3 °	144 ¾	13			455 X Lm	"		
✓ 951 °	3 °	46 °	6			605 X Lm	"		
✓ 879 ½	3 °	117 ½	13				"		
✓ 481 ¾	9 °	509 ¾	18			905 X Lm	"		
✓ 894 ½	4 °	101 ½	13				"		
✓ 949 °	2 °	49 °	12				"		
✓ 400 ½	80 °	519 ½	18				Willar Casting Co Inc Buffalo, N.Y		
✓ 474 ½	69 °	456 ½	18			380 X Lm	Jackson Craft Mfg Co Inc " (Rem)		
✓ 333 °	104 °	563 °	21				Sartin's Inc.		
✓ 409 °	134 °	457 °	18			605 X Lm	"		
✓ 398 ½	107 °	494 ½	18				"		
✓ 402 °	105 °	493 °	18				"		
✓ 699 °	120 °	181 °	0				Supt		
✓ 717 ½	133	149 ½	13				Kenneth F Shore, D.P.S. Denver, Colo		
✓ 995 ¾	4 ¼	0 °	0				Homestake		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930000

DATE 1967			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
11/6	11/14		490	493	Bars	So. Dakota	3 775 35
			491	494	Scrap	Ind	10 61
			492	495	✓	✓	44 63
			493	496	✓	✓	35 29
			494	497	✓	✓	184 29
			495	498	✓	✓	330 95
			496	499	✓	✓	74 18
			497	500	✓	✓	144 08
			498	501	✓	✓	243 66
			499	502	✓	✓	508 36
11/7	11/14		500	503	✓	✓	40 68
11/8			501	504	Bar	✓	21 32
			502	505	"		5 524 43
			503	506	Scrap	Ind	137 20
			504	507	✓	✓	509 80
			505	508	✓	✓	59 39
	11/15	S.B.	5	5	S.B. 5	From "K" - Series 4	36 27
11/9			506	509	Scrap	Ind	450 75
			507	510	✓	✓	872 06
			508	511	✓	✓	989 00
11/13	11/17		509	512	Retort	Jefferson	42 99
			510	513	✓	Adams	31 88
			511	514	Scrap	Ind	13 18
			512	515	Bars	So. Dakota	2 536 69
			513	516	✓	✓ ✓	2 904 13
			514	517	✓	✓ ✓	2 099 87
			515	518	Scrap	Ind	28 01
			516	519	"	✓	40 94
	11/21		517	520	✓	✓	135 74
	11/20		518	521	Scrap	Ind	413 80

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓997 $\frac{3}{4}$	2 $\frac{1}{4}$	0 °	0			\$	\$	\$	\$
✓296 °	83 °	621 °	21				Homestake		
✓491 $\frac{1}{2}$	100 °	408 $\frac{1}{2}$	16			2 ³⁰ x Lm	Samuel Schmaran, Chicago Ill		
✓51 $\frac{1}{2}$	33 °	215 $\frac{1}{2}$	16			2 ³⁰ x Lm	Louis W. Spiegel, Canoga Park, Cal		
✓528 $\frac{1}{2}$	83 °	388 $\frac{1}{2}$	21				Motorola Scottsdale, Ariz		
✓54 $\frac{1}{2}$	206 °	229 $\frac{1}{2}$	16				Southeast Tex Perc. Mnt. San Antonio, Tex		
✓452 °	145 °	403 °	16			2 ³⁰ x Lm	W.C. Sheffer Pen Co, Ft Windsor, Iowa		
✓404 °	78 °	518 °	18				Southeast Smelter & Ref. Dallas, Tex		
✓554 °	95 °	351 °	21				Wilbar Casting Co, Buffalo, N.Y.		
✓401 °	110 °	489 °	18				Southeast Smelt. & Ref. Dallas, Tex		
✓519 $\frac{1}{2}$	79 °	401 $\frac{1}{2}$	21				John Robert Mfg., Norman, Okla		
✓228 $\frac{1}{2}$	548 °	223 $\frac{1}{2}$	7				Star Jewelry Co - Houston, Tex		
✓997.2	2.8	0.0	0				William Hannenberg, Portland, Ore		
✓564 $\frac{1}{2}$	81 °	354 $\frac{1}{2}$	21				Homestake		
✓397 °	111 °	492 °	18				Isotini Inc		
✓567 $\frac{1}{2}$	28 °	404 $\frac{1}{2}$	21				"		
✓480 °	94 °	426 °	0				Kirschner's Raynor Deamon Co. Mer., Mer.		
✓395 $\frac{1}{2}$	109 °	495 $\frac{1}{2}$	18				Supt.		
✓394 °	101 °	505 °	18				Isotini Inc		
✓398 °	128 °	474 °	18				"		
✓856 °	139 °	5 °	12				"		
✓881 °	113 °	6 °	12				Kirkling & Alenker, Lakewood, Colo		
✓362 $\frac{1}{2}$	191 °	446 $\frac{1}{2}$	16				"		
✓998 $\frac{1}{2}$	1 $\frac{1}{2}$	0 °	0				Heelyer Jewelers, Chariton, Iowa		
✓997 $\frac{1}{2}$	2 $\frac{1}{2}$	0 °	0				Homestake		
✓998 $\frac{1}{2}$	1 $\frac{1}{2}$	0 °	0				"		
✓408 °	108 °	484 °	18				"		
✓435 °	131 °	434 °	16				W.H. Miller, Denver, Colo.		
✓387 °	99 °	514 °	18				Midtown Mfg Jewelers Inc, Salt Lake City, Utah		
✓398 $\frac{1}{2}$	111 °	490 $\frac{1}{2}$	18				4 ⁵⁵ x Lm John Robert Mfg Co Norman, Okla		
							7 ⁵⁵ x Lm John Robert Mfg., Norman, Okla		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 936500

DATE 1967			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
11/13	11/20		519	522	Retort	Adams	93.57 ✓
			520	523	Scrap	Ind	61.44 ✓
			521	524	✓	✓	246.57 ✓
			522	525	Gr & Nugs.	Alaska	29.76 ✓
			523	526	Scrap	Ind	24.16 ✓
11/14			524	527	✓	✓	773.50 ✓
			525	528	✓	✓	518.46 ✓
			526	529	✓	✓	133.74 ✓
			527	530	✓	✓	178.15 ✓
	11/22		528	531	✓	✓	503.47 ✓
			529	532	✓	✓	162.44 ✓
			530	533	✓	✓	3.54 ✓
	11/22		531	534	✓	✓	72.16 ✓
			532	535	✓	✓	130.17 ✓
			533	536	✓	✓	1.75 ✓
	11/21		534	537	✓	✓	427.35 ✓
			535	538	✓	✓	504.30 ✓
11/14			536	539	Scrap	Ind	510.68 ✓
			537	540	✓	✓	572.18 ✓
	pm letter 11/9/67		538	541	An medal Bracelet	✓	513.13 ✓
	11/21	" "	539	542	Medal	1 Guatemala Gold med.	2.45 ✓
	11/17	" "	C-36	C-38	Coin	1-20 Peso Mex.	0.50 ✓
		" "	C-37	C-39	✓	1-50 Peso "	0.53 ✓
		" "	C-38	C-40	✓	1- US Gold Coin	1.33 ✓
		" "	C-39	C-41	✓	5-2 Peso	0.05 ✓
		" "	C-40	C-42	✓	5-50 " Mex	3.14 ✓
		" "			✓	17- 2 1/2 Peso mex	1.13 ✓
11/15	11/14/67		C-41	C-43	✓	5- Gold Plated Ni. Canadian	
	11/22		540	543	Scrap	1- " " Quarter "	
	11/21		541	544	Bars	Ind	37.18 ✓
			542	545	Scrap	So Dakota	5168.58 ✓
						Ind	25.28 ✓

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 843 °	114 °	43 °	12			\$	\$	Cooley and Gravel Co	\$
✓ 423 ½	69 °	507 ½	18			3.05 x Lm		Triad Mfg Corp, Inc Buffalo, N.Y.	
✓ 457 °	129 °	414 °	16					J. L. Thorpe & Co Deadwood, S. Dak.	
✓ 842 ½	151 °	6 ½	12					Harold Strandberg, Anchorage, Alaska	
✓ 163 °	120 °	117 °	13					C. Vaughn & Co. Inc. Dickinson, Tex	
✓ 396 ½	109 °	444 ½	18					Justino Inc	
✓ 388 ½	97 °	514 ½	18					" "	
✓ 973 °	6 °	21 °	6			3.05 x Lm		Motorola	
✓ 983 °	1 °	16 °	6					"	
✓ 918 °	3 °	79 °	13					"	
✓ 999 ½	3 °	197 ½	16			3.80 x Lm		"	
✓ 995 ½	0 °	4 ½	0					"	
✓ 882 ½	1 °	116 ½	13					"	
✓ 997 °	2 °	1 °	0					"	
✓ 999 °	0 °	1 °	0					"	
✓ 913 ½	1 °	85 ½	13					"	
✓ 915 ½	3 °	81 ½	13					"	
✓ 405 ½	141 °	453 ½	18			7.55 x Lm		Justino	
✓ 400 °	131 °	469 °	18			8.30 x Lm		"	
✓ 754 °	57 °	189 °	16					The Estate of Dale Foster, Arcadia, Florida	
✓ 900 °	0 °	100 °	13					Michael Hofmann, El Paso, Tex	
✓ 900 °	0 °	100 °	13					James W. Kiskling, Houston, Tex	
✓ 900 °	0 °	100 °	13					Mrs. Rosa Oliveros, Weslaco, Tex	
✓ 900 °	0 °	100 °	0					Director of Customs, Nogales, Ariz	
✓ 900 °	0 °	100 °	0					" " " "	
✓ 900 °	0 °	100 °	13					Estate of Dale Foster, Arcadia, Cal.	
✓ 1 ½	158 °	840 ½	0					Bureau Customs, Minneapolis, Minn.	
✓ 509 ½	120 °	370 ½	21			2.30 x Lm		Louis W. Spiegel, Caroga Park, Calif.	
✓ 997.3	2.7	0.0	0					Homestake,	
✓ 954 ½	3 °	42 ½	6			2.30 x Lm		Motorola, Phoenix	

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 938502

DATE 1967

NUMBER

MODE
OF
PAYMENT

DESCRIPTION

WEIGHT
AFTER
MELTING

Received	Reported	Hour	Receipt	Assay			
11/15	11/21		543	546	Scrap	Ind	29.22
	11/22		544	547	✓	✓	243.05
			545	548	✓	✓	274.65
			546	549	✓	✓	475.15
			547	550	✓	✓	458.41
			548	551	✓	✓	10.55
11/17	11/24		549	552	✓	✓	7.57
			550	553	✓	✓	161.32
11/20			551	554	✓	✓	447.21
			552	555	✓	✓	101.07
			553	556	✓	✓	307.61
			554	557	✓	✓	74.21
			555	558	✓	✓	27.09
			556	559	✓	✓	274.13
			557	560	✓	✓	459.32
			558	561	✓	✓	376.10
			559	562	Retort	Idaho	9.31
			560	563	" + Gr	Alaska	51.00
			561	564	Bars	So. Dakota	2209.66
			562	565	"	"	3684.49
			563	566	Retort	Boulder, Colo	24.61
11/21			564	567	Scrap	Ind	982.55
			565	568	✓	✓	831.60
			566	569	✓	✓	374.84
			567	570	✓	✓	1029.34
			568	571	✓	✓	377.73
			569	572	✓	✓	6583.4
11/22	11/29		570	573	Retort	Montana	22.78
			571	574	"	Adams	24.16
			572	575	Bars	So. Dakota	5652.35

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 594 $\frac{1}{2}$	2°	403 $\frac{1}{2}$	21			\$ 230 x $\frac{1}{2}$ lb	\$ Motorola,	\$ Phoenix,	\$ Ariz
✓ 993°	1°	6°	6				"	"	
✓ 923°	4°	73°	13				"	"	
✓ 924°	4°	72°	13				"	"	
✓ 913°	5°	82°	13				"	"	
✓ 644 $\frac{1}{2}$	161°	194 $\frac{1}{2}$	16			230 x $\frac{1}{2}$ lb	Clifford L. Green,	Denver,	Colo
✓ 495 $\frac{1}{2}$	72°	433°	16				Argenzio Bros.	Denver,	Colo
✓ 846°	219°	435°	16			455 x $\frac{1}{2}$ lb	John Robert mfg Co	Norman,	Okl
✓ 970 $\frac{1}{2}$	1°	28 $\frac{1}{2}$	6				Motorola,	Phoenix	
✓ 997 $\frac{1}{2}$	0°	2 $\frac{1}{2}$	0				"	"	
✓ 981 $\frac{1}{2}$	1°	17 $\frac{1}{2}$	6				"	"	
✓ 974°	0°	26°	6				"	"	
✓ 869°	1°	130°	13			230 x $\frac{1}{2}$ lb	"	"	
✓ 996 $\frac{1}{2}$	0°	3 $\frac{1}{2}$	0				The Bendix Corp	Kansas City,	Division
✓ 414 $\frac{1}{2}$	112°	473 $\frac{1}{2}$	18			830 x $\frac{1}{2}$ lb	Sotens Inc		
✓ 416°	107°	477°	18			680 x $\frac{1}{2}$ lb	Sotens, Inc		
✓ 654°	322°	24°	12			230 x $\frac{1}{2}$ lb	Wendell Morse,	Keupeluf,	Alto
✓ 859°	138°	3°	12				Engbret Johnson,	Spokane,	Wash.
✓ 997 $\frac{3}{4}$	2 $\frac{1}{4}$	0°	0				Homestake		
✓ 998 $\frac{3}{4}$	1 $\frac{1}{4}$	0°	0				"		
✓ 783°	188°	29°	12				Edward J. Mc Lellan,	Longmont,	Colo
✓ 387 $\frac{1}{2}$	167°	445 $\frac{1}{2}$	16				Sotens Inc.		
✓ 395 $\frac{1}{2}$	75°	529 $\frac{1}{2}$	18				"	"	
✓ 399 $\frac{1}{2}$	111°	489 $\frac{1}{2}$	18				"	"	
✓ 403°	99°	498°	18				"	"	
✓ 392 $\frac{1}{2}$	99°	508 $\frac{1}{2}$	18				"	"	
✓ 383°	115°	502°	18				"	"	
✓ 915°	82°	3°	12				Mrs. A. K. Scharf		
✓ 868 $\frac{1}{2}$	111°	20 $\frac{1}{2}$	12				Norkling & Alensker,	Lockwood,	Colo
✓ 997.8	2.2	0.0	0				Homestake		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 980500

DATE 1967			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
11/22	11/29		573	576	Scrap	Ind	194.71
			574	577	✓	✓	183.24
			575	578	✓	✓	44.33
			576	579	✓	✓	52.84
			577	580	✓	✓	540.5
			578	581	✓	✓	351.42
11/22			579	582	mut Coin	30 mutilated Silver Dollars	24.93
			580	583	"	138 - 1/2 \$ 247 - 1/4 \$ 408 - 1/10 \$ U.S. Silver	133.04
11/24			581	584	Scrap	Ind	568.10
			582	585	✓	✓	167.71
			583	586	✓	✓	4.94
	12/1		584	587	✓	✓	15.24
11/27	11/29		585	588	Ret & Gr	Curay	442.44
11/28	12/1		586	589	Retort	Chaffee, Colo	1.22
			587	590	Scrap	Ind	7.16
			588	591	Bars	Ind	1581.15
			589	592	"	✓	334.01
			590	593	Scrap	Ind	734.71
	12/1		591	594	✓	✓	192.51
11/29			592	595	✓	✓	692.51
			593	596	✓	✓	1134.68
			594	597	Bars	Do Dokata	5232.33
11/30			595	598	Scrap	Ind	2.85
12/5			596	599	✓	"	342.71
			597	600	✓	"	32.17
			598	601	✓	"	138.17
			599	602	✓	"	527.87
			600	603	✓	"	485.04
			601	604	✓	"	566.20
			602	605	✓	"	515.64

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 403 $\frac{1}{2}$	72 °	524 $\frac{1}{2}$	18			\$	\$ Wilbar Casting Co., Inc.,	Buffalo, N.Y.	
✓ 995 °	0 °	5 °	0				Motorola,	Phoenix, Ariz.	
✓ 905 °	0 °	95 °	13			2 $\frac{30}{100}$ Lm	"		"
✓ 995 °	0 °	5 °	0				"		"
✓ 931 °	6 °	63 °	13				"		"
✓ 924 °	7 °	69 °	13						
✓ 0 °	911 $\frac{3}{4}$	88 $\frac{1}{4}$	0				Supt.		
✓ 0 °	827 °	173 °	0				"		
✓ 411 °	90 °	499 °	18			8 $\frac{30}{100}$ Lm	John Roberts Mfg.,	Norman, Okla.	
✓ 507 $\frac{1}{2}$	96 °	396 $\frac{1}{2}$	21				S.W. Texas Precious Metals,	San Antonio, Tex.	
✓ 672 °	162 °	166 °	16				Finch Jewelers,	Corina, Calif.	
✓ 814 $\frac{1}{2}$	88 °	597 $\frac{1}{2}$	21				Mrs. C.A. Brownmillie,	Marcus, Iowa	
✓ 412 °	141 °	447 °	16				Idarado Mining Co.,	Duray, Colo.	
✓ 841 $\frac{1}{2}$	146 °	12 $\frac{1}{2}$	12			2 $\frac{30}{100}$ Lm	Richard O. Hanson,	Steward, Colo.	
✓ 562 °	60 °	378 °	21				Charlie B. Scott,	Austin, Tex.	
✓ 997 $\frac{3}{4}$	2 $\frac{1}{4}$	0.0	0				Homestake		
✓ 997 $\frac{3}{4}$	2 $\frac{1}{4}$	0.0	0				"		
✓ 906 °	3 °	91 °	13				Motorola	Phoenix	
✓ 991 $\frac{1}{2}$	0 °	8 $\frac{1}{2}$	6				"		"
✓ 394 $\frac{1}{2}$	99 °	506 $\frac{1}{2}$	18				Intens	Princeton, Ill.	
✓ 393 $\frac{1}{2}$	104 °	502 $\frac{1}{2}$	18				"		"
✓ 997 °	3 °	0 °	0				Homestake		
✓ 382 $\frac{1}{2}$	288 °	329 $\frac{1}{2}$	13				Morris Inc.,	Blytheville, Arkansas	
✓ 961 °	1 °	38 °	6				Motorola.		
✓ 989 $\frac{1}{2}$	0 °	10 $\frac{1}{2}$	6				"		
✓ 865 °	5 °	130 °	13			3 $\frac{80}{100}$ Lm	"		
✓ 862 $\frac{1}{2}$	5 °	132 $\frac{1}{2}$	13			6 $\frac{80}{100}$ Lm	"		
✓ 894 $\frac{1}{2}$	2 °	103 $\frac{1}{2}$	13				"		
✓ 911 °	3 °	86 °	13				"		
✓ 586 $\frac{1}{2}$	5 °	408 $\frac{1}{2}$	21			4 $\frac{25}{100}$ Lm	"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930900

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
12/5			603	606	Scrap	Ind	354.74
			604	607	"	"	460.51
			605	608	"	"	204.89
			606	609	"	Nevada	4424.03
12/6			607	610	Bars	✓. Oak	2133.87
			608	611	"	"	3752.39
			609	612	Scrap	Ind	296.81
			610	613	✓	✓	89.94
			611	614	✓	✓	184.36
			612	615	✓	✓	56.02
			613	616	✓	✓	91.24
			614	617	✓	✓	688.15
			615	618	✓	✓	470.83
12/7 3 PM. 12/11			616	619	✓	✓	39.69
			617	620		✓	423.31
			618	621		✓	1017.18
			619	622		✓	968.72
			620	623		✓	686.73
			621	624		✓	1017.22
			622	625		✓	521.98
			623	626		✓	4.62
12/8	12/11	S.B.	5	5	Crown's Bar	slip. Nov. Canis purchased	31.63
	12/13		624	627	Scrap	Ind	23.53
	12/11		625	628	✓	✓	73.75
		S.B.	6	6	S.B.	2nd Quarter Penny 10m 1000000	17.25
12/7	12/13		626	629	Bars	For Dakota	7934.53
			627	630	Scrap	Ind	89.42
			628	631	✓	✓	87.59
			629	632	✓	✓	95.05
	12/15		630	633			453.44

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 990 $\frac{1}{2}$	0°	9 $\frac{1}{2}$	6			\$ Motorola	\$		\$
✓ 988 $\frac{1}{2}$	2°	9 $\frac{1}{2}$	6			"			
✓ 994°	0°	6°	6			"			
995 $\frac{1}{4}$	2 $\frac{3}{4}$	21°	0			Cashier Mng Co.			
✓ 997 $\frac{1}{2}$	2 $\frac{1}{2}$	0°	0			Hornestake			
✓ 997 $\frac{1}{2}$	2 $\frac{1}{2}$	0°	0			"			
✓ 984 $\frac{1}{2}$	84°	331 $\frac{1}{2}$	18			J. W. Sweet & Ref. Co.			
✓ 448 $\frac{1}{2}$	192°	359 $\frac{1}{2}$	16	305 $\frac{1}{2}$		" " "			
✓ 405 $\frac{1}{2}$	114°	480 $\frac{1}{2}$	18	380 $\frac{1}{2}$		Wilbur Casting Co., Buffalo, N. Y.			
✓ 452°	67°	481°	18	385 $\frac{1}{2}$		Irish Manufacturers Group, Buffalo, N. Y.			
✓ 398°	109°	490°	18			Gosteen			
✓ 403 $\frac{1}{2}$	107°	489 $\frac{1}{2}$	18			"			
✓ 423°	114°	463°	18	755 $\frac{1}{2}$		" Jacobson Jew			
✓ 528°	130°	342°	18			Jacobson Jewelry Co., Omaha			
✓ 419 $\frac{1}{2}$	111°	469 $\frac{1}{2}$	18	755 $\frac{1}{2}$		Gosteen			
✓ 386 $\frac{1}{2}$	151°	462 $\frac{1}{2}$	18			"			
✓ 393°	111°	496°	18			"			
✓ 424 $\frac{1}{2}$	111°	464 $\frac{1}{2}$	18			"			
✓ 407 $\frac{1}{2}$	102°	490 $\frac{1}{2}$	18			"			
✓ 394 $\frac{1}{2}$	109°	496 $\frac{1}{2}$	18			"			
✓ 733°	172°	95°	13			Glenn M. Barrett, Klemmer			
✓ 759°	52°	189°	0			Supt			
✓ 651 $\frac{1}{2}$	206°	142 $\frac{1}{2}$	13	230 $\frac{1}{2}$		Mr. Harry A. Williams, Klemmer			
✓ 484 $\frac{1}{2}$	106°	409 $\frac{1}{2}$	16			Klemmer & Redford, Salt Lake City			
✓ 437°	115°	448°	0			Supt			
✓ 996.4	3.6	0°	0			Hornestake			
✓ 988°	0°	12°	6			Motorola			Phoenix
✓ 983 $\frac{1}{2}$	0°	16 $\frac{1}{2}$	6			"			"
✓ 959°	2°	39°	6			"			"
✓ 818 $\frac{1}{2}$	4°	177 $\frac{1}{2}$	16	605 $\frac{1}{2}$		"			"

Remelt before
34 x was Ref
4

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE 1967			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
12/7	12/13		631	634	Retort	Jefferson	21.27 ✓
12/8			632	635	Scrap	Ind	1025.51 ✓
			633	636	✓	✓	18.54 ✓
			634	637	Bars	So Dakota	1372.61 ✓
			635	638	✓	✓ ✓	4024.09 ✓
			636	639	Retort	Boulder	21.76 ✓
			637	640	"	Jefferson	33.84 ✓
12/11			638	641	Scrap	Ind	1025.84 ✓
			639	642	✓	✓	965.66 ✓
	11/4 DM Letter 12/6/67		C-42	C-44	an Coins	49- Dbl Eagle U.S.	52.63 ✓
	12/14		640	643	Bars	Eureka Nevada	7435.70 ✓
	12/15		641	644	Scrap	Ind	2.83 ✓
	11/4 DM Letter 12/7/67		C-43	C-45	an Coins	81- Dbl Eagle U.S.	87.05 ✓
12/12	12/15		642	645	Bars	So Dakota	6527.48 ✓
			643	646	Scrap	Ind	461.99 ✓
			644	647	✓	✓	545.51 ✓
			645	648	✓	✓	461.03 ✓
			646	649	✓	✓	533.77 ✓
	12/18		647	650	✓	✓	272.06 ✓
	12/15		648	651	✓	✓	78.40 ✓
	12/18		649	652	✓	✓	61.67 ✓
	12/15		650	653	✓	✓	51.61 ✓
	12/18		651	654	✓	✓	66.44 ✓
	12/15		652	655	✓	✓	244.15 ✓
			653	656	✓	✓	232.35 ✓
	12/18		654	657	✓	✓	251.09 ✓
			655	658	✓	✓	250.77 ✓
			656	659	✓	✓	186.37 ✓
12/13			657	660	Ret	Adams	29.21 ✓
			658	661	✓	Idaho	18.64 ✓

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 867 1/2	128 0	4 1/2	12			\$	\$ Robt Bray	\$ Sub Grand Co	\$ Black Hawk, Colo
✓ 404 0	105 0	491 0	18				Sister's	Owatonna, Minn	
✓ 539 0	67 0	394 0	21			2 30 x Lm	Galaxie Jewelers,	Demol, Colo.	
✓ 997 3/4	2 1/4	0 0	0				Hornstroke		
✓ 998 1/4	1 3/4	0 0	0				"		
✓ 806 1/2	183 0	10 1/2	12				Edward J. Mc Lellan	Longmont, Colo.	
✓ 853 0	142 0	5 0	12				Herkling & Glensker	Longmont, Colo	
✓ 396 1/2	108 0	495 1/2	18				Sister's	Owatonna, Minn	
✓ 396 0	108 0	496 0	18				"	"	"
✓ 900 0	0 0	100 0	0				Federal Reserve Bank,	Minn, Minn.	
✓ 992.5	4.0	3.5	6				Carlton Gold Mining Co.	Elko Nev.	
✓ 447 1/2	129 0	423 1/2	16				Julia Wusman,	Cheyenne, Wyo	
✓ 900 0	0 0	100 0	0				Federal Reserve Bank	Minn, Minn	
✓ 996.9	3.1	0.0	0				Hornstroke		
✓ 898 0	0 0	102 0	13				Motorola	Phoenix	
✓ 814 0	5 0	181	16			6 30 x Lm	"		"
✓ 852 0	4 0	144 0	13			6 05 x Lm	"		"
✓ 903 0	0 0	97 0	13				"		"
✓ 998 0	0 0	2 0	0				"		"
✓ 769 0	0 0	231 0	16			3 05 x Lm	"		"
✓ 989 1/2	0 0	10 1/2	6				"		"
✓ 983 0	0 0	17 0	6				"		"
✓ 995 0	0 0	5 0	0				"		"
✓ 994 0	0 0	6 0	6				"		"
✓ 979 1/2	1 0	19 1/2	6				"		"
✓ 980 0	0 0	20 0	6				"		"
✓ 991 1/2	0 0	8 1/2	6				"		"
✓ 969 0	2 0	29 0	6				"		"
✓ 874 0	81 0	45 0	12			2 30 x Lm	Herkling & Glensker,	Longmont, Colo.	
✓ 968 1/2	225 0	6 1/2	12				A. W. Josue,	Garden Valley, Idaho	

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE 1967

NUMBER

MODE
OF
PAYMENT

DESCRIPTION

WEIGHT
AFTER
MELTING

Received

Reported

Hour

Receipt

Assay

12/13	12/20		659	662	Scrap	Ind	242.90
12/15			660	663	Bar	So Dakota	1691.97
			661	664	"	✓	6076.85
			662	665	Scrap	Ind	426.51
			663	666	✓	✓	488.44
			664	667	✓	✓	429.90
			665	668	✓	✓	856.53
12/18			666	669	✓	✓	1005.83
			667	670	✓	✓	811.46
			668	671	✓	✓	916.37
		SB	SB-7	SB-7	SB	"K" Grains 5	36.33
	12/22		669	672	Bar	Nevada	4662.76
			✓	673	"	✓	3549.92
			670	674	Scrap	Ind	434.75
			671	675	✓	✓	398.43
			672	676	✓	✓	243.25
			673	677	✓	✓	316.73
			674	678	✓	✓	358.57
12/19			675	679	✓	✓	518.57
			676	680	✓	✓	571.63
			677	681	✓	✓	494.21
			678	682	✓	✓	519.56
			679	683	✓	✓	193.16
			680	684	Relect	Utah	169
12/20			681	685	Scrap	Ind	63.37
			682	686	✓	✓	978.03
			683	687	✓	✓	329.69
12/19	DML 12/15		C-44	C-46	Coins	6 mex = 1-5 Peso 1-5 Peso 1-20 " 1-20 " 1-10 " 1-2 "	239
	"		C-45	C-47	✓	1-20 Peso mex	53
			C-46	C-48	✓	1-Lira, Pina	25

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓424 $\frac{1}{2}$	135 $\frac{0}{4}$	440 $\frac{1}{2}$	16			\$	\$ H. Thorp & Co	Deerwood, Ark.	\$
✓497 $\frac{3}{4}$	2 $\frac{1}{4}$	0 $\frac{0}{4}$	0				Norman, Okla		
✓497.7	2.3	0.0	0				"		
✓389 $\frac{1}{2}$	133 $\frac{0}{4}$	477 $\frac{1}{2}$	18			7 $\frac{55}{100}$ Lm	John Photo Mfg,	Norman Okla	
✓402 $\frac{0}{4}$	114 $\frac{0}{4}$	484 $\frac{0}{4}$	18				Justin's	Owatonna, Min	
✓397 $\frac{1}{2}$	105 $\frac{0}{4}$	497 $\frac{1}{2}$	18				"	✓	
✓392 $\frac{0}{4}$	100 $\frac{0}{4}$	508 $\frac{0}{4}$	18				"	✓	
✓395 $\frac{1}{2}$	131 $\frac{0}{4}$	473 $\frac{1}{2}$	18				"	✓	
✓400 $\frac{1}{2}$	111 $\frac{0}{4}$	488 $\frac{1}{2}$	18				"	✓	
✓403 $\frac{1}{2}$	121 $\frac{0}{4}$	475 $\frac{1}{2}$	18				"	✓	
✓421 $\frac{1}{2}$	87 $\frac{0}{4}$	491 $\frac{1}{2}$	0				Supt		
✓494.7	2.3	3.0	6				Carlisle Gold Mfg,	Elko, Nevada	
✓494.5	2.5	3.0	6				"	"	"
✓494 $\frac{1}{2}$	1 $\frac{0}{4}$	4 $\frac{1}{2}$	6				Motorola	Phoenix, Ariz	
✓858 $\frac{1}{2}$	5 $\frac{0}{4}$	136 $\frac{1}{2}$	13			5 $\frac{30}{100}$ Lm	"	"	"
✓947 $\frac{0}{4}$	0 $\frac{0}{4}$	53 $\frac{0}{4}$	13				"	"	"
✓843 $\frac{0}{4}$	5 $\frac{0}{4}$	152 $\frac{0}{4}$	16			5 $\frac{30}{100}$ Lm	"	"	"
✓995 $\frac{1}{2}$	0 $\frac{0}{4}$	4 $\frac{1}{2}$	0				"	"	"
✓386 $\frac{0}{4}$	107 $\frac{0}{4}$	507 $\frac{0}{4}$	18				Justin's	Princeton, Ill	
✓400 $\frac{0}{4}$	111 $\frac{0}{4}$	489 $\frac{0}{4}$	18				"	"	"
✓425 $\frac{0}{4}$	112 $\frac{0}{4}$	463 $\frac{0}{4}$	18			7 $\frac{55}{100}$ Lm	"	Owatonna Min	
✓418 $\frac{0}{4}$	114 $\frac{0}{4}$	468 $\frac{0}{4}$	18			8 $\frac{30}{100}$ Lm	"	"	"
✓410 $\frac{0}{4}$	63 $\frac{0}{4}$	527 $\frac{0}{4}$	18				Walter Casting Co. Inc,	Buffalo, N.Y.	
✓541 $\frac{0}{4}$	388 $\frac{0}{4}$	71 $\frac{0}{4}$	13			2 $\frac{30}{100}$ Lm	William Roy Nelson,	Richfield, Utah	
✓610 $\frac{0}{4}$	185 $\frac{0}{4}$	205 $\frac{0}{4}$	16				Carl Blawrock,	Denver, Colo	
✓412 $\frac{0}{4}$	115 $\frac{0}{4}$	473 $\frac{0}{4}$	18				Justin's	Owatonna, Min	
✓421 $\frac{1}{2}$	116 $\frac{0}{4}$	462 $\frac{1}{2}$	18			5 $\frac{30}{100}$ Lm	"	Princeton, Ill.	
✓900 $\frac{0}{4}$	0 $\frac{0}{4}$	100 $\frac{0}{4}$	13				Arthur L. Freeman,	Mustegon, Mich	
✓900 $\frac{0}{4}$	0 $\frac{0}{4}$	100 $\frac{0}{4}$	0				Dir Customs - Houston,	Tex	
✓916 $\frac{0}{4}$	0 $\frac{0}{4}$	84 $\frac{0}{4}$	0				Bureau Customs	"	"

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE 1967			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
12/19	12/22		C-46	C-49	Coins	1-Cencuenta Peso	31 ✓
changed to 3/12/67	C-60-63		C-47	C-50	✓	Coins + Jewelry	699 ✓
12/21			C-48	C-51	✓	1-50 Peso	133 ✓
			C-49	C-52	✓	1-10 ⁰⁰ U.S.	53 ✓
			C-50	C-53	✓	1-20 Peso mex	53 ✓
			C-51	C-54	✓	1-2 Peso mex	11 ✓
			C-52	C-55	✓	1-20 Peso mex 1-2 1/2 Peso 1-10 " "	100 ✓
12/26			684	688	Bars.	2. plak	6630 31 ✓
			685	689	Pin	Mutilated Coin	337 ✓
			686	690	"	"	7026 ✓
12/29	9:45 AM		687	691	Bars	3. plak	22907 ✓
			688	692	"	"	453206 ✓
		689 ✓	690	694	Scrap	Ind	21438 ✓
			691	695	"	"	44637 ✓
			692	696	"	"	46460 ✓
			693	697	"	"	17726 ✓
12/22	11A		694	698	✓	✓	355 ✓
12/19			695	699	"	"	46421 ✓
			696	700	"	"	36433 ✓
			697	701	"	"	8477 ✓
			700	704	Bars	Kenada - Fincka	712503 ✓
12/26			701	705	Scrap	Ind	7062 ✓
			702	706	Retent com. lers	Colo - Derray	47831 ✓
12/22	11 1/2	→	689	693	Scrap	Ind	1335 ✓
			698	702	✓	✓	5640 ✓
12/26			699	703	✓	✓	787 ✓
12/27			703	707	✓	✓	49003 ✓
			704	708	✓	✓	2942 ✓
12/28			705	709	✓	✓	83143 ✓
	1A		706	710	✓	✓	48867 ✓

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 900 ⁰	0 ⁰	100 ⁰	0			\$	\$	\$	\$
✓ 874 ¹ / ₂	16 ⁰	109 ¹ / ₂	0				Bureau of Customs, Houston, Tex		
✓ 900 ⁰	0 ⁰	100 ⁰	13				Dist Dir of Customs, Laredo, Tex		
✓ 900 ⁰	0 ⁰	100 ⁰	0				David H. Walke, Shreveport, La		
✓ 900 ⁰	0 ⁰	100 ⁰	13				Kung Sit Hui, N. Y., N. Y.		
✓ 900 ⁰	0 ⁰	100 ⁰	13				Mrs. Robert C. White, Bradenton, Fla		
✓ 900 ⁰	0 ⁰	100 ⁰	0				William G. Hubersberger, Pueblo, Colo		
✓ 900 ⁰	0 ⁰	100 ⁰	0				district director Customs; Houston		
✓ 997 ³ / ₄	27	00	0				Honestake		
✓ 0 ⁰	905 ¹ / ₂	94 ¹ / ₂	0				Supt		
✓ 0 ⁰	783 ¹ / ₂	216 ¹ / ₂	0				"		
✓ 997 ³ / ₄	2 ³ / ₄	0 ⁰	0				Honestake		
✓ 998 ⁰	2 ⁰	0 ⁰	0				"		
✓ 994 ⁰	0 ⁰	6 ⁰	6				Moscola		
✓ 866 ¹ / ₂	3 ⁰	130 ¹ / ₂	13			6 ⁰⁵ h.m.	"		
✓ 872 ¹ / ₂	2 ⁰	125 ¹ / ₄	13			6 ⁰⁵ "	"		
✓ 996 ⁰	0 ⁰	4 ⁰	0				"		
✓ 753 ⁰	2 ⁰	245 ⁰	16			2 ³⁰ x h	"		Phoenix
✓ 875 ¹ / ₂	4 ⁰	120 ¹ / ₂	13			6 ⁰⁵ h.m.	"		
✓ 970 ⁰	1 ⁰	29 ⁰	6				"		
✓ 994 ⁰	0 ⁰	6 ⁰	6				"		
✓ 993.1	2.9	4.0	6				Radwin Mfg Co.		
✓ 434 ⁰	80 ⁰	486 ⁰	18			3 ⁰⁵ x h	Triad Mfg's Group, Inc, Buffalo, N.Y		
✓ 595 ¹ / ₂	186 ⁰	218 ¹ / ₂	16				Idarado.		
✓ 749 ⁰	135 ⁰	116 ⁰	13				Dr. Roscoe D. Baker, Parker, Colo		
✓ 982 ¹ / ₂	1 ⁰	16 ¹ / ₂	6				Motowla - Scottsdale, Ariz		
✓ 725 ¹ / ₂	134 ⁰	140 ¹ / ₂	13				Dr. George J. Rervis, Demore, Colo.		
✓ 412 ⁰	110 ⁰	478 ⁰	18			9 ⁸⁰ x h	John Roberts Mfg. Norman, okla		
✓ 529 ⁰	140 ⁰	331 ⁰	18			2 ³⁰ x h	Louis W. Spugel, Canoga Pk, Calif		
✓ 393 ¹ / ₂	112 ⁰	494 ¹ / ₂	18				Jostens. Princeton, Ill.		
✓ 409 ¹ / ₂	186 ⁰	404 ¹ / ₂	16			6 ⁸⁰ x h	Ring Specialty Co. Inc. Minneapolis, Minn		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

1967 + DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
12/28/67			707	711	Bars	So Dakota	5021 34
			708	712	Scrap	Ind	210 54
			709	713	✓	✓	328
			710	714	✓	✓	79 32
			711	715	✓	✓	112 99
			712	716	✓	✓	445 53
			713	717	Retort ^{wet}	Idaho	5 37
12/29/67			714	718	Scrap	Ind	531 54
			715	719	✓	✓	159 36
	1/4		716	720	1/✓	✓	2 54
1/2			717	721	Bars	Nevada	4704 13
			718	722	Scrap	Ind	736 59
1/4	1/8		719	723	Bars	So Dakota	2247 26
			720	724	✓	✓	3491 96
			721	725	Scrap	Ind	495 34
			722	726	✓	✓	848 48
			723	727	✓	✓	627 02
			724	728	✓	✓	445 80
			725	729	✓	✓	462 80
1/5			726	730	✓	✓	308 75
			727	731	✓	✓	387 6
			728	732	Bars	So Dakota	3058 43
			729	733	"	Nevada	5120 27
	1/11		730	734	"	Ind	110 56
	1/8		731	735	"	So Dakota	1132 50
			732	736	"	"	3922 98
1/11			733	737	Scrap	Ind	494 62
			734	738	✓	✓	496 68
			735	739	✓	✓	450 02
			736	740	✓	✓	167 35

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
997.7	2.3	0.0	0			\$	\$ Homestake	\$	\$
995.0	0.0	5.0	0				Matowla		Phoenix
993.0	0.0	7.0	6			2 ³⁰ xLm	"		"
995 1/2	0.0	4 1/2	0				"		"
943.0	2.0	255.0	18			3 ⁰⁵ xLm	"		"
997.0	2.0	1.0	0				"		"
659.0	334.0	7.0	12				Elvire T. Seaton, Atlanta, Arkho		
401.0	74.0	525.0	18				Jostens Princeton, Ill		
940.0	4.0	56.0	13			49.40 Cash x Chg 3 ³⁰ xLm	Coo's Porcelain Co Golden, Colo		
483.0	78.0	439.0	16				Thomas T. Amaro, Denver, Colo		
994 1/2	3.0	2 1/2	6				Carlin Gold Mining Co. Elko, Nevada		
402 1/2	107.0	490 1/2	18			12 ⁰⁵ xLm	John Roberts mfg Norman, Okla		
997 1/2	2 1/2	0.0	0				Homestake		
998.0	2.0	0.0	0				"		
412 1/2	121.0	466 1/2	18				Jostens Owatonna, Minn		
409 1/2	106.0	484 1/2	18				" " "		
396.0	107.0	497.0	18				" Princeton, Ill.		
419 1/2	116.0	464 1/2	18			7 ⁵⁵ xLm	" Owatonna, Minn		
422.0	114.0	464.0	18			8 ³⁰ xLm	" " "		
417 1/2	117.0	465 1/2	18			6 ⁰⁵ xLm	" " "		
418 1/2	96.0	425 1/2	16			2 ³⁰ xLm	Star Jewelry Co, Inc Houston, Tex.		
997.0	3.0	0.0	0				Homestake		
993.7	3.3	3.0	6				Carlin Gold Mining Co, Elko, Nev.		
147.0	573.0	260.0	10				William Kammberg, Portland, Ore.		
997 1/2	2 1/2	0.0	0				Homestake		
998.0	2.0	0.0	0				"		
920.0	3.0	77.0	13				Matowla		Phoenix
918.0	4.0	78.0	13				"		"
911.0	4.0	85.0	13				"		"
993 1/2	0.0	6 1/2	6				"		"

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
1/8	1/11		737	741	Scrap	Ind	129.40
			738	742	✓	✓	140.85
			739	743	✓	✓	194.10
			740	744	✓	✓	102.34
			741	745	✓	✓	494.77
			742	746	✓	✓	159.78
			743	747	✓	✓	61.56
			744	748	✓	✓	52.21
			745	749	✓	✓	144.04
			746	750	✓	✓	157.72
			747	751	✓	✓	296.25
			748	752	✓	✓	110.55
			749	753	✓	✓	331.15
1/9	1/15		750	754	✓	✓	60.64
	1/15		751	755	✓	✓	61.24
1/12 3:30 PM	1/16		752	756	✓	✓	325.07
✓	✓		753	757	—	✓	55.84
			754	758	Ret	Scrap	152.90
1/10	1/15		755	759	Scrap	Ind	180
			756	760	✓	✓	530.74
	1/11		757	761	✓	✓	467.23
			758	762	✓	✓	896.61
	1/17		759	763	✓	✓	842.28
	1/11		760	764	✓	✓	884.83
	1/17		761	765	✓	✓	987.95
1/12 3:30 PM	1/16		762	766	✓	✓	293.68
	1/17		763	767	✓	✓	265.60
			764	768	—	—	267.54
	1/16		765	769	✓	✓	157.6
			766	770	✓	✓	30.75
							20.38
							39.74
							69.54

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 986 ½	0 °	13 ½	6			\$	\$ Motwla	\$	\$ Phoenix
✓ 988 °	0 °	12 °	6				"		"
✓ 965 ½	2 °	32 ½	6				"		"
✓ 995 ½	0 °	4 ½	0				"		"
✓ 918 ½	4 °	77 ½	13				"		"
✓ 986 ½	0 °	13 ½	6				"		"
✓ 997 ½	1 °	1 ½	0				"		"
✓ 987 °	0 °	13 °	6				"		"
✓ 991 °	1 °	8 °	6				"		"
✓ 988 °	0 °	12 °	6				"		"
✓ 994 °	0 °	6 °	6				"		"
✓ 917 ½	1 °	81 ½	13			30 ⁵ X Lm	"		"
✓ 993 °	0 °	7 °	6				"		"
✓ 407 °	221 °	372 °	16			23 ⁰ X Lm	Sweet Smelter Ref.		Dallas Tex
✓ 636 ½	88 °	275 ½	18				"	"	"
✓ 398 °	116 °	486 °	18				John Roberts Mfg. Norman, Okla.		"
✓ 420 ½	89 °	490 ½	18			4 ⁵⁵ X Lm	"	"	"
✓ 825 °	171 °	4 °	12				Stamill Creek, Black Hawk, Colo		
✓ 418 °	111 °	471 °	18			8 ³⁰ X Lm	Isoton		Owatonna, Minn
✓ 415 ½	119 °	465 ½	18			8 ³⁰ X Lm	"	"	"
✓ 398 °	104 °	498 °	18				"	"	"
✓ 400 ½	109 °	490 ½	18				"	"	"
✓ 401 ½	126 °	472 ½	18				"	"	"
✓ 408 ½	127 °	464 ½	18			6 ⁰⁵ X Lm	"	"	"
✓ 410 °	111 °	479 °	18			7 ⁵⁵ X Lm	"		Princeton, Ill
✓ 544 ½	87 °	368 ½	21				Mugler's Jewellers, Idaho Falls, Idaho.		
✓ 306 ½	393 °	300 ½	13				Rio Grande Wholesale Jewellers, Albuquerque, N. Mex.		
✓ 551 ½	67 °	381 ½	21				J. Wesler, Jeweler, Houston, Texas		
✓ 469 °	99 °	432 °	16			23 ⁰ X Lm	Star Jewellery Co., Inc. Houston, Tex		
✓ 430 °	174 °	396 °	16			23 ⁰ X Lm	Louis W. Spiegel, Conago Park, Calif		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930990

DATE 1965			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
1/12		GB	6	6	Grains Bot	Grains bot December. C-46, C-47, C-48, C-49, C-50 C-51, C-52, C-53, C-54, C-55	39 60
	1/17		767	771	Scrap	Ind	689 96
			768	772	✓	✓	718 88
	1/19		769	773	✓	✓	722 96
			770	774	✓	✓	798 88
			771	775	Scrap	Ind	638 97
			772	776	✓	✓	814 41
			773	777	✓	✓	101 41
	1/19		774	778	✓	✓	571 12
	1/17		775	779	Scrap	Ind	81 92
	1/19		776	780	✓	✓	135 09
	1/17		777	781	Scrap	Ind	54 71
	1/19		778	782	✓	✓	10 68
1/15	1/17		779	783	Bars	Nevada	5709 25
	1/19		780	784	Scrap	Ind	124 60
			781	785	Bars	South Dakota	6115 40
			782	786	✓	✓ ✓	2531 05
			783	787	✓	✓ ✓	2167 73
			784	788	Relist	Adams	37 42
			785	789	✓	Jefferson	21 32
			786	790	✓	Boulder	24 28
			787	791	Scrap	Ind	98 9
			788	792	✓	✓	273 86
	1/22		789	793	✓	✓	323 6
1/16	1/19		790	794	✓	✓	901 70
			791	795	✓	✓	491 92
		SB	SB-8	SB-8	SB	From "K" Grains #6	38 61
1/17	1/22		792	796	Scrap	Ind	485 96
			793	797	✓	✓	457 50
			794	798	✓	✓	805 96

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 999 $\frac{1}{2}$	35°	165 $\frac{1}{2}$	0			\$	\$ Supt	\$	\$
✓ 392°	55°	553°	21				Supt O.C. Tanner, Inc. Salt Lake City, Utah		
✓ 894°	4°	102°	13			8 ³⁰ x Lm	Motorola		Phoenix, Ariz
✓ 894°	4°	102°	13			8 ³⁰ x L	"		" "
✓ 881 $\frac{1}{2}$	5°	113 $\frac{1}{2}$	13			9 ⁰⁵ x Lm	"		"
✓ 970°	2°	28°	6				Motorola		Phoenix
✓ 865°	5°	130°	13			10 ⁵⁵ x Lm	"		"
✓ 979°	1°	20°	6				"		"
✓ 998 $\frac{1}{2}$	0°	1 $\frac{1}{2}$	0				"		"
✓ 572 $\frac{1}{2}$	45°	382 $\frac{1}{2}$	21				Kochmer's Raynor Diamond Co. Minn.		
✓ 451°	72°	477°	18			30 ⁵⁵ x Lm	Fashion Craft Mfg Co. Buffalo, N.Y.		
✓ 532 $\frac{1}{2}$	77°	390 $\frac{1}{2}$	21				T.A. Darrin Co, Minneapolis, Minn.		
✓ 522°	238°	240°	16			2 ³⁰ x Lm	Petersen Jeweler, Boulder, Colo		
✓ 992.3	2.2	5.5	6				Carlin Gold Mng, Elko, Nevada		
✓ 992 $\frac{1}{2}$	0°	7 $\frac{1}{2}$	6				O.C. Tanner Inc, Salt Lake City, Utah		
✓ 997.1	2.9	0.0	0				Homestake		
✓ 997 $\frac{1}{2}$	2 $\frac{1}{2}$	0°	0				"		
✓ 997 $\frac{1}{4}$	2 $\frac{3}{4}$	0°	0				"		
✓ 880 $\frac{1}{2}$	116°	3 $\frac{1}{2}$	12				Kerkling & Slomka, Silverwood, Colo		
✓ 854 $\frac{1}{2}$	142°	3 $\frac{1}{2}$	12				"		"
✓ 791 $\frac{1}{2}$	199°	9 $\frac{1}{2}$	12				Edward J. McEllan, Englewood, Colo.		
✓ 693 $\frac{1}{2}$	158°	148 $\frac{1}{2}$	13				Irish Jeweler, Corona, Calif		
✓ 573°	61°	366°	21				Isteno - Princeton, Ill.		
✓ 520 $\frac{1}{2}$	54°	425 $\frac{1}{2}$	21			2 ³⁰ white Gold	Samuel Gordon Co Okla City, Okla.		
✓ 404 $\frac{1}{2}$	117°	478 $\frac{1}{2}$	18				Isteno Owatonna Minn.		
✓ 397 $\frac{1}{2}$	80°	522 $\frac{1}{2}$	18				" Princeton, Ill		
✓ 409 $\frac{1}{2}$	87°	503 $\frac{1}{2}$	0				Supt.		
✓ 417°	115°	468°	18			8 ³⁰ x Lm	Isteno's Inc Owatonna, Minn		
✓ 404°	113°	473°	18			7 ⁵⁵ x Lm	"		"
✓ 397 $\frac{1}{2}$	106°	496 $\frac{1}{2}$	18				"		"

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 230500

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
1/17	1/22		795	799	Scrap	Ind	699 16 ✓
			796	800	✓	✓	583 86 ✓
			797	801	✓	✓	112 14 ✓
			798	802	Bars	So Dokata	5176 73 ✓
		DML 1/14/68	799	803	✓	Gold & Silver in melted form - See Letter 1/14/68	1 16 ✓
1/18			800	804	Scrap	Ind	753 72 ✓
			801	805	✓	✓	565 73 ✓
1/19	1/24		802	806	✓	✓	440 86 ✓
1/22			803	807	Bars	Nevada	5793 71 ✓
			804	808	Scrap	Ind	10 56 ✓
			805	809	✓	✓	44 43 ✓
1/23			C-53	C-56	Coin	1-2 Pesos mex	0 05 ✓
1/22	1/25		806	810	Retort	Chaffee - Colorado	648 ✓
1/23			807	811	Bars	So Dokata	165099 ✓
			808	812	✓	✓	353515 ✓
	1/26		809	813	Scrap	Ind	25940 ✓
1/24			810	814	✓	✓	420 63 ✓
1/23			811	815	✓	✓	411 96 ✓
			812	816	✓	✓	476 69 ✓
			813	817	✓	✓	398 97 ✓
			814	818	✓	✓	462 65 ✓
			815	819	✓	✓	119 08 ✓
			816	820	✓	✓	76 84 ✓
			817	821	✓	✓	88 21 ✓
			818	822	✓	✓	168 86 ✓
			819	823	✓	✓	180 33 ✓
			820	824	✓	✓	86 63 ✓
			821	825	✓	✓	117 30 ✓
			822	826	✓	✓	82 64 ✓
			823	827	✓	✓	22 69 ✓

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 408 $\frac{1}{2}$	105 °	486 $\frac{1}{2}$		18		\$	\$	\$	\$
✓ 394 °	113 °	493 °		18			Sosters	Owatonna	Min
✓ 491 $\frac{1}{2}$	103 °	405 $\frac{1}{2}$		16			"	"	"
✓ 997.5	2.5	0.0		0			Louis W. Spiegel, Canoga Park, Calif.		
✓ 107 $\frac{1}{2}$	881 °	11 $\frac{1}{2}$		4			Homestake		
✓ 392 $\frac{1}{2}$	110 °	497 $\frac{1}{2}$		18			Arthur H. Adams, Long Beach, Calif.		
✓ 393 $\frac{1}{2}$	103 °	503 $\frac{1}{2}$		18			Sosters, Princeton, Ill.		
✓ 423 $\frac{1}{2}$	117 °	459 $\frac{1}{2}$		18			✓	✓	✓
✓ 996.4	2.2	1.4		0			Sosters	Owatonna	Min
✓ 569 $\frac{1}{2}$	54 °	376 $\frac{1}{2}$		21		2 $\frac{30}{100}$ x Lm	Carlin Gold Mng.	Elko, Nev	
✓ 375 $\frac{1}{2}$	163 °	461 $\frac{1}{2}$		18		2 $\frac{30}{100}$ x Lm	Barros Insulin, Beaup, Mont.		
✓ 900 °	0 °	100 °		13			Norman Burnett		
✓ 835 $\frac{1}{2}$	161 °	3 $\frac{1}{2}$		12			Wfg Insulin, Salt Lake City, Utah		
✓ 996 $\frac{3}{4}$	3 $\frac{1}{4}$	0 °		0			Man Welmar Crotty, Belleville, Ill		
✓ 997 $\frac{3}{4}$	2 $\frac{1}{4}$	0 °		0			Albert C. Horne, Granite, Colo		
✓ 896 $\frac{1}{2}$	3 °	100 $\frac{1}{2}$		13		4 $\frac{55}{100}$ x Lm	Homestake		
✓ 893 $\frac{1}{2}$	3 °	103 $\frac{1}{2}$		13		6 $\frac{05}{100}$ x Lm	"		
✓ 843 °	5 °	152 °		16		6 $\frac{05}{100}$ x Lm	"		
✓ 907 $\frac{1}{2}$	2 °	90 $\frac{1}{2}$		13			"		
✓ 832 °	6 °	162 °		16		6 $\frac{05}{100}$ x Lm	"		
✓ 906 °	3 °	91 °		13			"		
✓ 989 °	1 °	10 °		6			"		
✓ 938 °	2 °	60 °		13		3 $\frac{05}{100}$ x Lm	"		
✓ 998 °	1 °	1 °		0			"		
✓ 981 $\frac{1}{2}$	1 °	17 $\frac{1}{2}$		6			"		
✓ 891 °	1 °	108 °		13			"		
✓ 998 °	0 °	2 °		0			"		
✓ 997 °	0 °	3 °		0			"		
✓ 991 °	0 °	9 °		6			"		
✓ 991 $\frac{1}{2}$	0 °	8 $\frac{1}{2}$		6			"		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 920500

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
1/23	1/26		824	828	Scrap	Ind	21 61 ✓
			825	829	✓	✓	176 42 ✓
			826	830	✓	✓	177 26 ✓
			827	831	Bars	Boulder Co	1 48 ✓
	1/29		828	832	Scrap	Ind	2644 ✓
1/24			829	833	✓	✓	38 18 ✓
			830	834	✓	✓	1 109 08 ✓
			831	835	✓	✓	491 18 ✓
			832	836	✓	✓	1 027 73 ✓
1/25	1/30		833	837	✓	✓	431 10 ✓
			834	838	✓	✓	1 207 73 ✓
			835	839	✓	✓	584 02 ✓
			836	840	✓	✓	672 43 ✓
			837	841	✓	✓	712 20 ✓
			838	842	✓	✓	1 002 97 ✓
	1/31		839	843	✓	✓	56 31 ✓
1/26	1/29		840	844	Ag Coin	1093 U.S. Dollars	8 11 ✓
			841	845	✓	254 Dollars 1319 1/4 Dollars 1313 1/10 "	445 40 ✓
	2/1		842	846	Ref & Ins	Ouray	393 70 ✓
			843	847	Bars	So. Dakota	4 425 86 ✓
			844	848	Scrap	Ind	524 47 ✓
			845	849	✓	✓	559 81 ✓
			846	850	✓	✓	464 19 ✓
			847	851	✓	✓	590 62 ✓
			848	852	✓	✓	579 67 ✓
			849	853	✓	✓	490 09 ✓
			850	854	✓	✓	86 99 ✓
			851	855	✓	✓	83 34 ✓
			852	856	✓	✓	106 30 ✓
			853	857	✓	✓	36 72 ✓

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 988 °	0 °	12 °		6		\$	\$ Motorola	\$ Phoenix	\$ Ariz
✓ 717 ½	219 °	63 ½		13			"	"	"
✓ 406 °	110 °	484 °		18		455x _{Ln}	John Roberts mfg.	Norman, Okla	
✓ 855 °	78 °	67 °		13			John B. O'Malley Jr.	Aurora, Colo	
✓ 467 ½	143 °	449 ½		16		230x _{Ln}	The Atlas Co.	Denver, Colo	
✓ 557 ½	100 °	342 ½		18			Harry E. Rogers,	Denver Colo	
✓ 884 ½	102 °	513 ½		18			Jostens	Ovatomna, Minn.	
✓ 426 ½	109 °	464 ½		18		830x _{Ln}	"	"	"
✓ 403 ½	100 °	496 ½		18			"	"	"
✓ 425 °	111 °	464 °		18		680x _{Ln}	"	"	"
✓ 403 ½	113 °	483 ½		18			"	"	
✓ 406 ½	109 °	484 ½		18			"	"	
✓ 395 ½	0 °	604 ½		21			"	"	
✓ 354 °	66 °	580 °		21			"	"	
✓ 429 ½	105 °	465 ½		18			"	"	
✓ 514 °	89 °	397 °		21		230 white Gold	Berger Co.,	Houston, Tex	
✓ 0 °	910 ½	89 ½		0			Supl.		
✓ 0 °	872 °	128 °		0			✓		
✓ 493 °	169 °	338 °		13			Idarado Mining Co.	Ariz, Colo-	
✓ 997 ¾	2 ¼	0 °		0			Homestake		
✓ 878 ½	4 °	117 ½		13		680x _{Ln}	Motorola	Phoenix	
✓ 874 °	5 °	121 °		13		680x _{Ln}	"	"	
✓ 816 °	7 °	177 °		16		680x _{Ln}	"	"	
✓ 881 ½	3 °	115 ½		13		755x _{Ln}	"	"	
✓ 880 °	5 °	115 °		13		755x _{Ln}	"	"	
✓ 826 ½	5 °	168 ½		16		680x _{Ln}	"	"	
✓ 998 ½	0 °	1 ½		0			"	"	
✓ 993 ½	0 °	6 ½		6			"	"	
✓ 998 °	0 °	2 °		0			"	"	
✓ 973 °	2 °	25 °		6			"	"	

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 536500

DATE 1968

NUMBER

MODE
OF
PAYMENT

DESCRIPTION

WEIGHT
AFTER
MELTING

Received	Reported	Hour	Receipt	Assay			
1/26	2/1		854	858	Scrap	Ind	37 82
			855	859	✓	✓	41 47
			856	860	✓	✓	54 09
			857	861	✓	✓	63 50
			858	862	✓	✓	296 32
			859	863	✓	✓	83 48
			860	864	✓	✓	54 23
			861	865	✓	✓	154 60
			862	866	✓	✓	171 19
			863	867	✓	✓	73 20
1/29			864	868	✓	✓	13 10
			865	869	⁴ Bars	Eureka, Nev	4363 24
			✓	870	³ ✓	✓ ✓	3581 48
1/30			866	871	Scrap	Ind	391 64
	2/2		867	872	✓	✓	67 85
1/31			868	873	✓	✓	76 54
			869	874	✓	✓	623 72
			870	875	✓	✓	225 10
			871	876	✓	✓	152 21
			872	877	Bars	So Dakota	1583 12
			873	878	✓	"	4371 98
2/1			874	879	Scrap	Ind	346 73
2/1			875	880	✓	✓	500 55
2/2	2/7		876	881	Bars	So Dakota	3447 98
	2/8		877	882	Scrap	Ind	28 28
			878	883	✓	✓	469 34
			879	884	✓	✓	430 94
			880	885	✓	✓	408 35
			881	886	✓	✓	424 48
			882	887	✓	✓	415 17

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 923 1/2	2 0	74 1/2	13			\$ 230 x Lm	\$ Motorola,		\$ Phoenix
✓ 987 1/2	209 0	3 1/2	12				"		"
✓ 996 0	1 0	3 0	0				"		"
✓ 994 1/2	0 0	5 1/2	6				"		"
✓ 997 0	1 0	2 0	0				"		"
✓ 998 0	1 0	1 0	0				"		"
✓ 996 0	1 0	3 0	0				"		"
✓ 904 0	0 0	96 0	13				"		"
✓ 995 1/2	1 0	3 1/2	0				"		"
✓ 994 1/2	1 0	4 1/2	6				"		"
✓ 556 0	65 0	379 0	21				Globe Jewelry Co,		Denver, Colo
✓ 996 0	2 0	2 0	0				Carlin Gold Mng Co,		Elko, Nev
✓ 996 0	2 0	2 0	0				✓ ✓ ✓	✓	✓
✓ 381 1/2	187 0	431 1/2	16			905 x Lm	John Roberts Mfg,		Norman, Okla
✓ 473 0	197 0	330 0	13			305 x Lm	Molberg's Gold Palace,		Denver, Colo
✓ 540 1/2	70 0	389 1/2	21				Gordon Erickson Co,		Min, Minn
✓ 995 0	0 0	5 0	0				Motorola		Phoenix
✓ 998 0	0 0	2 0	0				"		"
✓ 994 0	0 0	6 0	6				"		"
✓ 996 3/4	3 1/4	0 0	0				Homestake		
✓ 998 1/4	1 3/4	0 0	0				"		
✓ 425 0	112 0	463 0	18			605 x Lm	Sterling Inc.		Awatonna, Minn
✓ 348 0	95 0	557 0	21				✓ ✓	✓	✓
✓ 997 1/2	2 1/2	0 0	0				Homestake		
✓ 995 0	0 0	5 0	0				Motorola		Phoenix
✓ 915 0	2 0	83 0	13				✓		✓
✓ 902 1/2	3 0	94 1/2	13				✓		✓
✓ 987 1/2	2 0	10 1/2	6				✓		✓
✓ 896 1/2	3 0	100 1/2	13				✓		✓
✓ 894 0	4 0	102 0	13			530 x Lm	✓		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 10-20000

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
2/2	2/4		883	888	Scrap	Ind	298.21
			884	889	✓	✓	487.45
			885	890	✓	✓	451.78
			886	891	✓	✓	472.94
	2/9		887	892	✓	✓	73.51
			888	893	✓	✓	277.00
			889	894	✓	✓	813.17
2/5	2/8		890	895	Bars	Nevada	6186.31
	2/9		891	896	Scrap	Ind	373.44
			892	897	✓	✓	434.23
			893	898	✓	✓	120.44
			894	899	✓	✓	412.20
2/6	2/8		895	900	Scrap	Ind	234.19
	2/14		896	901	✓	✓ Remelt	43.01
							43.25
		GB	7	7	Gran Bar	Deposit for month Jan + C-56	27.79
2/7	2/13		897	902	Bars	So Dakota	1133.30
			898	903	✓	✓ ✓	4529.12
			899	904	Scrap	Ind	323.00
			900	905	✓	✓	413.30
			901	906	✓	✓	200.92
			902	907	✓	✓	115.49
			903	908	✓	✓	472.12
			904	909	✓	✓	470.95
			905	910	✓	✓	471.10
			906	911	✓	✓	24.19
2/9	2/14		907	912	✓	✓	65.16
			908	913	✓	✓	73.67
			909	914	✓	✓	290.87
			910	915	✓	✓	204.18
2/8			911	916	Scrap	Ind	217.18

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 879 ⁰	4 ⁰	117 ⁰		13		\$ 455 ^x L	Matwola		Phoenix
✓ 915 ¹ / ₂	4 ⁰	80 ¹ / ₂		13			✓		✓
✓ 907 ¹ / ₂	3 ⁰	89 ¹ / ₂		13			✓		✓
✓ 997 ¹ / ₂	0 ⁰	2 ¹ / ₂		0			✓		✓
✓ 972 ¹ / ₂	0 ⁰	27 ¹ / ₂		6			✓		Scottsdale
✓ 416 ¹ / ₂	87 ⁰	496 ¹ / ₂		18			Lostons		Owatoma
✓ 406 ¹ / ₂	106 ⁰	487 ¹ / ₂		18			✓		✓
✓ 994.7	2.6	2.7		6			Carlin Gold Mng, Elko, Nev.		
✓ 404 ¹ / ₂	103 ⁰	492 ¹ / ₂		18			Lostons		Owatoma Min
✓ 444 ⁰	118 ⁰	468 ⁰		18			✓	✓	
✓ 407 ¹ / ₂	112 ⁰	480 ¹ / ₂		18		455 ^x L	✓	✓	
✓ 405 ¹ / ₂	113 ⁰	481 ¹ / ₂		18		605 ^x L	✓	✓	
✓ 301 ⁰	627 ⁰	72 ⁰		7		455 ^x L	Lamar Surplus, Lamar, Colo.		
✓ 554 ¹ / ₂	81 ⁰	364 ¹ / ₂		21			Ling Bros, Dallas, Tex		
✓ 765 ¹ / ₂	69 ⁰	165 ¹ / ₂		0			Supt.		
✓ 997 ¹ / ₂	2 ¹ / ₂	0 ⁰		0			Homestake		
✓ 997 ¹ / ₂	2 ¹ / ₂	0 ⁰		0			✓		
✓ 694 ¹ / ₂	9 ⁰	296 ¹ / ₂		18		680 ^x L	Matwola		Phoenix
✓ 964 ¹ / ₂	3 ⁰	32 ¹ / ₂		6			✓		✓
✓ 996 ⁰	0 ⁰	4 ⁰		0			✓		✓
✓ 993 ⁰	0 ⁰	7 ⁰		6			✓		✓
✓ 798 ⁰	7 ⁰	195 ⁰		16		680 ^x L	✓		✓
✓ 786 ¹ / ₂	7 ⁰	206 ¹ / ₂		16		680 ^x L	✓		✓
✓ 803 ⁰	7 ⁰	190 ⁰		16		680 ^x L	✓		✓
✓ 953 ¹ / ₂	16 ⁰	30 ¹ / ₂		6			✓		Scottsdale
✓ 574 ⁰	91 ⁰	335 ⁰		18			Louis W. Spugel, Canoga Pk, Calif		
✓ 503 ⁰	132 ⁰	365 ⁰		21		305 ^x L	S.W. Smelling & Ref Co, Dallas, Tex		
✓ 557 ¹ / ₂	116 ⁰	376 ¹ / ₂		18			✓	✓	✓
✓ 544 ¹ / ₂	75 ⁰	380 ¹ / ₂		21			✓	✓	✓
✓ 413 ⁰	145 ⁰	442 ⁰		16		455 ^x L	John Roberts		Norman, Okla

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
2/9	2/13	SB	SB-9	SB-9	Durplus Bullion	"R" Grams, Bar 7	37 91
	2/14		912	917	Scrap	Ind	480 58
			913	918	✓	✓	622 75
			914	919	✓	✓	246 22
2/12			915	920	Retort	Adams	21 57
			916	921	✓	Jefferson	26 25
			917	922	✓	✓	20 50
2/9	2/28		C-54	C-57	au Corno	1-20 Peso 1-5 ✓ mex	0 67
			C-55	C-58	✓	1-10 Peso mex	0 27
			C-56	C-59	✓	1-10 Soles 1-5 ✓ Peruvian	0 22
			C-57	C-60	✓	1-2 1/2 Peso mex.	0 06
			C-58	C-61	✓	1-10 Peso 1-2 1/2 " mex	0 38
			C-59	C-62	✓	1-50 " mex 1-20 " mex	1 87
2/12	2/16		918	923	Bars	So Dokata	5 41329
	2/15		919	924	✓	✓	2 94388
			920	925	✓	✓	2 73309
			921	926	Scrap	Ind	679 02
			922	927	✓	✓	119 46
			923	928	✓	✓	461 06
			924	929	✓	✓	459 47
			925	930	✓	✓	164 34
			926	931	✓	✓	86 35
			927	932	✓	✓	88 15
			928	933	✓	✓	77 61
			929	934	✓	✓	252 26
			930	935	✓	✓	259 99
	2/16		931	936	✓	✓	87 82
			932	937	✓	✓	156 37
2/13	2/19		933	938	✓	✓	251 00
2/14	2/10		934	939	Scrap	Ind	565 68

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 495°	86°	419°	0			\$	\$		\$
✓ 419 ½	113°	467 ½	18			8 ³⁰ x Lm	Supt		
✓ 405°	109°	486°	18				Isotens		Crustanna, Minn.
✓ 454°	111°	435°	16				✓	✓	✓
✓ 859 ½	114°	26 ½	12			2 ³⁰ x Lm	A. L. Thorpe & Co.		Deadwood, So Dakota
✓ 815°	148°	37°	12			2 ³⁰ x Lm	Kerkling & Alenaker,		Lokewood, Colo
✓ 852°	140°	8°	12				✓	✓	✓
✓ 900°	0°	100°	13				George G. Lenzler,		New Orleans, La
✓ 900°	0°	100°	13				Orville Mitchell Jr,		Dallas, Tex
✓ 900°	0°	100°	13				John James Lebring,		Madison, Wisconsin
✓ 900°	0°	100°	13				Robert M. Show,		Kaufman, Texas
✓ 900°	0°	100°	13				Bernard K. Peterson,		Duthorland, Iowa
✓ 900°	0°	100°	13				James C. Fox,		Pine Bluff, Arkansas
✓ 997.3	2.7	0.0	0				Homestake		
✓ 997 ¼	2 ¾	0°	0				✓		
✓ 998 ½	1 ½	0°	0				✓		
✓ 874 ½	3°	122 ½	13			8 ³⁰ x Lm	Motorola		Phoenix
✓ 997 ½	0°	2 ½	0				✓		✓
✓ 883 ½	1°	115 ½	13			6 ⁰⁵ x Lm	✓		✓
✓ 877°	3°	120°	13			6 ⁰⁵ x Lm	✓		✓
✓ 991 ½	3°	5 ½	6				✓		✓
✓ 996 ½	2°	1 ½	0				✓		✓
✓ 996 ½	2°	1 ½	0				✓		✓
✓ 999°	0°	1°	0				✓		✓
✓ 981 ½	4°	14 ½	6				✓		✓
✓ 761°	1°	238°	16				✓		✓
✓ 455 ½	160°	384 ½	16			3 ⁰⁵ x Lm	South West Tex		Precious met. San Antonio, Tex
✓ 467°	72°	461°	18			3 ³⁰ x Lm	Tashon Craft Mfg Co. Inc,		Buffalo, N.Y.
✓ 478 ½	3°	18 ½	6			4 ⁵⁵ x Lm	Covers Potcelaine Co.		Golden, Colo
✓ 390 ½	103°	506 ½	18			76 ²⁰ x Lm	Isotens		Princeton, Ill -

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930500

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
2/14	2/16		935	940	Scrap	Ind	512.44
			936	941	✓	✓	613.0
	2/19		937	942	Retort	Boulder	17.64
	2/20		938	943	Scrap	Ind	12.56
	2/19		939	944	✓	✓	413.74
			940	945	✓	✓	406.62
2/15	2/20		941	946	Bars	So Dakota	4177.63
			942	947	Scrap	Ind	2.48
			943	948	✓	✓	381.67
			944	949	✓	✓	325.92
			945	950	✓	✓	389.86
			946	951	✓	✓	374.96
			947	952	✓	✓	50.99
			948	953	✓	✓	33.27
			949	954	✓	✓	28.26
			950	955	✓	✓	97.21
			951	956	✓	✓	46.26
			952	957	✓	✓	335.16
2/16			953	958	✓	✓	37.29
	2/21		954	959	✓	✓	286.28
			955	960	✓	✓	549.11
			956	961	Bars	✓	108.57
2/19			957	962	Scrap	✓	327.52
	2/26		958	963	Retort	Idaho	5.17
2/20			959	964	Bars	So Dakota	1617.65
			960	965	✓	✓ ✓	4291.61
			961	966	Scrap	Ind	181.87
			962	967	✓	✓	107.76
			963	968	✓	✓	27.66
			964	969	Retort	Adams	81.60

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 418 °	107 °	475 °	18			\$ 30 x Lm	\$ Istons	\$ Owatonna, Min.	
✓ 364 ½	120 °	515 ½	18				✓	✓	✓
✓ 802 °	187 °	11 °	12				Edward J. McEllan, Longmont, Colo		
✓ 502 °	89 °	409 °	21				Albert F. Long Co. Denver, Colo.		
✓ 406 ½	121 °	472 ½	18				Istons	Owatonna, Min.	
✓ 412 °	106 °	482 °	18				✓	✓	✓
✓ 997 ½	2 ½	0 °	0				Homestake,		
✓ 748 °	117 °	135 °	13				Dr. J. A. Walker, Windsor, Colo		
✓ 998 °	0 °	2 °	0				Motorola	Phoenix	
✓ 862 ½	4 °	133 ½	13			4 55 x Lm	✓		✓
✓ 891 ½	3 °	105 ½	13				✓		✓
✓ 886 °	4 °	110 °	13				✓		✓
✓ 995 ½	0 °	4 ½	0				✓		✓
✓ 996 ½	0 °	3 ½	0				✓		✓
✓ 995 °	0 °	5 °	0				✓		✓
✓ 979 °	0 °	21 °	6				✓		✓
✓ 449 °	1 °	550 °	18			230 x Lm	✓		✓
✓ 855 ½	6 °	138 ½	13			530 x Lm	✓		✓
✓ 439 °	86 °	475 °	18			380 x Lm	John Robertson, Norman, Okla		
✓ 408 ½	168 °	423 ½	16				Istons	Owatonna Min	
✓ 365 ½	197 °	437 ½	16				✓	✓	✓
✓ 476 °	133 °	391 °	16				S.W. Texas Prec Metals San Antonio, Tex		
✓ 419 °	116 °	465 °	18				Istons	Owatonna, Min	
✓ 149 ½	240 °	10 ½	12				A. W. Josue, Garden Valley, Idaho		
✓ 998 °	2 °	0 °	0				Homestake		
✓ 997 ¾	2 ¼	0 °	0				✓		
✓ 995 ½	0 °	4 ½	0				Motorola,	Phoenix Ariz	
✓ 994 °	1 °	5 °	6				✓	✓	
✓ 985 °	1 °	14 °	6				✓		
✓ 851 ½	120 °	28 ½	12				Coolidge & Co., Arvada, Colo		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930300

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
2/21	2/26		965	970	Scrap	Ind.	893.32
			966	971	✓	✓	278.28
			967	972	✓	✓	7.62
2/23			968	973	Ag Coin	33 Mint Ag Dollars	27.56
			969	974	Ag Coin Sub	358 1/2 # 11 41 1/4 # 3942 1/10 #	673.81
			970	975	Scrap	Ind.	199.18
			971	976	Bars	So Orskata	5385.28
2/26			972	977	✓	Nevada	4724.30
			973	978	Retort	Ouray	436.99
			974	979	Scrap	Ind.	786.70
			975	980	✓	✓	904.13
			976	981	✓	✓	854.50
			977	982	Bar	✓	776.8
			978	983	✓	✓	155.96
			979	984	Scrap	✓	163.51
			980	985	✓	✓	74.45
2/27			981	986	✓	✓	407.30
			982	987	✓	✓	453.79
			983	988	Wet Snaps	✓	559.65
	3/4		984	989	Bars	So Orskata	2366.59
			985	990	✓	✓	4319.29
	3/1		986	991	Scrap	✓	371.00
			987	992	✓	✓	382.04
			988	993	✓	✓	348.07
			989	994	✓	✓	352.29
			990	995	✓	✓	526.39
			991	996	✓	✓	235.54
			992	997	✓	✓	308.66
	3/4		993	998	✓	✓	57.30
			994	999	✓	✓	40.75

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 393 ⁰	115 ⁰	492 ⁰	18			\$	\$ Iostine	\$ Princeton,	\$ Ill.
✓ 425 ⁰	115 ⁰	460 ⁰	18			4.55x ^{1m}	✓	✓	
✓ 583 ¹ / ₂	72 ⁰	344 ¹ / ₂	18				Gordons Jewelry Inc, Butte, Mont.		
✓ 0 ⁰	901 ¹ / ₂	98 ¹ / ₂	0				Supt.		
✓ 0 ⁰	878 ¹ / ₄	121 ³ / ₄	0				✓		
✓ 728 ⁰	269 ⁰	3 ⁰	12				Motorola	Phoenix	
✓ 997.1	2.9	0.0	0				Homestake		
✓ 994 ¹ / ₂	2 ⁰	3 ¹ / ₂	6				Carlin Gold Mining Co. Elko, Nev		
✓ 479 ¹ / ₂	190 ⁰	330 ¹ / ₂	13				Idarado Mining Co, Duray, Colo.		
✓ 399 ⁰	109 ⁰	492 ⁰	18				Iostine Owatonna, Minn		
✓ 404 ⁰	124 ⁰	472 ⁰	18				✓	✓	
✓ 406 ¹ / ₂	100 ⁰	493 ¹ / ₂	18				✓	✓	
✓ 121 ⁰	723 ⁰	156 ⁰	7				Wm Hannenberg, Portland, Oregon		
✓ 484 ⁰	129 ⁰	387 ⁰	16				S.W. Texas Precious Met. Co. San Antonio, Tex		
✓ 430 ¹ / ₂	69 ⁰	500 ¹ / ₂	18			3.80x ^{1m}	Willas Casting Co Inc, Buffalo, N.Y.		
✓ 411 ¹ / ₂	60 ⁰	528 ¹ / ₂	18				✓	✓	✓
✓ 467 ⁰	105 ⁰	488 ⁰	18				Iostine Owatonna, Minn		
✓ 392 ⁰	58 ⁰	550 ⁰	18				✓	✓	✓
✓ 425 ¹ / ₂	111 ⁰	463 ¹ / ₂	18			905x ^{1m}	✓	✓	✓
997 ³ / ₄	2 ¹ / ₄	0 ⁰	0				Homestake,		
997 ³ / ₄	2 ¹ / ₄	0 ⁰	0				✓		
✓ 865 ⁰	6 ⁰	129 ⁰	13			5.30x ^{1m}	Motorola, Phoenix Ariz		
✓ 869 ⁰	5 ⁰	126 ⁰	13			5.30x ^{1m}	✓	✓	
✓ 866 ⁰	4 ⁰	130 ⁰	13			5.30x ^{1m}	✓	✓	
✓ 866 ¹ / ₂	5 ⁰	128 ¹ / ₂	13			5.30x ^{1m}	✓	✓	
✓ 992 ¹ / ₂	0 ⁰	7 ¹ / ₂	6				✓	✓	
✓ 997 ⁰	0 ⁰	3 ⁰	0				✓	✓	
✓ 979 ¹ / ₂	2 ⁰	18 ¹ / ₂	6				✓	✓	
✓ 995 ⁰	0 ⁰	5 ⁰	0				Motorola		
✓ 977 ⁰	1 ⁰	22 ⁰	6			2.30x ^{1m}	✓	✓	

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 900500

DATE 1968

NUMBER

MODE
OF
PAYMENT

DESCRIPTION

WEIGHT
AFTER
MELTING

Received	Reported	Hour	Receipt	Assay			
2/27	3/4		995	1000	Scrap	Ind	30 90
			996	1001	✓	✓	93 15
			997	1002	✓	✓	263 29
			998	1003	✓	✓	50 90
			999	1004	✓	✓	160 14
			1000	1005	✓	✓	30 89
			1001	1006	✓	✓	36 83
			1002	1007	✓	✓	18 14
2/28			1003	1008	Wet Scraps	✓	513 97
			1004	1009	Scrap	✓	120 35
			1005	1010	✓	✓	89 59
2/29	3/2		1006	1011	Bars	So Dakota	5 580 13
			1007	1012	Scrap	Ind	102 96
			1008	1013	Button	✓	2 95
	3/6		1009	1014	Retort	Jefferson	24 33
3/1	3/7		1010	1015	Scrap	Ind	3 81
3/4	3/6		1011	1016	Bars	Nevada	5 272 33
	3/7		1012	1017	Scrap	Ind	9 43
			1013	1018	Bars	So Dakota	2 144 26
			1014	1019	✓	✓	3 882 99
			1015	1020	Scrap	Ind	193 93
			1016	1021	✓	✓	506 82
			1017	1022	✓	✓	514 20
	3/6		1018	1023	✓	✓	37 49
			1019	1024	✓	✓	366 60
	3/8		1020	1025	✓	✓	59 78
			1021	1026	✓	✓	383 55
	3/7		1022	1027	Retort	Adams	18 28
			1023	1028	✓	Jefferson	29 09
3/5	3/8		1024	1029	Scrap	Ind	989 97

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 997 °	1 °	2 °	0			\$	\$ Motorola	\$ Phoenix,	\$ Ariz
✓ 994 °	0 °	6 °	6				✓	✓	
✓ 974 °	1 °	25 °	6				✓	✓	
✓ 991 ½	0 °	8 ½	6				✓	✓	
✓ 990 °	0 °	10 °	6				✓	✓	
✓ 985 °	0 °	15 °	6				✓	✓	
✓ 880 ½	1 °	118 ½	13			2 ³⁰ x ¹⁰⁰	✓	✓	
✓ 993 °	0 °	7 °	6			2 ³⁰ x ¹⁰⁰	✓	✓	
✓ 420 ½	110 °	469 ½	18			8 ³⁰ x ¹⁰⁰	Suttons Quatonna, Minn		
✓ 514 °	62 °	424 °	21				O.C. Tanner, Inc. Salt Lake City, Utah		
✓ 569 °	76 °	355 °	21				Selco, Inc., Tulsa, Okla		
✓ 997.7	2.3	0 °	0				Homestake		
✓ 572 °	102 °	326 °	18				Louis W. Spiegel, Caroga Park, Cal		
✓ 885 ½	31 °	83 ½	13				Techmanis Corp. Salt Lake City, Utah		
✓ 890 °	104 °	6 °	12				Robert B. Ray & Suburban Metal Co. Black Hawk Colo.		
✓ 664 ½	162 °	173 ½	16				Dr. T.R. Queeggenom, Denver, Colo.		
✓ 993.5	2.5	4.0	6				Carlin Gold Mining Co. Elko, Nev.		
✓ 342 °	82 °	576 °	21				Samuel Schmarer, Chicago, Ill		
✓ 998 °	2 °	0 °	0				Homestake		
✓ 997 ¼	2 ¾	0 °	0				✓		
✓ 420 °	95 °	485 °	18			4 ⁵⁵ x ¹⁰⁰	John Roberts Mfg. Norman, Okla		
✓ 907 ½	3 °	89 ½	13				Motorola Phoenix Ariz		
✓ 896 ½	4 °	99 ½	13				✓	✓	✓
✓ 992 °	0 °	8 °	6				✓	✓	✓
✓ 993 °	0 °	7 °	6				✓	✓	✓
✓ 463 °	126 °	411 °	16			2 ³⁰ x ¹⁰⁰	S.W. Smalley & Ref. Dallas, Tex		
✓ 540 ½	88 °	371 ½	21				✓	✓	✓
✓ 908 °	86 °	6 °	12				Kirkling & Slenaker, Lakewood, Colo		
✓ 859 ½	135 °	5 ½	12				✓	✓	✓
✓ 393 °	120 °	487 °	18				Suttons Quatonna, Minn		

REGISTER OF ASSAYS,

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
3/5	3/7		1025	1030	Scrap	Ind	886 33
			1026	1031	Wet ✓	✓	346 71
			1027	1032	Scrap	✓	630 65
			1028	1033	✓	✓	598 92
	3/8		1029	1034	✓	✓	130 96
			1030	1035	✓	✓	422 57
			1031	1036	✓	✓	296 18
			1032	1037	✓	✓	886 36
			1033	1038	✓	✓	780 43
3/6	3/11		1034	1039	✓	✓	627 63
	→ GB	GB-8	GB-8	Gains Bar	Gains for Month Felt		32 50
	→ SB	SB-10	SB-10	Surplus Bullion	Swaps Cellar Metalico		414 17
	3/12		1035	1040	Scrap	Ind	467 65
			1036	1041	Bars	So Dakota	3981 23
			1037	1042	Scrap	Ind	234 98
			1038	1043	✓	✓	890 4
3/7			1039	1044	✓	✓	141 23
			1040	1045	✓	✓	87 76
			1041	1046	✓	✓	394 48
3/12			C-60	C-63	Au Coins	1-5 Peso	0 40
			C-61	C-64	+ Jewelry	1-10 ✓ 3-5 Peso 20-2 ✓ 1-Austrian	3 44
			C-62	C-65	Au Coin	1-5 Peso 1-Pendant	0 13
			C-63	C-66	Au Coin + Jewelry	2-5 Peso 2-2 1/2" ✓ 2-Turks	2 76
	3/13		C-64	C-67	Au Coin	1-20 Peso	0 53
			C-65	C-68	✓	2-10 Peso 1-20 ✓	1 06
3/7	3/15		1042	1047	Retort	Adams	26 16
3/8	3/13		1043	1048	Bars	So Dakota	2094 45
			1044	1049	✓	✓	3072 35
3/11	3/15	SB	SB-11	SB-11	Surplus Bull	3rd Quarterly Cleanup	21 07
	3/13	SB	SB-12	SB-12	✓	From K" Grams #8	57 93

Au. Pr. m. h.
2/5/68
J. m. m. h.
C-47-C50
C-47-C50

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 403 $\frac{1}{2}$	129 $\frac{0}{2}$	467 $\frac{1}{2}$	18			\$	Jostens	Owatonna	Min
✓ 422 $\frac{0}{2}$	112 $\frac{0}{2}$	466 $\frac{0}{2}$	18			680 x Lm	✓	✓	✓
✓ 405 $\frac{1}{2}$	191 $\frac{0}{2}$	403 $\frac{1}{2}$	16				✓	✓	✓
✓ 396 $\frac{1}{2}$	104 $\frac{0}{2}$	519 $\frac{1}{2}$	18				✓	✓	✓
✓ 411 $\frac{1}{2}$	106 $\frac{0}{2}$	482 $\frac{1}{2}$	18			305 x Lm	✓	✓	✓
✓ 393 $\frac{0}{2}$	108 $\frac{0}{2}$	499 $\frac{0}{2}$	18				✓	✓	✓
✓ 421 $\frac{1}{2}$	115 $\frac{0}{2}$	463 $\frac{1}{2}$	18			605 x Lm	✓	✓	✓
✓ 399 $\frac{0}{2}$	110 $\frac{0}{2}$	491 $\frac{0}{2}$	18				✓	✓	✓
✓ 397 $\frac{0}{2}$	109 $\frac{0}{2}$	494 $\frac{0}{2}$	18				✓	✓	✓
✓ 396 $\frac{1}{2}$	93 $\frac{0}{2}$	510 $\frac{1}{2}$	18				1 ✓	Princeton, Ill	
✓ 829 $\frac{0}{2}$	56 $\frac{0}{2}$	115 $\frac{0}{2}$	0				Supt	U.S. Mint - Denver	
✓ 25 $\frac{1}{2}$	270 $\frac{0}{2}$	704 $\frac{1}{2}$	0				✓	✓	✓
✓ 399 $\frac{1}{2}$	121 $\frac{0}{2}$	479 $\frac{1}{2}$	18			755 x Lm	Jostens	Princeton, Ill.	
✓ 997 $\frac{1}{2}$	2 $\frac{1}{2}$	0 $\frac{0}{2}$	0				Homestake		
✓ 428 $\frac{1}{2}$	126 $\frac{0}{2}$	445 $\frac{1}{2}$	16				A. L. Thorp,	Deadwood, S. D. K.	
✓ 476 $\frac{1}{2}$	62 $\frac{0}{2}$	461 $\frac{1}{2}$	18			305 x Lm	Fashion Craft Mfg Co, Inc	Buffalo, N.Y.	
✓ 425 $\frac{1}{2}$	108 $\frac{0}{2}$	466 $\frac{1}{2}$	18				Jostens	Owatonna, Min	
✓ 326 $\frac{1}{2}$	90 $\frac{0}{2}$	583 $\frac{1}{2}$	21			605 x Lm	✓	✓	✓
✓ 394 $\frac{0}{2}$	111 $\frac{0}{2}$	495 $\frac{0}{2}$	18						
✓ 900 $\frac{0}{2}$	0 $\frac{0}{2}$	100 $\frac{0}{2}$	13				Harry J. Adams	Buffalo, N.Y.	
✓ 900 $\frac{0}{2}$	32 $\frac{0}{2}$	68 $\frac{0}{2}$	13				Dally Ofie	Brooklyn, N.Y.	
✓ 900 $\frac{0}{2}$	0 $\frac{0}{2}$	100 $\frac{0}{2}$	13				LeRoy W. Goyer	San Antonio, Tex	
✓ 913.8 $\frac{0}{2}$	0 $\frac{0}{2}$	86.2	13				Rose Wlado	Newark, N. J.	
✓ 900 $\frac{0}{2}$	0 $\frac{0}{2}$	100 $\frac{0}{2}$	13				Dr. Matthew J. Bichele	San Augustine, Tex	
✓ 900 $\frac{0}{2}$	0 $\frac{0}{2}$	100 $\frac{0}{2}$	13				Mrs. George W. Lamborn	Chicago, Ill	
✓ 848 $\frac{1}{2}$	109 $\frac{0}{2}$	42 $\frac{1}{2}$	12				Kerkham & Shuker,	St. Edward, Colo	
✓ 997 $\frac{0}{2}$	3 $\frac{0}{2}$	0 $\frac{0}{2}$	0				Homestake		
✓ 998 $\frac{0}{2}$	2 $\frac{0}{2}$	0 $\frac{0}{2}$	0				✓		
✓ 457 $\frac{1}{2}$	84 $\frac{0}{2}$	458 $\frac{1}{2}$	0				Supt		
✓ 457 $\frac{1}{2}$	86 $\frac{0}{2}$	426 $\frac{1}{2}$	0				✓		

REGISTER OF ASSAYS,

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
3/8	3/15		1045	1050	Scrap	Ind	618.80
3/11			1046	1051	✓	✓	35.57
3/12	3/18		1047	1052	Bars	So Dokata	5700.75
3/12			1048	1053	Scrap	Ind	302.50
			1049	1054	✓	✓	318.65
			1050	1055	✓	✓	271.99
			1051	1056	✓	✓	149.46
			1052	1057	✓	✓	332.69
			1053	1058	✓	✓	18.01
			1054	1059	✓	✓	69.64
			1055	1060	✓	✓	115.78
			1056	1061	✓	✓	6.24
3/13			1057	1062	Wet ✓	✓	455.42
			1058	1063	Scrap	✓	549.55
			1059	1064	✓	✓	744.70
			1060	1065	✓	✓	421.48
3/15	3/20		1061	1066	Bars	So Dokata	1693.52
			1062	1067	✓	✓ ✓	4101.83
	3/22		1063	1068	Scrap	Ind	5.08
	3/22		1064	1069	Scrap	Ind	509.56
			1065	1070	✓	✓	499.05
			1066	1071	✓	✓	527.80
	3/21		1067	1072	✓	✓	479.33
			1068	1073	✓	✓	472.02
			1069	1074	✓	✓	501.03
	3/22		1070	1075	✓	✓	83.22
	3/21		1071	1076	✓	✓	160.20
			1072	1077	✓	✓	497.65
	3/22		1073	1078	✓	✓	55.02
			1074	1079	✓	✓	245.98

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 942 $\frac{1}{2}$	5°	52 $\frac{1}{2}$	13			45.48 $\frac{1}{2}$ C+D $\frac{1}{2}$ Chg 755 $\frac{1}{2}$ Lm	Crosby Porcelain Co. ^{\$} Gldon, ^{\$} Colo.		
✓ 860°	97°	43°	12				Motwola Scottsdale, Ariz		
✓ 997.6	2.4	0.0	0				Homestake		
✓ 808°	8°	184°	16			530 $\frac{1}{2}$ Lm	Motwola Phoenix, Ariz		
✓ 831 $\frac{1}{2}$	6°	162 $\frac{1}{2}$	16			530 $\frac{1}{2}$ Lm	✓	✓	✓
✓ 781 $\frac{1}{2}$	9°	209 $\frac{1}{2}$	16			455	✓	✓	✓
✓ 996 $\frac{1}{2}$	0°	3 $\frac{1}{2}$	0				✓	✓	✓
✓ 889°	1°	110°	13				✓	✓	✓
✓ 325°	1°	674°	23			230 $\frac{1}{2}$ Lm	✓	✓	✓
✓ 997°	1°	2°	0				✓	✓	✓
✓ 559°	52°	389°	21				Kuehner's Kayner Diamond Co ^{min.} Minn.		
✓ 720°	141°	139°	13				Dr. J. W. King, Aberdeen, So Dakota		
✓ 418 $\frac{1}{2}$	112°	469 $\frac{1}{2}$	18			755 $\frac{1}{2}$ Lm	Jostens, Owatonna, Minn.		
✓ 407 $\frac{1}{2}$	121°	471 $\frac{1}{2}$	18				✓	✓	✓
✓ 407°	131°	462°	18				✓	✓	✓
✓ 347 $\frac{1}{2}$	130°	522 $\frac{1}{2}$	18				✓	✓	✓
✓ 997 $\frac{1}{4}$	2 $\frac{3}{4}$	0°	0				Homestake		
✓ 998 $\frac{1}{4}$	1 $\frac{3}{4}$	0°	0				✓		
524 $\frac{1}{2}$	86°	389 $\frac{1}{2}$	21				Larry McKay, Flagstaff, Ariz		
✓ 877 $\frac{1}{2}$	4°	118 $\frac{1}{2}$	13			680 $\frac{1}{2}$ Lm	Motwola Phoenix, Ariz		
✓ 864 $\frac{1}{2}$	5°	130 $\frac{1}{2}$	13			680 $\frac{1}{2}$ Lm	✓	✓	✓
✓ 901 $\frac{1}{2}$	2°	96 $\frac{1}{2}$	13			680 $\frac{1}{2}$ Lm	✓	✓	✓
✓ 982°	2°	16°	6				✓	✓	
✓ 865 $\frac{1}{2}$	4°	130 $\frac{1}{2}$	13			680 $\frac{1}{2}$ Lm	✓	✓	
✓ 870°	2°	128°	13			680 $\frac{1}{2}$ Lm	✓	✓	
✓ 932°	1°	67°	13				✓	✓	
✓ 994 $\frac{1}{2}$	1°	4 $\frac{1}{2}$	6				✓	✓	
✓ 858°	4°	138°	13			680 $\frac{1}{2}$ Lm	✓	✓	
✓ 385 $\frac{1}{2}$	4°	610 $\frac{1}{2}$	21				✓	✓	
✓ 865°	4°	131°	13			455 $\frac{1}{2}$ Lm	✓	✓	

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930900

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
3/15	3/22		1075	1080	Scrap	Ind	509.98
	3/21		1076	1081	✓	✓	120.12
			1077	1082	✓	✓	96.31
			1078	1083	✓	✓	223.46
			1079	1084	✓	✓	62.76
3/18	3/20		1080	1085	Bars	Nevada	5958.66
		SB	SB-13	SB-13	Scraps	Behind Turnarous	97.75
3/19	3/21		1081	1086	Scrap	Ind	648.57
			1082	1087	✓	✓	849.75
			1083	1088	✓	✓	364.87
3/25			1084	1089	mut ag Cairn	16 Ag Dollars	12.74
			1085	1090	✓	260 1/2# 2266 1/10# 710 1/4#	428.27
3/22	3/26		C-66	C-69	Am Coins	1-2 1/2 Peso	0.86
			C-67	C-70	✓	1-2 Peso 1-2 1/2 " 1-5 "	0.25
			C-68	C-71	✓	1-50 " 5-10 "	2.67
3/26	3/28		1086	1091	Scrap	Ind	502.17
			1087	1092	✓	✓	444.45
			1088	1093	✓	✓	426.53
			1089	1094	✓	✓	255.87
			1090	1095	✓		29.32
3/22			C-69	C-72	Am Coins	20-50 Peso	46.57
3/28	4/1		C-70	C-73	✓	37-20 " 1-20 Peso	0.53
			C-71	C-74	✓	2-50 ✓ 2-2 1/2 Peso 1-10 ✓ 1-20 ✓	3.93
			C-72	C-75	✓	1-10 Peso	0.27
			C-73	C-76	✓	5-2 1/2 Peso	0.33
			C-74	C-77	✓	1-20 Peso	0.53
			C-75	C-78	✓	1-4 Ducat 3-1 ✓	0.78
				C-79	✓	1-2 1/2 Peso	0.06
3/29	4/1	GB	C-76	C-80	✓	1-5 Peso	0.13
			GB-9	GB-9	Spain Bar	March Deposit Am Coins 54-C 68	30.65

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 865 $\frac{1}{2}$	4 °	130 $\frac{1}{2}$	13			6 ⁸⁰ X Lm	\$ Motorola	\$ Phoenix	\$ Ariz
✓ 914 °	0 °	26 °	6				✓	✓	
✓ 993 °	1 °	6 °	6				✓	✓	
✓ 953 °	2 °	45 °	6				✓	✓	
✓ 986 $\frac{1}{2}$	1 °	12 $\frac{1}{2}$	6				✓	✓	
✓ 994.9	2.1	2.0	6				Carlin Gold Mng Elko, Nev-		
✓ 462 $\frac{1}{2}$	96 °	441 $\frac{1}{2}$	0				Supt		
✓ 392 $\frac{1}{2}$	104 °	503 $\frac{1}{2}$	18				Josten's Promitor, Ill		
✓ 393 °	111 °	496 °	18				✓	✓	✓
✓ 564 °	93 °	343 °	18				✓	✓	✓
✓ 0 °	917 °	83 °	0				Supt		
✓ 0 °	864 $\frac{1}{2}$	135 $\frac{1}{2}$	0				✓		
✓ 900 °	0 °	100 °	13				Mrs Thelma Denton, Corsicana, Tex		
✓ 900 °	0 °	100 °	13				William Deale, Blount Hill, Maryland		
✓ 900 °	0 °	100 °	13				Paul Tedder, Morgan City, La		
✓ 987 $\frac{1}{2}$	2 °	10 $\frac{1}{2}$	6				Motorla, Phoenix Ariz		
✓ 990 °	0 °	10 °	6				✓	✓	✓
✓ 569 °	7 °	424 °	21			6 ⁰⁵ X Lm	✓	✓	✓
✓ 999 °	0 °	1 °	0				✓	✓	✓
✓ 998 $\frac{1}{2}$	0 °	1 $\frac{1}{2}$	0				✓	✓	✓
✓ 900 °	0 °	100 °	13				Antonio F. Karam, McAllen, Texas		
✓ 900 °	0 °	100 °	13				Dr. A. Horton Smith, Ft. Huachuca Ariz		
✓ 900 °	0 °	100 °	0				Port Director of Customs, Hidalgo, Texas		
✓ 900 °	0 °	100 °	0				Dist Dir Customs, El Paso, Tex		
✓ 900 °	0 °	100 °	0				Bureau of Customs, Dallas, Tex		
✓ 900 °	0 °	100 °	0				✓	✓	✓
✓ 985 °	0 °	15 °	0				Dist Dir Customs, Minn, Minn		
✓ 900 °	0 °	100 °	0				✓	✓	✓
✓ 900 °	0 °	100 °	13				Mark Eugene Hommer, Bentonwood, Mo.		
✓ 779 $\frac{1}{2}$	58 °	162 $\frac{1}{2}$	0				Supt		

REGISTER OF ASSAYS,

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
3/28	4/1		1091	1096	Scrap	Ind	90.73
			1092	1097	✓	✓	242.06
4/2	4/3	SB	SB-14	SB-14	S.B.	From "K" Grains 9	44.58
4/1	4/4		1093	1098	Scrap	Ind	391.66
			1094	1099	✓	✓	398.17
			1095	1100	✓	✓	333.84
			1096	1101	✓	✓	231.02
			1097	1102	✓	✓	555.06
			1098	1103	✓	✓	99.46
4/2	4/11		1099	1104	Bars	✓	3.84
4/8			1100	1105	Scrap	✓	532.35
4/10			1101	1106	Au. Wafers	✓	49.96
4/16	DML 4/12/68		C-77	C-81	Au. Coin	1-2 1/2 Peso	0.06
4/18	DML 4/17/68		C-78	C-82	Coin	1-Canadian Ag Dollar Gold Plated	0.74
4/23	" 4/19 "		C-79	C-83	✓	1-20 Peso mex	0.53
	4/25 "		C-80	C-84	✓	1-2 ✓ ✓	0.05
	" "		C-81	C-85	✓	1-2 ✓ ✓	0.11
	" "		C-82	C-86	✓	1-10 Sueros Ecuadorian Gold	0.25
4/25	4/26		1102	1107	Ag Coin	14-Mut Ag S.S. Dollars	10.78
			1103	1108	✓	Mut Coin 615 1/10 \$	95.60
	5/6		1104	1109	Scrap	Ind	568.95
			1105	1110	✓	✓	564.96
			1106	1111	✓	✓	545.55
			1107	1112	✓	✓	544.87
			1108	1113	✓	✓	565.52
			1109	1114	✓	✓	748.93
			1110	1115	✓	✓	556.20
4/26	5/3		1111	1116	✓	✓	44.27
	5/1		C-83	C-87	Au. Coin	2 Venezuelan Coins	1.42
			C-84	C-88	✓	2 mut millian Gold Coins	0.02

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 416 °	68 °	516 °		18		\$	\$ Wellbar Casting Co. Inc, Buffalo, N.Y.		
✓ 412 1/2	107 °	480 1/2		18		455 ⁵⁰ Lm	✓	✓	✓
✓ 460 1/2	89 °	450 1/2		0			Supt		
✓ 979 °	1 °	20 °		6			Motorola	Phoenix	Ariz
✓ 950 1/2	5 °	44 1/2		6			✓	✓	✓
✓ 894 °	0 °	106 °		13			✓	✓	✓
✓ 989 1/2	0 °	10 1/2		6			✓	✓	✓
✓ 989 °	0 °	11 °		6			✓	✓	✓
✓ 770 °	5 °	225 °		16		305 ⁵⁰ Lm	✓	✓	✓
✓ 999 °	0 °	1 °		0			John C. Bacon, Dallas, Texas		
✓ 916 1/2	3 °	80 1/2		13		C & D & Co. 194 ⁵⁰ 830 ⁵⁰ Lm	Coors Porcelain Co. Golden, Colo		
✓ 999 °	0 °	1 °		0			Dist Div Customs, Duluth, Minn.		
✓ 900 °	0 °	100 °		13			Miss Dorothy Jannin, Tucson, Ariz		
✓ 999 798 °	202 °			0			Bureau of Customs, Duluth, Minn.		
✓ 900 °	0 °	100 °		0			"	"	Houston, Tex
✓ 900 °	0 °	100 °		0			"	"	Dallas, Tex
✓ 900 °	0 °	100 °		0			"	"	"
✓ 900 °	0 °	100 °		17			Lester M. Reeks, Houston, Tex		
✓ 0 °	869 1/2	130 1/2		0			Supt		
✓ 0 °	895 1/4	104 3/4		0			Supt		
✓ 932 °	1 °	67 °		17			Motorola	Phoenix, Ariz	
✓ 937 °	1 °	62 °		17			✓	✓	✓
✓ 934 °	2 °	64 °		17			✓	✓	✓
✓ 936 1/2	2 °	61 1/2		17			✓	✓	✓
✓ 932 1/2	1 °	66 1/2		17			✓	✓	✓
✓ 920 1/2	1 °	78 1/2		17			✓	✓	✓
✓ 932 °	1 °	67 °		17			✓	✓	✓
✓ 943 °	211 °	446 °		23		300 ⁵⁰ Lm	Norman Berndt Mfg Jeweler		
✓ 899 1/2	75 °	25 1/2		17 ⁵⁰			Bureau of Customs, Dallas, Tex		
✓ 884 °	9 °	107 °		21			Tony Vile, Brooklyn, N.Y.		

Dale & Kelly,
Utah

End Fiscal '68

Form 123
TREASURY DEPARTMENT
MINT SERVICE

REGISTER OF ASSAYS,

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
5/1			GB 10	GB 10	Grains Bar	Dep mo of April plus AuCoins C-72-C86	65.59
5/3			SB 15	SB-15	Surplus Bullion	Was "K" Grains 10	47.57
5/8	5/16		C-85	C-89	Coins	1-50 Peso mex 2-20 v	2.40
5/22	5/24		1112	1117	Ag Coin	197 melted S.S. & mut. Ag Coin	15.88
			1113	1118	✓	184 1/2# 339 1/4# 800 1/2#	202.12
6/6	6/10		S.R. Rec 16	16	S.B.	Magnetic material removed from deposits	12.28
✓			SB 17	17	S.B.	4th Quarterly Ship Inspection	8.31
✓			GB 11	11	G.B.	Grains deposits may C-87, C-88, C-89	9.07
✓	3 PM 6/11		1114	1119	Scrap	Ind	519.07
			1115	1120	✓	✓	511.43
			1116	1121	✓	✓	494.32
			1117	1122	-	✓	534.08
	6/11		1118	1123	✓	✓	520.31
			1119	1124	-	✓	550.28
			1120	1125	✓	✓	524.10
			1121	1126	✓	✓	494.70
			1122	1127	✓	✓	542.27
			1123	1128	✓	✓	321.41
6/10			SB 18	18	S.B.	"K" Grains #11	91.38
			SB 19	19	S.B.	"K" Grains #12	23.72
6/12			SB 20	20	S.B.	From C & D metal #7	2.96
6/13	D.M. L... 6/10/68		1124	1129	Scrap	Gold Ring	0.64
	" "		C-86	C-90	Au Coin	1-50 Peso mex	0.18
	" "		C-87	C-91	✓	1-2 v 1-50 Peso mex	0.13
6/18			SB 21	21	A.B.	Forfeited Items	1.99
			GB 12	12	G.B.	Grains - June Deposit + C90, C91	5.17

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 888 $\frac{1}{2}$	15°	96 $\frac{1}{2}$		0		\$	\$ Supt	\$ U.S. mint, Denver	\$
✓ 475 $\frac{1}{2}$	77°	447 $\frac{1}{2}$		0			✓	✓	✓
✓ 900°	0°	100°		17			Sack Hart, Pauls Valley, Okla		
✓ 0°	923 $\frac{1}{2}$	76 $\frac{1}{2}$		0			Supt. U.S. mint, Denver		
✓ 0°	856 $\frac{3}{4}$	143 $\frac{1}{4}$		0			✓	✓	✓
✓ 406 $\frac{1}{2}$	189°	404 $\frac{1}{2}$		0			Supt.		
✓ 441 $\frac{1}{2}$	64°	494 $\frac{1}{2}$		0			✓		
✓ 894 $\frac{1}{2}$	36°	69 $\frac{1}{2}$		0			✓		
✓ 884°	3°	113°		21		900 x L	Matamoras		
✓ 887°	2°	111°		21		900 x L	✓		
✓ 846 $\frac{1}{2}$	4°	149 $\frac{1}{2}$		21		900 x L	✓		
✓ 900°	2°	98°		17		900 x L	✓		
✓ 888 $\frac{1}{2}$	4°	107 $\frac{1}{2}$		21		900 x L	✓		
✓ 933 $\frac{1}{2}$	2°	64 $\frac{1}{2}$		17			✓		
✓ 896 $\frac{1}{2}$	2°	101 $\frac{1}{2}$		21		900 x L	✓		
✓ 844 $\frac{1}{2}$	5°	150 $\frac{1}{2}$		21		900 x L	✓		
✓ 922°	3°	75°		17			✓		
✓ 836°	5°	159°		21		700 x L	✓		
✓ 477 $\frac{1}{2}$	89°	433 $\frac{1}{2}$		0			Supt		
✓ 456 $\frac{1}{2}$	83°	460 $\frac{1}{2}$		0			✓		
✓ 389°	141°	470°		0			Supt		
✓ 769°	120°	171°		21			Bureau Customs, Brownsville Tex		
✓ 900°	0°	100°		17			✓	✓	✓
✓ 900°	0°	100°		17			✓	✓	✓
✓ 520 $\frac{1}{2}$	189°	290 $\frac{1}{2}$		0			Supt. U.S. mint Denver		
✓ 899 $\frac{1}{2}$	5°	95 $\frac{1}{2}$		0			✓	✓	✓

Jiscal '69 Start

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930000

DATE 1968			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
7/2	D.M.L.	6/28/68	C-1	C-1	au. Coin	1-2 1/2 Peso 1-20 Peso 1-5 v 1-10 v	1.00
7/10	✓	✓	1	1	Ind	1- Bracelet	1.58
7/15	7/17	DML 7/10/68	C-3	C-3	Au Coin	1-Bz Sovereign	0.12
	✓	DML 7/10/68	C-3	C-4	✓	1-2 1/2 Peso mex	0.06
7/24	7/29		2	2	ag Coin	17 Mut S.S. \$	12.98
			3	3	✓	mut: 240 1/2 \$, 498 1/4 \$ 989 1/10 \$	258.49
7/15	7/31	D.M.L. 7/10/58	C-2	C-2	Coins	6- Au Washed Canadian Silver Dollars	4.45
7/23		SB	1	1	Surplus Bullion	Sweep Cellar Metallics	196.23
8/2	8/12		4	4	Scrap	Ind	30.14
8/6		GB	1	1	Grains	July Grains + C-1 + C-3	1.39
8/8	7/22/68	F.M.V.	C-4	C-5	Points	2-2 Peso 5-2 1/2 Peso 1-5 Peso	1.38
8/12	7/31/68	D.M.L.	5	5	Spinel Ag	5032G745	980.00
			✓	✓	✓	Record Plz Contact CMF68-3	267.81
			✓	✓	✓	746	267.81
			✓	✓	✓	747	1021.57
			✓	✓	✓	748	1021.64
			✓	✓	✓	749	1016.43
			✓	✓	✓	750	1016.55
8/20	8/23		6	6	Scrap	Ind	975.95
8/23	8/29	DML 8/19/68	C-5	C-6	Au. mex Coins ag Coin	1-50 Cordobas, 1-20 P. 3-10 P. 2-2 1/2 P. 22-2 1/2 P. 132 Mut S.S. \$	207.00
			7	7		mut: 1248 1/2 \$ 2514 1/4 \$ 7528 1/10 \$	267.00
8/27	9/6		9	9	Scrap	Ind	267.00
			10	10	✓		267.00
			11	11	✓		267.00
9/3			12	12	✓		267.00
			13	13	✓		267.00
		GB	2	2	Grains	August Grains + Au Coins C2, C5, C6	267.00
9/13	9/24		14	14	Scrap	Ind	267.00
9/18	9/23		15	15	✓		267.00
9/16	9/27		16	16	ag Coin	mut S.S. \$ 111	267.00

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 900 °	0 °	100 °	17			\$	\$	\$	\$
✓ 723 ½	81 °	195 ½	21				Port. Dept. Customs, Brownsville, Tex		
✓ 916 °	0 °	84 °	17				✓	✓	✓
✓ 900 °	0 °	100 °	17				✓	✓	✓
✓ 0 °	916 °	84 °	0				Waldags, Tex		
✓ 0 °	876 °	124 °	0				✓	✓	✓
✓ 0 °	799 °	201 °	12				Supt, U.S. Mint - Denver		
✓ 107 °	132 °	761 °	0				✓	✓	✓
✓ 430 °	107 °	463 °	23			3 ⁰⁰ x Lm	Bureau of Customs, Duluth, Minn.		
✓ 780 °	136 °	84 °	0				Supt, U.S. Mint, Denver, Colo.		
✓ 900 °	0 °	100 °	0				Norman Bernhardt, Salt Lake City, Utah		
0 °	999 °		0				Supt, U.S. Mint - Denver		
0 °	999 ½		0				Bureau of Customs, Nogales, Arizona		
0 °	999 ½		0				Kennecott Copper Corp, Salt Lake City, Utah		
0 °	999 ½		0				Garfield, N.M.		
0 °	999 ½		0				✓		✓
0 °	999 ½		0				✓		✓
0 °	999 ½		0				✓		✓
0 °	999 ½		0				✓		✓
0 °	999 ½		0				✓		✓
✓ 543 ½	90 °	366 ½	30				S.W. Texas Precious Metals, San Antonio, Tex		
✓ 892 ½	17 °	90 ½	0				Electrical Director, Lubbock, Texas		
✓ 0 °	898 ¾	101 ¼	0				Supt, U.S. Mint, Denver		
✓ 0 °	872 °	128 °	0				✓	✓	✓
✓ 556 ½	89 °	354 ½	30				Raymond Martinez, Phoenix, Ariz		
✓ 561 °	81 °	358 °	30				✓	✓	✓
✓ 490 ½	77 °	432 ½	23			3 ⁰⁰ x Lm	Star Jewelry Co, Inc, Houston, Tex		
✓ 429 °	75 °	496 °	23			4 ⁰⁰ x Lm	Triad Manufacturing Group, Buffalo, N.Y.		
✓ 451 °	91 °	458 °	23			3 ⁰⁰ x Lm	Star Jewelry Co, Inc, Houston, Tex		
✓ 484 ½	371 °	144 ½	0				Supt, U.S. Mint, Denver, Colo		
✓ 501 °	95 °	344 °	30				Bergert & Co, Houston - Texas		
✓ 447 ½	81 °	471 ½	23				Louis W. Spiegel, Canoga Park, Calif		
✓ 0 °	898 ½	101 ½	0				Supt, U.S. Mint, Denver		

REGISTER OF ASSAYS,

DATE 1968-1969			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
9 26	9 27		17	17	Ag. Coin	mut Ag Coin 888 1/2 \$, 2620 1/4 \$ 12.794 1/10 \$	2 015 30
9 30	10 4		18	18	Scrap	Incl	70 41
10 3		GB	3	3	Grains	Grains from Sept Deposits	304
10 25	10 28		19	19	ag Coin	mut Ag Coin 62-S.S. \$	49 86
			20	20	"	mut Ag Coin 367 1/2 \$ 679-1/4 \$ 2272-1/10 \$	445 13
11 22			21	21	Ag Coin	mut Ag Coin 8-S.S. \$	5 78
			22	22	"	mut Ag Sub Coin 55 1/2 \$, 259-1/4 \$, 624-1/10 \$	120 56
" 26	12 6	DML 11/20/68	C-6	C-7	Au. Coin	4-2 Peso Mex	0 21
12 10	12 9	DML 12/1/68	C-7	C-8	✓	2-50 Peso Mex	2 68
12 12	12 13	DML 12/9/68	C-8	C-9	✓	1-50 Peso Mex 1-10 ✓ ✓	0 39
12 16	12 17	DML 12/9/68	C-10	C-11	✓	1-2 1/2 U.S. Gold Coin	0 13
	12 19	"	C-9	C-10	✓	Covers 132 mut Au Coins these were melted	33 96
		"	23	23	Scrap	Jewelry	7 26
12 23	12 24		24	24	Ag. Coin	mut S.S. \$'s	4 78
			25	25	"	mut Coin: 121-1/2 \$'s 280-1/4 \$'s 543 1/10 \$'s	153 16
12 31	1/6/69	GB	4	4	Grains	Grains for Oct, Nov, Dec, 1968 Plus C-7, C-8, C-9, C-10, C-11	38 78
1/9/69	1/28		26	26	Scrap	Incl	78 31
1/22	"		27	27	✓	✓	551 21
1/24	"		28	28	Ag. Coin	mut S.S. \$'s (10)	8 12
"	"		29	29	✓	mut Ag Coin 21-1/2 \$, 88-1/4 \$, 248-1/10 \$	297 91
1/28	2/6	DML 2/24/69	C-11	C-12	Au Coin	2-2 peso Mex	0 10
"	"	"	C-12	C-13	✓	1-20 peso Mex	0 53
1/28	2/17	1/22/69	C-13	C-14	✓	1-50 Peso, 1-20 Peso, 1-10 Peso	3 05
2/13	"	DML 2/10/69	C-14	C-15	Au Coin	5-50 Peso, 6-2 1/2 Peso 1-50 Peso 1-20 ✓ 1-2 1/2 ✓	1 93
"	"	"	C-15	C-16	✓	3-20 Peso	0 15
"	2/18	"	C-16	C-17	✓	1-2 1/2 Peso	0 06
"	2/17	"	C-17	C-18	✓	1-10 Peso	0 26
2/20	2/24		30	30	Silver Coin	17-1/2 \$ 49 1/4 \$ 212-1/10 \$	114 10
3/3	3/7		31	31	Scrap	mut Ag Coins	772 78
3/5	"	GB	5	5	Grains	Incl Deposits for Jan, Feb 1969 Au Coins #12 thru #18	6 86

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 0°	887°	113°	0			\$	\$		\$
✓ 434°	72°	494°	23			400 x Lm	Supt. U.S. Mint, Denver		
✓ 145°	688°	167°	0				Triad Mfg. Group, Inc. Buffalo, N.Y.		
✓ 0°	898 1/4	101 3/4	0				Supt. U.S. Mint, Denver		
✓ 0°	897 1/2	102 1/2	0				✓	✓	✓
✓ 0°	900 3/4	99 1/4	0				✓	✓	✓
✓ 0°	897 3/4	102 1/4	0				✓	✓	✓
✓ 900°	0°	100°	0				Bureau Customs, San Antonio, Tex		
✓ 900°	0°	100°	0				District Director Customs, Houston, Tex.		
✓ 900°	0°	100°	0				Bureau of Customs, Dallas Tex		
✓ 900°	0°	100°	0				Bureau of Customs, Laredo, Tex		
✓ 899 1/2	3°	97 1/2	17				✓	✓	✓
✓ 411°	382°	207°	13				✓	✓	✓
✓ 0°	904 3/4	95 1/4	0				Supt. U.S. Mint, Denver, Colo		
✓ 0°	875 1/4	124 3/4	0				✓	✓	✓
✓ 886 1/2	14°	99 1/2	0				✓	✓	✓
✓ 625°	139°	236°	21				Carl Blaurock, Denver, Colo		
✓ 690°	67°	243°	21				William Pastor, DBA		
✓ 0°	900°	100°	0				Southwest Texas Precious Metals, San Antonio, Texas		
✓ 0°	843 1/2	156 1/2	0				Supt. U.S. Mint, Denver, Colo		
✓ 900°	0°	100°	0				✓	✓	✓
✓ 900°	0°	100°	0				Bureau Customs, Dallas, Tex		
✓ 900°	0°	100°	0				✓	✓	✓
✓ 900°	0°	100°	0				✓	✓	✓
✓ 900°	0°	100°	0				District Director Customs, El Paso, Tex		
✓ 900°	0°	100°	0				✓	✓	✓
✓ 894°	17°	99°	0				Bureau Customs, Dallas, Tex		
✓ 900°	0°	100°	0				District Director Customs, Laredo, Tex		
✓ 0°	662 1/4	337 3/4	0				Supt. U.S. Mint, Denver		
✓ 536°	112°	352°	30				William Pastor, DBA		
✓ 861	36°	103°	0				Southwest Texas Precious Metals, San Antonio, Tex		
							Supt. U.S. Mint, Denver, Colo		

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 230900

DATE 1969			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
3/6	3/27	DML 3/4/69	32	32	Sever Service	1 Bar + 13 Nuggets	38
"	3/28		33	33	Scrap	Ind	20.62
3/24	3/25		34	34	mut Ag Coins	4 Mut P.S. \$'s	2.61
"	"		35	35	mut Ag Coins	30-1/2 \$'s, 35-1/4 \$'s, 332-1/10 \$'s	56.36
4/11	4/23		36	36	Scrap	Ind	85.92
4/14	✓	DML 4/11	37	37	"	2-Gold Balls	1.78
	✓		38	38	"	Ind	856.23
4/24	4/25		39	39	mut Ag Coin	Mut: 10-S.S. \$'s	65.54
	"		40	40	✓	Mut: 13-1/2 \$'s, 163-1/4 \$'s, 307-1/10 \$'s	322.22
5/13	5/14	DML 5/8	C-18	C-19	Am Coin	6-500 U.S. Am Coins	1.54
		"	C-19	C-20	✓	1-100, 1-50, 1-20, 1-10, 1-5 Sole Peruvian Coins	2.77
5/12	5/26		41	41	Scrap	Dental, etc	777.62
	5/15		42	42	Scrap	2-Gold Bars	30.45
5/19	6/2		43	43	✓	Jewelry	1.26541
5/23	5/23		44	44	mut Ag Coin	68-Mut S.S. \$'s	55.76
			45	45	✓	129-1/2 \$'s, 657-1/10 \$'s, 252-1/4 \$'s	163.39
5/29	6/3		46	46	Scrap	Ind	49.74
6/6	6/9	GB	6	6	Seams	Seams for March, April, May	8.99
	✓	SB	3	3	Surplus Bullion	Same + Am Coins 18+19	10.52
6/4	✓	SB	2	2	✓	From C+D Muscl #4	803.11
		SB				Sweep Cellar Metallus	

GOLD AND SILVER DEPOSITS

← Total - 1969

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 809 $\frac{1}{2}$	164 °	26 $\frac{1}{2}$	0			\$	\$	\$	\$
							Secretary of Treasury, Wash. D.C.		
✓ 554 °	39 °	407 °	30			3 ⁰⁰ W. G.	Ed. Benjamin & Sons, San Diego, Calif		
✓ 0 °	910 $\frac{1}{2}$	89 $\frac{1}{2}$	0				Supt. U.S. mint - Denver, Colo		
✓ 0 °	834 °	166 °	0			✓	✓	✓	✓
✓ 643 °	174 °	183 °	21				Carl Blaurack - Denver, Colo		
✓ 857 °	140 °	3 °	0				Port Director of Customs, Douglas, Ariz.		
							William Pastge, DBA		
✓ 477 °	94 °	429 °	23				Southeast Prec Metals Co., San Antonio, Tex		
✓ 0 °	911 °	89 °	0				Supt. U.S. mint, Denver, Colo		
✓ 0 °	757 $\frac{1}{2}$	242 $\frac{1}{2}$	0			✓	✓	✓	✓
✓ 900 °	0 °	100 °	0				Rupert W. ^{myers} Meyers, Beaumont, Texas		
✓ 900 °	0 °	100 °	0				Bureau of Customs, San Antonio, Texas		
✓ 113 $\frac{1}{2}$	123 °	163 $\frac{1}{2}$	21			12 ⁰⁰ X Pm	Property Disposal Office, Pueblo, Colo.		
✓ 999 °	1 °	0 °	8				Pueblo Army Depot, Pueblo, Colo.		
✓ 398 $\frac{1}{2}$	103 °	498 $\frac{1}{2}$	23				Bureau of Stds, Boulder, Colo		
✓ 0 °	903 °	97 °	0				Star Engraving Co. - Houston - Texas		
✓ 0 °	899 °	101 °	0			✓	✓	✓	✓
✓ 469 °	135 °	396 °	23			3 ⁰⁰ Lm	Lm. Norman Bennett, Salt Lake City, Utah		
✓ 685 $\frac{1}{2}$	130 °	184 $\frac{1}{2}$	0				Supt. U.S. mint - Denver, Colo		
✓ 77 °	295 °	628 °	0			✓	✓	-	✓
✓ 339 °	86 °	575 °	0			✓	✓	-	✓

FISCAL-1970 →

Form 123
TREASURY DEPARTMENT
MINT SERVICE

REGISTER OF ASSAYS,

DATE 1969			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
7/1	7-11		1	1	Scrap Ind	Ind	674.5
7/3	✓		2	2	Dent	Ind	351.4
7/7	✓	DML 6/29/69	3	3	Scrap	Au Shavings	0.31
7/10	7/18		4	4	✓	Ind	42.4
7/14	7/24		5	5	✓	✓	Remelt = 3699.4
7/7	7/17	DML 6/29/69	C-1	C-1	au medal	Venezuelan	0.41
	✓	DML 6/26/69	C-2	C-2	Au Coin	1-10 Peso mex	0.21
7/8	✓	DML 7/3/69	C-3	C-3	✓	1-2 1/20 Peso mex 1-5 ✓ ✓	0.41
	✓	✓	C-4	C-4	✓	4-10 Peso mex	10.1
7/11	✓	DML 7/3/69	C-5	C-5	✓	1-20 Peso mex	0.52
7/24	7/25		6	6	Ag Coin	12-5.5. \$'s	9.4
7/25	7/25		7	7	✓	216-1/2 \$'s, 1085-1/10 \$	301.7
8/6	8/7	DML 8/4/69	C-6	C-6	✓	2-50 Peso mex	0.21
8/7	8/8	DML 6/17/69	8	8	1/2 Ag	Rare! Kennicott 14-144 S144E-434 Contract B90103M	25 225.1
✓	✓	✓	8	9	5- Gold	S145E-442 ✓	25 211.9
✓	✓	✓	8	10		S148E-518 ✓	7 482.14
✓	✓	✓	8	11		S158F-753 ✓	25 111.10
✓	✓	✓	8	12		S161F-825 ✓	25 039.50
8/21	8/25		9	13	Ag Coin	Mut 95.5. \$'s	7.53
	✓		10	14	✓	Mut Ag Coin	219.64
8/26	9/16		11	15	Scrap	65-1/2 \$, 193 1/4 \$, 986 1/10 \$'s	46.35
9/18	9/22		12	16	Ag Coin	Ind mut: 9, 3.5. \$'s	7.55
			13	17	✓	mut: 32-1/2 \$, 31-1/4 \$, 85-1/10 \$'s	34.51
	9/23	SB	1	1	S.B.	Seigns Cellas Metallico	277.51
		SB	2	2	✓	✓ ✓ ✓	468.32
		SB	3	3	✓	✓ ✓ ✓	454.78
		SB	4	4	✓	✓ ✓ ✓	318.67
	10/15		14	18	SCRAP	IND.	2436.78
10/16	10/20	DML 10/13/69	C-7	C-7	Au Coin	1-1 Pakhani Persian coin	0.26
10/23	10/24		17	21	Ag Coin	Mut: 5 S.S. \$	3.61

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
✓ 592 ⁰	93 ⁰	315 ⁰	30			\$	\$	William Pastor	\$
✓ 985 ⁰	2 ⁰	13 ⁰	8					South West Texas Pac. R.R. San Antonio, Tex	
✓ 897 ⁰	7 ⁰	96 ⁰	0					Property Disposal Office	
✓ 701 ¹ / ₂	125 ⁰	173 ¹ / ₂	21					Pueblo Army Depot, Pueblo, Colo	
✓ 398 ⁰	98 ⁰	504 ⁰	30			Bar & Chg. 73.19		Bureau Customs, El Paso, Texas	
✓ 897 ⁰	52 ⁰	51 ⁰	0					Ed. Benjamin and Sons, San Diego, Cal.	
✓ 900 ⁰	0 ⁰	100 ⁰	0					Star Engraving Company, Houston - Tex	
✓ 900 ⁰	0 ⁰	100 ⁰	0					Bureau Customs, Port Arthur, Tex	
✓ 900 ⁰	0 ⁰	100 ⁰	0					✓ ✓ , El Paso, Tex	
✓ 900 ⁰	0 ⁰	100 ⁰	0					Port Director Customs, Dallas, Tex	
✓ 900 ⁰	0 ⁰	100 ⁰	0					✓ ✓ ✓ ✓ ✓	
✓ 900 ⁰	0 ⁰	100 ⁰	0					✓ ✓ ✓ ✓ ✓	
RS 0 ⁰	911 ¹ / ₂	88 ¹ / ₂	0					Supt. U.S. Mint - Denver, Colo	
RS 0 ⁰	891 ⁰	109 ⁰	0					✓ r - r ✓	
✓ 900 ⁰	0 ⁰	100 ⁰	0					Bureau Customs, Dallas, Texas	
✓ 90 ⁰	999 ¹ / ₂	0 ¹ / ₂	0					Acct of: Treasurer of the United States	
✓ 0 ⁰	999 ¹ / ₂	0 ¹ / ₂	0					✓ ✓ ✓	
✓ 0 ⁰	999 ¹ / ₂	0 ¹ / ₂	0					✓ ✓ ✓	
✓ 0 ⁰	999 ¹ / ₂	0 ¹ / ₂	0					✓ ✓ ✓	
✓ 0 ⁰	999 ¹ / ₂	0 ¹ / ₂	0					✓ ✓ ✓	
RS 0 ⁰	904 ³ / ₄	95 ¹ / ₄	0					Supt. U.S. Mint - Denver, Colo	
RS 0 ⁰	893 ¹ / ₂	106 ¹ / ₂	0					✓ ✓ ✓ ✓	
✓ 548 ⁰	166 ⁰	286 ⁰	30					Carl Plaurack, Denver, Colo	
✓ 0 ⁰	902 ¹ / ₂	97 ¹ / ₂	0					Supt. U.S. Mint - Denver, Colo.	
✓ 0 ⁰	901 ³ / ₄	98 ¹ / ₄	0					r ✓ ✓ ✓	
✓ 79 ⁰	58 ⁰	863 ⁰	0					✓ ✓ ✓ ✓	
✓ 78 ⁰	59 ⁰	863 ⁰	0					✓ ✓ ✓ ✓	
✓ 35 ⁰	47 ⁰	918 ⁰	0					✓ ✓ ✓ ✓	
✓ 34 ¹ / ₂	46 ⁰	919 ¹ / ₂	0					✓ ✓ ✓ ✓	
✓ 193 ¹ / ₂	46 ⁰	760 ¹ / ₂	30			Wh. Tc Au 78.00		Star Engraving Co. Houston, Tex	
✓ 900 ⁰	0 ⁰	100 ⁰	0					Bureau of Customs, El Paso, Tex	
✓ 0 ⁰	900 ³ / ₄	99 ¹ / ₄	0					Supt U.S. MINT, Denver, Colo.	

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 230500

DATE 1969			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
10/23	10/24		18	22	Ag Coin	Mut: 55- $\frac{1}{2}$ \$, 120- $\frac{1}{4}$ A, 270- $\frac{1}{10}$ \$	124.3
10/24	11/3		15	19	Scrap	Ind.	45.0
10/24			16	20	Scrap	Ind.	389.8
10/24			19	23	silver Coins	67 Cuban + 1 Chinese Ag Coins	12.4
10/24	11/3	DMA 10/6/69	C-8	C-8	Sold Coin	32 Mex Au Coins - 3-1 U.S. Au coins 1 gold plated Kennedy $\frac{1}{2}$ \$, 1 bracelet, 6 Buzle	12.4
10/27	11/24		20	24	Scrap	Ind.	803.95
11/3	"		21	25	Scrap	1- Gold Button 1- Dent Scrap	0.07
11/13	"		22	26	au Bars	Gold Bars	1929.16
11/17	"		23	27	Scrap	Ind.	73.74
11/18	11/20		24	28	Mut ag coin	4 U.S. \$'s	332
"	"		25	29	✓	62- $\frac{1}{10}$ \$'s, 279- $\frac{1}{10}$ \$'s 114- $\frac{1}{4}$ \$'s	66.64
11/10	11/24	DML 11/5/69	C-9	C-9	au Coins	12- Mex Au Coins	0.78
"	"	"	C-10	C-10	✓	8- Foreign 7- U.S.	8.30
"	"	"	C-11	C-11	✓	11- Mex Coins & Jewelry Scrap	2.72
"	"	"	C-12	C-12	✓	1- Mex Au Coin	0.53
"	"	"	C-13	C-13	✓	4- Mex Coins	0.44
"	"	"	C-13	C-14	✓	1- Venezuela Gold Piece	0.64
11/26	12/1	11/5/69 11/20/69	C-14	C-15	✓	1- Canadian 5 ⁰⁰ = 0.264g 1- Russian 5 Roubles = 0.133g	0.39
"	12/3	"	26	30	Coins au Plated canadian	419 Dollars 41 Dimes 41 Quarters 41 Pennies all au Plated	339.18
"	"	"	27	31	✓	41 nickels } all au 41 Pennies } Plated	9.98
12/17	12/22		28	32	Scrap	Ind.	94.06
12/18	"		29	33	Mut ag coin	5- U.S. \$'s	3.79
"	"		30	34	"	27- $\frac{1}{2}$ \$'s 43- $\frac{1}{4}$ " 91- $\frac{1}{10}$ \$'s	25.72
12/23	1/7/70		31	35	Scrap	Ind.	738.38
12/31	"	SB	5	5	Surplus Bullion	Cleanup: Behind Immans	30.14
1/12/70	1/20	DML 1/7/70	32	36	Scrap	Ind.	0.66
"	1/19	"	C-15	C-16	au Coin	1-5 Peso Mex	0.13
"	"	"	C-16	C-17	✓	2-2 Peso Mex	0.10
"	"	"	C-17	C-18	✓	3-2 Peso Mex	0.15
1/14/70	1/20	1/12/70	C-18	C-19	✓	7- Mex Coins: 1-50 Peso 1-20 Peso, 2-10 Peso, 1-2 1/2 Peso 1-3 1/2 Peso	2.64

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
0°	814 1/2	185 1/2	0			\$	\$	\$	\$
460 1/2	115°	424 1/2	23			300 x Lm	Supt. U.S. Mint, Denver, Colo.		
997°	1°	2°	8				Norman Berndt, Mfg. Jeweler, Salt Lake City, Utah		
0°	817°	183°	0				Property Disposal Office, Pueblo Army Depot, Pueblo, Colo.		
854°	44°	102°	0				Bureau of Customs, San Antonio, Texas		
509°	84°	407°	30				Bureau of Customs, San Antonio, Texas		
977°	3°	20°	0				Southwest Texas Precious Metals, San Antonio, Texas		
998 1/2	1°	0 1/2	0				District Director of Customs, El Paso, Texas		
573°	250°	177°	21				Bureau of Customs, Laredo, Texas		
0°	912 3/4	87 1/4	0				Carl Blaurock, Denver, Colo.		
0°	898 3/4	101 1/4	0				Supt. U.S. Mint - Denver, Colo.		
900°	0°	100°	0				✓ ✓ - ✓ ✓		
837°	15°	148°	0				Bureau Customs, Hidalgo, Texas		
866 1/2	25°	108 1/2	0				✓ ✓, Brownsville, Tex		
900°	0°	100°	0				Port Director of Customs, San Antonio, Tex		
900°	0°	100°	0				Bureau of Customs, ✓ ✓ ✓		
900°	54°	46°	0				✓ ✓, Minneapolis, Minn		
898 1/2	0°	101 1/2	0				Bureau Customs, Pembina, North Dakota		
0°	796°	204°	0				✓ ✓, ✓ ✓		
0°	0°	1000°	0				✓ ✓, ✓ ✓		
563°	76°	361°	30			400 x Lm	Ed. Benjamin, San Diego, Calif		
0°	894°	106°	0				Supt. U.S. Mint - Denver, Colo		
0°	899°	101°	0				✓ ✓ - ✓ ✓		
548 1/2	92°	359 1/2	30			270 W.G 11 1/2 x Lm	Southwest Texas Precious Metals, San Antonio, Tex		
303°	123°	574°	0				Supt. U.S. Mint, Denver, Colo		
262 1/2	308°	429 1/2	0				Bureau Customs, El Paso, Texas		
900°	0°	100°	0				✓ ✓, Hidalgo, Texas		
900°	0°	100°	0				✓ ✓, Brownsville, Texas		
900°	0°	100°	0				✓ ✓, El Paso, Texas		
900°	0°	100°	0				✓ ✓, San Antonio, Texas		

DATE 1970			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
1/21	1/23		33	37	Ag Coin	3-S.S. \$'s	247
			34	38	Ag Coin	832-1/2 \$'s	
2/17	2/19		35	39	✓	1188-1/4 \$'s, 5329-1/10 \$'s	1023.28
			36	40	✓	19-S.S. \$'s	15.4
2/27	3/11	DML 2/20/70	C-19	C-20	Ag Coin	72-1/2 \$'s	
3/11	3/16	DML 3/6/70	C-21	C-22	Ag Coin	205-1/4 \$'s, 361-1/10 \$'s	93.30
3/3	3/25	DML 2/24/70	C-20	C-21	Ag Coin	8 Mex Coins: 1-20 Peso, 7-5 Peso	1.40
3/19	✓	DML 3/17/70	37	41	Ind	1 GERMAN COIN: 10 MARKS	1.10
	3/24		38	42	Mut Ag Coin	1-50 Peso Mex	1.30
	✓		39	43	✓	5-5 Peso Mex	
3/31	4/3	GB	1	1	Spains Bar	10-50 " "	14.00
4/13	4/14		40	44	Ind	Pieces & US Bull	17.50
4/23			41	45	Ind	92-S.S. \$'s	17.85
4/23			42	46	Ind	107-1/2 \$'s 1028-1/10 \$'s	
4/23			43	47	Dent	408-1/4 \$'s	205.69
4/22	4/23		44	48	Mut	Grains from 7/1/69 - 3/31/70 +	
4/22	4/23		45	49	Ag Coin	Ag Coins #C-1 thru C-22	58.50
5/13	5/7	DML 4/28/70	C-22	C-23	Ag Coin	1 Bar in exchange for Gold contained in sweeps purchased from Denver Mint	227.51
5/16	5/7	DML 5/4/70	C-23	C-24	✓	Jewelry Scrap, Filings etc	55.91
5/19	5/21		46	50	Mut Ag Coin	Jewelry Scrap, Filings etc	30.40
✓	✓		47	51	✓	Dental Scrap + Filings	16.37
6/2			C-24	C-25	Ag Coin	38 Mut. SS dollars	34.04
6/3	6/8		48	52	Ag Coin	77-1/2 \$, 183-1/4 \$	99.20
✓	✓		49	53	✓	474-1/2 \$	0.54
6/4		DML 4/2/70	C-25	C-26	Ag Coin	1 Mut. V.S. 10.00 Ag Coin	0.64
✓			C-25	C-27	Ag Coin	13-2 Peso Mex	24.66
6/4	6/8	DML 4/2/70	C-25	C-26	Ag Coin	27-S.S. \$'s	40.53
6/11	6/12	SB	6	6	Ag Coin	27-1/2 \$'s; 81-1/4 \$'s; 201-1/10 \$'s	0.53
6/17	6/18		C-26	C-27	Ag Coin	1-20 Peso Mex	13.89
✓			C-27	C-28	Ag Coin	17-Mut Ag \$'s	32.16
						Mut: 23-1/2 \$'s	0.05
						58-1/4 \$'s; 174-1/10 \$'s	0.12
						1-20 Peso Mex	0.17
						1-20 Peso Mex	5.49
						1-20 Peso Mex	0.72
						1-20 Peso Mex	0.01

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
0°	903°	97°	0			\$	\$	\$	\$
0°	896 1/4	103 3/4	0				Supt. U.S. Mint - Denver		
0°	906 3/4	93 1/4	0				✓	✓	✓
0°	903°	97°	0				✓	✓	✓
900°	0°	100°	0				Bureau Customs, Dallas Texas		
900°	0°	100°	0				✓	✓	✓
900°	0°	100°	0				Nogales, Ariz		
825°	167°	8°	0				account Gold Reserve Act - Line		
0°	902 3/4	97 1/4	0				Secretary of the Treasury,		
0°	900°	100°	0				Supt. U.S. Mint, Denver, Colo		
797 1/2	82°	120 1/2	0				✓	✓	✓
999 3/4	0 1/4	0°	0				American Smelting & Refining Co. Crockett, Calif. 94525		
548 1/2	110°	341 1/2	30				Raymond Martinez, P.O. Box 1561 Phoenix, Ariz 85001		
558°	98°	344°	30				✓	✓	✓
622°	117°	261°	30				✓	✓	✓
0°	898 1/2	101 1/2	0				Supt. U.S. Mint, Denver, Colo		
0°	897°	103°	0				" " " "		
882°	0°	118°	0				See letter + phone conversation - Melba + Johnson Denver		
900°	0°	100°	0				Sharon Bridges, Salem, Oregon		
0°	889°	111°	0				Bureau Customs, Roma, Texas		
0°	896 1/4	103 3/4	0				Supt. U.S. Mint - Denver, Colo		
900°	0°	100°	0				✓	✓	✓
0°	905 1/4	94 3/4	0				Bureau Customs, San Antonio, Tex		
0°	901 1/2	98 1/2	0				Supt. U.S. Mint - Denver, Colo		
900°	0°	100°	0				✓	✓	✓
583°	0°	417°	0				Bureau Customs - Brownsville, Tex		
604°	182°	214°	0				Bureau Customs - Brownsville, Texas		
132°	206°	662°	0				Supt. U.S. Mint, Denver, Colo		
642°	134°	224°	0				Port Austin Customs, Dallas, Tex		
900°	0°	100°	0				✓	✓	✓

Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.	OF CHARGES	Gold	Silver	Total
900 ²	0 ²	100 ²	0			\$	Port Director Customs, Dallas, Texas		
613 ²	112 ²	275 ²	0				Supt. U.S. Mints, Denver, Colo		

Start Fiscal 71-72

Form 123
TREASURY DEPARTMENT
MINT SERVICE

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 220500

DATE			NUMBER		MODE OF PAYMENT	DESCRIPTION	WEIGHT AFTER MELTING
Received	Reported	Hour	Receipt	Assay			
1970							
7/22	7/27		1	1	Aq Coin	13 - Mut S.S. \$'s	10.44
7/22	✓		2	2	✓	Mut Aq Coin: 190 1/2 \$'s, 391-1/4 \$'s, 890-1/10 \$'s	211.41
7/22	8/12		C-1	C-1	Au Coins	1-2 1/2 Perso Mex	0.06 P
8/3	✓		C-2	C-2	✓	1-50 } 1-5 } 1-20 } 1-2 } Perso-Mex 1-10 } 1-2 }	238 P
8/17	8/21	Dec DML 7/30/70	C-3	C-3	✓	231 - mex, 4 - U.S., 2 - Kona 1 Sp Au Coin, etc	73.24
8/18	8/21		3	3	Mut Aq Coin	2 - S.S. \$'s	1.61
✓	✓		4	4	Aq Coin	Mut: 32-1/4 \$'s, 18-1/2 \$'s, 76-1/10 \$'s	18.64
8/17	✓	DML 7/30/70 C-3	5	5	Scrap	Scrap	17.55
8/28	9/9	DML 8/27/70	6	6	Scrap	Ind	107 AP
✓	✓	"	7	7	✓	✓	1738 P
✓	✓	"	C-4	C-4	Au Coin	1-500 U.S.	0.26 P
✓	✓	"	C-5	C-5	✓	135 - Mex Au Coins 3 - U.S. Coins, 1 Russ Ruble	50.37 AP
✓	✓	"	C-6	C-6	✓	2 - Mex Meds, 55 - Mex Coins 2 - U.S. Coins	17.39 AP
9/8	9/14	DML 9/14/70	C-7	C-7	✓	25 - Various Coins 1 - Dutch mmm Mex	8.31 AP
✓	✓	"	C-8	C-8	✓	2 - U.S. 30 - Medals 4 - Mex	117 AP
✓	✓	"	8	8	Ind	Jewelry from C-7	3.14 AP
✓	✓	"	9	9	✓	3 Aq medallions	37.16 AP
9/30	10/6	DML 9/30/70	1	1	Grains Bars	2,944 Au Plated Aq med Grains, July, Aug, Sept + C-1 → C-8	4.10
11/18	11/20		10	10	Aq Coin	20-1/4 \$'s 6-1/2 \$'s 75-1/10 "	11.85
12/11			11	11	Aq Coin	Mut: 4- \$'s	3.32
✓			12	12	✓	9-1/2 \$'s, 14-1/4 \$'s, 21-1/10 \$'s	7.66
1971	1971		13	13	Aq Coin	Mut: 5-1/2 \$'s, 4-1/4 \$'s 4-1/10 \$'s	2.73
1/20	2/22		14	14	"	5 Mut S.S. \$'s	4.26
2/18	2/22		15	15	"	Mut: 10-1/2 \$'s 19-1/4 \$'s 12-1/10 \$'s	12.70
3/22	3/22	SB	1	1	C+D #2	From C+D #2 also DMR - Cleanup	12.55
✓	✓		16	16	Mut Aq Silver	13-1/2 \$'s, 10-1/4 \$'s, 28-1/10 \$'s	8.79
4/21	4/23		17	17	Aq Coin	Mut A.S. \$'s - 12	10.24
✓	✓		18	18	✓	Mut Sub Silver Coins 13-1/2 \$'s, 23-1/4 \$'s, 49-1/10 \$'s	12.90
5/20	5/21		19	19	✓	Mut - 7 S.S. \$'s	5.92
✓	✓		20	20	✓	Mut Sub Silver Coins: 24-1/2 \$'s, 36-1/4 \$'s, 76-1/10 \$'s	21.88

0	0	901	0	99	0																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																																															
---	---	-----	---	----	---	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--	--

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt-ing	P. and R.	Bar Chg.		Gold	Silver	Total
999 $\frac{1}{4}$	0°	0 $\frac{3}{4}$			8	\$	\$ American Smelting & Refining Company 120 Broadway, New York, N.Y. 10005		

Fiscal 1972 →

Form 123
TREASURY DEPARTMENT
MINT SERVICE

REGISTER OF ASSAYS,

U. S. GOVERNMENT PRINTING OFFICE 930800

DATE

NUMBER

MODE
OF
PAYMENT

DESCRIPTION

WEIGHT
AFTER
MELTING

Received
1971-1972

Reported

Hour

Receipt

Assay

Mint. Ag

Mint. Sub. silver coin

7/2/71

7/23/71

1

1

Sub.
Duties
Bullion

8 Halves 11 Quarters 22 Dimes
Vacuum Recovery from Refractory
Melt Room + Residual of
Unfit Lots

6.95

3/10/72

3/13/72

SB-1

SB-1

28634

GOLD AND SILVER DEPOSITS

FINENESS			RATE OF CHARGES			AMOUNT OF CHARGES	AMOUNT PAYABLE		
Gold	Silver	Base	Melt- ing	P. and R.	Bar Chg.		Gold	Silver	Total
0 ⁰⁰	900 ¹ / ₄	99 ³ / ₄		0		\$	\$	\$	\$
25 ⁰⁰	142 ⁰⁰	833 ⁰⁰		0					
							Supt. U.S. Mint, Denver		
							Supt. U.S. Mint, Denver, Colo		





